

This document is meant purely as a documentation tool and the institutions do not assume any liability for its contents

► **B**

**COUNCIL REGULATION (EC) No 1255/96  
of 27 June 1996**

**temporarily suspending the autonomous Common Customs Tariff duties on certain industrial and agricultural products**

(OJ L 158, 29.6.1996, p. 1)

Amended by:

	Official Journal		
	No	page	date
► <b><u>M1</u></b> Council Regulation (EC) No 2484/96 of 20 December 1996	L 341	1	30.12.1996
► <b><u>M2</u></b> Council Regulation (EC) No 1186/97 of 27 June 1997	L 172	1	30.6.1997
► <b><u>M3</u></b> Council Regulation (EC) No 2590/97 of 16 December 1997	L 355	1	30.12.1997
► <b><u>M4</u></b> Council Regulation (EC) No 1359/98 of 29 June 1998	L 186	1	30.6.1998
► <b><u>M5</u></b> Council Regulation (EC) No 2797/98 of 17 December 1998	L 352	1	29.12.1998
► <b><u>M6</u></b> Council Regulation (EC) No 1381/1999 of 28 June 1999	L 165	1	30.6.1999

Corrected by:

- **C1** Corrigendum, OJ L 107, 7.4.1998, p. 16 (2590/97)
- **C2** Corrigendum, OJ L 125, 19.5.1999, p. 40 (2797/98)

▼B

**COUNCIL REGULATION (EC) No 1255/96  
of 27 June 1996**

**temporarily suspending the autonomous Common Customs Tariff  
duties on certain industrial and agricultural products**

THE COUNCIL OF THE EUROPEAN UNION,

Having regard to the Treaty establishing the European Community, and in particular Article 28 thereof,

Having regard to the proposal from the Commission,

Whereas production in the Community of the products specified in this Regulation is currently inadequate or non-existent; whereas producers thus cannot meet the needs of user industries in the Community;

Whereas it is in the interest of the Community to suspend partially or totally the autonomous Common Customs Tariff duties for these products;

Whereas the decision to suspend such autonomous duties should be taken by the Community;

Whereas the Regulations temporarily suspending the autonomous Common Customs Tariff duties on certain industrial and agricultural products have largely renewed previous measures; whereas, therefore, in the interests of rationalizing implementation of the measures concerned, it would seem appropriate not to limit the period of validity of this Regulation as its scope can be adapted and products added to or removed from the list through a Council Regulation, if necessary;

Whereas the amendments to the combined nomenclature and the Taric codes do not give rise to any substantive amendment; whereas, for reasons of simplification, provision should be made to empower the Commission, following receipt of the opinion of the Customs Code Committee, to make the necessary amendments and technical adaptations of the Annex to this Regulation, including the publication of a consolidated version,

HAS ADOPTED THIS REGULATION:

*Article 1*

The autonomous Common Customs Tariff duties for the products listed in the Annex hereto shall be suspended at the level indicated against each of them.

*Article 2*

The technical adaptations, including publication of a consolidated version, arising from amendments of the combined nomenclature and Taric codes shall be adopted by the Commission in accordance with the procedure laid down in Article 3.

*Article 3*

1. The Commission shall be assisted by the Customs Code Committee set up by Article 247 of Regulation (EEC) No 2913/92<sup>(1)</sup>.
2. The representative of the Commission shall submit to the Committee a draft of the measures to be taken. The Committee shall deliver its opinion on the draft within a time limit which the chairman may lay down according to the urgency of the matter. The opinion shall be delivered by the majority laid down in Article 148 (2) of the Treaty in the case of decisions which the Council is required to adopt on a proposal from the Commission. The votes of the representatives of the

<sup>(1)</sup> OJ No L 302, 19. 10. 1992, p. 1. Regulation as amended by the 1994 Act of Accession.

**▼B**

Member States within the Committee shall be weighted in the manner set out in that Article. The chairman shall not vote.

3. The Commission shall adopt measures which apply immediately.

However, if these measures are not in accordance with the opinion of the Committee, they shall be communicated by the Commission to the Council forthwith. In that event, the Commission shall defer application of the measures which it has decided for three months from the date of such communication.

The Council, acting by a qualified majority, may take a different decision within the period referred to in the previous indent.

*Article 4*

This Regulation shall enter into force on the day following its publication in the *Official Journal of the European Communities*.

It shall apply from 1 July 1996.

This Regulation shall be binding in its entirety and directly applicable in all Member States.

▼ M5

## ANNEX

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 0603 90 00 ex 0604 99 10 ex 0604 99 90	10 10 10	Flowers, flower buds, foliage, leaves and other parts of plants, not further prepared than dried, dyed or bleached, for use in the manufacture of pot pourri of subheading 3307 49 00 <sup>(a)</sup>	0
ex 0710 21 00	10	Peas in pods, of the species <i>Pisum sativum</i> of the variety <i>Hortense axiphium</i> , frozen, of a thickness not exceeding 6 mm, to be used, in their pods, in the manufacture of prepared meals <sup>(a)</sup> <sup>(b)</sup>	0
ex 0711 90 60 ex 0711 90 60	11 91	Mushrooms, excluding mushrooms of the species <i>Agaricus</i> spp., provisionally preserved in brine, in sulphur water, or in other preservative solutions, but unsuitable in that state for immediate consumption, for the food-canning industry <sup>(a)</sup>	0
ex 0712 30 00 ex 0712 30 00	17 24	Mushrooms, excluding mushrooms of the species <i>Agaricus</i> spp., dried, whole or in identifiable slices or pieces, for treatment other than simple repacking for retail sale <sup>(a)</sup> <sup>(b)</sup>	0
<b>▼ <u>M6</u></b>			
ex 0713 33 90	20	Beans, white, dried, of the species <i>Phaseolus vulgaris</i> , of which not more than 2 % by weight are retained by a screen with apertures of a diameter of 8 mm	0
<b>▼ <u>M5</u></b>			
ex 0804 10 00 ex 0804 10 00	11 21	Dates, fresh or dried, for the processing industry, other than for the production of alcohol <sup>(a)</sup>	0
ex 0804 10 00 ex 0804 10 00	12 22	Dates, fresh or dried, for packing for retail sale into immediate packings of a net content not exceeding 11 kg <sup>(a)</sup>	0
ex 0810 40 50	10	Fruit of the species <i>Vaccinium macrocarpon</i> , fresh	0
ex 0810 90 85	10	Rose-hips, fresh	0
0811 90 50 0811 90 70		Fruit of the genus <i>Vaccinium</i> , uncooked or cooked by steaming or boiling in water, frozen, not containing added sugar or other sweetening matter	
ex 0811 90 95 ex 0811 90 95	66 67		0
ex 0811 90 95	40	Rose-hips, uncooked or cooked by steaming or boiling in water, frozen, not containing added sugar or other sweetening matter	0
ex 1518 00 91	10	Soya-bean oil, modified with maleic acid, for the manufacture of cosmetic products <sup>(a)</sup>	0
ex 2707 99 11	10	Crude light oils containing by weight: — 10 % or more of vinyltoluenes, — 10 % or more of indene and — 1 % or more but not more than 5 % of naphthalene	0
ex 2805 30 10	10	Alloy of cerium and other rare-earth metals, containing by weight 47 % or more of cerium	0
ex 2805 30 10	20	Alloy of lanthanum and other rare-earth metals, containing by weight 43 % or more of lanthanum	0
ex 2805 30 90	10	Lanthanum of a purity by weight of 99 % or more	0
ex 2811 19 80	10	Sulphamidic acid	0
ex 2811 29 90	10	Tellurium dioxide	0
ex 2812 90 00	10	Nitrogen trifluoride	0
ex 2818 30 00	10	Aluminium hydroxide oxide in the form of pseudo-boehmite	4

## ▼M5

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 2819 90 90	10	Dichromium trioxide: — of a specific surface of 37 m <sup>2</sup> /g or more (as determined by the BET method), — of a purity by weight of 99,5 % or more calculated on the dry substance, — of a specific gravity of 1,2 g/cm <sup>3</sup> or less, for the manufacture of magnetic chromium dioxide (*)	0
ex 2820 90 90	10	Manganese (II,III) oxide containing by weight 70 % or more of manganese	0
ex 2821 10 00	10	Diiron trioxide, in the form of powder, of a purity by weight of 99,2 % or more, for the manufacture of goods of heading No 8504 (*)	0
ex 2823 00 00	10	Titanium dioxide, of a purity by weight of 99,9 % or more, with an average grain-size of 1,2 µm or more but not exceeding 1,8 µm, for the manufacture of goods of heading No 8532 or 8533 (*)	0
▼M6			
▼M5			
ex 2825 50 00	10	Copper (I or II) oxide containing by weight 78 % or more of copper and not more than 0,03 % of chloride	0
ex 2826 90 90	10	Potassium hexafluorophosphate	0
ex 2827 39 90	10	Copper monochloride of a purity by weight of 96 % or more but not exceeding 99 %	0
ex 2827 60 00	10	Titanium tetraiodide	0
ex 2830 20 00	10	Zinc sulphide containing: — 20,0 mg/kg or less of chloride, — 0,2 mg/kg or less of copper, — 0,5 mg/kg or less of iron and — 1,0 mg/kg or less of lead	0
ex 2836 91 00	20	Lithium carbonate, containing one or more of the following impurities at the concentrations indicated: — 2 mg/kg or more of arsenic, — 200 mg/kg or more of calcium, — 200 mg/kg or more of chlorides, — 20 mg/kg or more of iron, — 150 mg/kg or more of magnesium, — 20 mg/kg or more of heavy metals, — 300 mg/kg or more of potassium, — 300 mg/kg or more of sodium, — 200 mg/kg or more of sulphates, determined according to the methods specified in the European Pharmacopœia	0
ex 2837 19 00	10	Zinc cyanide	0
ex 2839 90 00	10	Lead silicate hydrate, of a lead content by weight of (84,5 ± 1,5) %, evaluated as lead monoxide, in the form of powder	0
ex 2843 90 90	20	Palladium monoxide	0
ex 2843 90 90	30	Mixture of palladium phthalocyanines	0
2845 10 00		Heavy water (deuterium oxide) ( <i>Euratom</i> )	0
2845 90 10		Deuterium and compounds thereof; hydrogen and compounds thereof, enriched in deuterium; mixtures and solutions containing these products ( <i>Euratom</i> )	0

▼ **M5**

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 2846 10 00	10	Rare-earth concentrate containing by weight 60 % or more but not more than 95 % of rare-earth oxides and not more than 1 % each of zirconium oxide, aluminium oxide or iron oxide, and having a loss on ignition of 5 % or more by weight	0
ex 3824 90 95	48		
ex 2850 00 20	10	Silane	0
ex 2903 30 80	10	Carbon tetrafluoride (tetrafluoromethane)	0
ex 2903 30 80	20	1,1,1,2,3,3,3-Heptafluoropropane	0
ex 2903 30 80	30	Perfluoroethane	0
▼ <b>M6</b>			
ex 2903 30 80	40	1,1-Difluoroethane	0
▼ <b>M5</b>			
ex 2903 59 90	10	1,6,7,8,9,14,15,16,17,17,18,18-Dodecachloropentacyclo-[12.2.1.1 <sup>6,9</sup> .0 <sup>2,13</sup> .0 <sup>5,10</sup> ]octadeca-7,15-diene, for use in the manufacture of polyamide, polyethylene, synthetic rubber or polystyrene <sup>(a)</sup>	0
ex 2903 59 90	20	Hexachlorocyclopentadiene	0
ex 2903 69 90	10	Di- or tetrachlorotricyclo[8.2.2.2 <sup>4,7</sup> ]hexadeca-1(12),4,6,10,13,15-hexaene, mixed isomers	0
ex 2903 69 90	40	2,6-Dichlorotoluene, of a purity by weight of 99 % or more and containing: — 0,001 mg/kg or less of tetrachlorodibenzodioxines, — 0,001 mg/kg or less of tetrachlorodibenzofurans, — 0,2 mg/kg or less of tetrachlorobiphenyls	0
▼ <b>M6</b>			
ex 2903 69 90	50	1-(Chloromethyl)naphthalene	0
▼ <b>M5</b>			
ex 2904 10 00	30	Sodium <i>p</i> -styrenesulphonate	0
ex 2904 20 00	10	Nitromethane	0
ex 2904 20 00	20	Nitroethane	0
ex 2904 20 00	30	1-Nitropropane	0
ex 2904 20 00	40	2-Nitropropane	0
ex 2904 90 20	10	Tosyl chloride	0
ex 2904 90 40	10	Trichloronitromethane, for the manufacture of goods of subheading 3808 20 <sup>(a)</sup>	0
ex 2904 90 85	10	Quintozene (ISO)	0
ex 2905 19 00	10	Potassium <i>tert</i> -butanolate (potassium <i>tert</i> -butoxide), whether or not in the form of a solution in tetrahydrofuran	0
ex 3824 90 95	56		
2905 29 10		Allyl alcohol	0
ex 2905 39 80	10	2-Methylpropane-1,3-diol	0
▼ <b>M6</b>			
▼ <b>M5</b>			
ex 2905 49 10	10	Ethylidynetrimethanol	0
2906 11 00		Menthol	0
ex 2906 19 00	10	Cyclohex-1,4-ylenedimethanol	0
ex 2906 19 00	20	4,4'-Isopropylidenedicyclohexanol	0
ex 2906 29 00	10	2,2'-( <i>m</i> -Phenylene)dipropan-2-ol	0
ex 2907 21 00	10	Resorcinol	0
ex 2907 29 00	10	Disodium 1,4-dihydroanthracene-9,10-diolate, in the form of an aqueous solution	0
ex 2907 29 00	20	4,4'-(3,3,5-Trimethylcyclohexylidene)diphenol	0
ex 2907 29 00	30	4,4',4''-Ethylidynetriphenol	0
ex 2907 29 00	40	Mixture of isomers of methylenediphenol	0

▼ M5

	CN code	TARIC	Description	Rate of autonomous duty (%)
▼ <u>M6</u>	ex 2907 29 00	50	6,6',6"-Tricyclohexyl-4,4',4"-butane-1,1,3-triyltri( <i>m</i> -cresol)	0
▼ <u>M5</u>	ex 2908 20 00	10	Disodium 3-hydroxynaphthalene-2,7-disulfonate	0
	ex 2908 90 00	10	4-Nitroso- <i>o</i> -cresol	0
	ex 2909 19 00	10	1,2-Bis(2-chloroethoxy)ethane	0
	ex 2909 30 90	10	4-( <i>p</i> -Tolyloxy)biphenyl	0
▼ <u>M6</u>	ex 2909 30 90	20	1,2-Bis( <i>m</i> -tolylloxy)ethane	0
	ex 2909 30 90	30	1,2-Diphenoxyethane	0
▼ <u>M5</u>	ex 2909 44 00	10	2-Hexyloxyethanol	0
	ex 2909 50 90	10	4-(2-Methoxyethyl)phenol	0
	ex 2910 90 00	30	2,3-Epoxypropan-1-ol (glycidol)	0
	ex 2910 90 00	40	Perfluoroepoxypropane	0
	ex 2910 90 00	60	1,2-Epoxyoctadecane, of a purity by weight of 82 % or more	0
	ex 3824 90 95	59		0
	ex 2912 29 00	10	Terephthalaldehyde	0
	ex 2912 49 00	10	3-Phenoxybenzaldehyde	0
	ex 2914 19 90	10	3,3-Dimethylbutan-2-one	0
	2914 21 00		Camphor	0
	ex 2914 29 00	10	Estr-4-ene-3,17-dione	0
	ex 2914 50 00	30	2'-Hydroxyacetophenone	0
	ex 2914 50 00	40	4'-Hydroxyacetophenone	0
	ex 2914 50 00	50	6'-Methoxy-2'-acetophenone	0
	ex 2914 70 90	10	1-Chloro-3,3-dimethylbutan-2-one	0
	ex 2914 70 90	30	4,4'-Dibromobenzil	0
	ex 2915 29 00	10	Antimony triacetate	0
	ex 2915 39 90	20	5 $\alpha$ -Bromo-6 $\beta$ -hydroxy-17-oxo-androstan-3 $\beta$ -yl acetate	0
	ex 2915 39 90	30	But-3-ene-1,2-diyl di(acetate)	0
	ex 2915 40 00	10	Vinyl chloroacetate	0
	ex 2915 60 19	10	2,2,4-Trimethylpentane-1,3-diol monoisobutyrate	0
	ex 2915 90 80	20	Trimethyl orthoacetate	0
	ex 2915 90 80	30	2-Ethylbutyric acid	0
	ex 2915 90 80	40	Nonanoic acid (pelargonic acid)	0
	ex 2916 12 90	10	2- <i>tert</i> -Butyl-6-(3- <i>tert</i> -butyl-2-hydroxy-5-methylbenzyl)-4-methylphenyl acrylate	0
	ex 2916 12 90	20	2-Ethoxyethyl acrylate	0
▼ <u>M6</u>	ex 2916 12 90	30	Isobutyl acrylate	0
▼ <u>M5</u>	ex 2916 14 90	10	2,3-Epoxypropyl methacrylate	0
	ex 2916 20 00	10	Methyl 3-(2,2-dichlorovinyl)-2,2-dimethylcyclopropane-carboxylate	0
	ex 2916 20 00	30	Empenthrin (ISO)	0
	ex 2916 39 00	10	Methyl 3-chlorobenzoate	0
	ex 2916 39 00	20	3,5-Dichlorobenzoylchloride	3,6
	ex 2916 39 00	40	Vinyl 4- <i>tert</i> -butylbenzoate	0
	ex 2916 39 00	50	3,5-Dimethylbenzoyl chloride	0
	ex 2916 39 00	60	4-Ethylbenzoyl chloride	0

## ▼M5

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 2917 11 00	20	Bis( <i>p</i> -methylbenzyl) oxalate	0
ex 2917 19 90	20	Sodium 1,2-bis(cyclohexyloxycarbonyl)ethanesulphonate	0
ex 2917 19 90	50	Glutaric anhydride	0
ex 2917 20 00	30	1,4,5,6,7,7-Hexachloro-8,9,10-trinorborn-5-ene-2,3-dicarboxylic anhydride	0
ex 2917 39 80	10	Dimethyl naphthalene-2,6-dicarboxylate	0
ex 2917 39 80	20	Benzene-1,2,4,5-tetracarboxylic acid (pyromellitic acid)	0
ex 2917 39 80	30	Benzene-1,2:4,5-tetracarboxylic dianhydride (pyromellitic dianhydride)	0
ex 2918 13 00	10	L-(-)-Di- <i>p</i> -toluoyltartaric acid	0
ex 2918 17 00	10	<i>R</i> -Phenylglycolic acid (D-mandelic acid)	0
ex 2918 19 99	40	L-Malic acid	0
ex 2918 29 10	10	2-Hydroxy-1-naphthoic acid	0
ex 2918 29 50	10	Gallic acid, of a purity by weight of 99,7 % or more calculated on the dry weight (measured by acidimetry), with a moisture content by weight of less than 10 %, a sulphated ash content by weight of less than 0,06 %, an iron content of less than 8 mg/kg and an iodine colour number not exceeding 3 on the DIN 6162 scale	0
ex 2918 29 90	10	Hexamethylene bis[3-(3,5-di- <i>tert</i> -butyl-4-hydroxyphenyl)propionate]	0
ex 2919 00 90	10	2,2'-Methylenebis(4,6-di- <i>tert</i> -butylphenyl) phosphate, monosodium salt	0
ex 2920 10 00	10	Fenitrothion (ISO)	0
ex 2920 10 00	20	Tolclofos-methyl (ISO)	0
ex 2920 90 10	10	Diethyl sulphate	0
2920 90 30		Trimethyl phosphite	0
ex 2920 90 85	10	<i>O,O'</i> -Dioctadecylpentaerythritol bis(phosphite)	0
ex 2920 90 85	30	<i>O,O'</i> -Bis(2,4-di- <i>tert</i> -butylphenyl)pentaerythritol bis(phosphite)	0
ex 2921 19 80	10	Triallylamine	0
ex 2921 19 80	20	Ethyl(2-methylallyl)amine	0
ex 2921 29 00	10	<i>N,N,N',N'</i> -Tetrabutylhexamethylenediamine	0
ex 2921 29 00	20	Tris[3-(dimethylamino)propyl]amine	0
ex 2921 29 00	30	Bis[3-(dimethylamino)propyl]methylamine	0
ex 2921 30 99	10	Dicyclohexyl(methyl)amine	0
ex 2921 42 10	10	2,6-Dichloro-4-nitroaniline	0
ex 2921 42 10	20	2-Bromo-4,6-dinitroaniline	0
ex 2921 42 10	30	4-Aminobenzene-1,3-disulphonic acid and its salts	0
ex 2921 42 10	40	2-Bromo-6-chloro-4-nitroaniline	0
ex 2921 43 00	10	5-Amino-2-chlorotoluene-4-sulphonic acid	0
ex 2921 43 00	20	4-Amino-6-chlorotoluene-3-sulphonic acid	0
ex 2921 44 00	10	Methyldiphenylamine	0
ex 2921 45 00	10	3-Aminonaphthalene-1,5-disulphonic acid, monosodium salt	0
ex 2921 45 00	20	2-Aminonaphthalene-1,5-disulphonic acid and its sodium salts	0
ex 2921 45 00	30	2-Aminonaphthalene-1-sulfonic acid	0
ex 2921 49 10	20	Pendimethalin (ISO)	3,5
ex 2921 49 90	10	8-Anilinonaphthalene-1-sulphonic acid	0
ex 2921 59 90	10	Mixture of isomers of 3,5-diethyltoluenediamine	0

▼ **M5**

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 2922 19 90	55	4,4-Dimethoxybutylamine	0
ex 2922 19 90	60	2-[2-(Dimethylamino)ethyl(methyl)amino]ethanol	0
ex 2922 19 90	70	<i>N,N,N',N'</i> -Tetramethyl-2,2'-oxybis(ethylamine)	0
ex 2922 21 00	10	2-Amino-5-hydroxynaphthalene-1,7-disulphonic acid and its salts, of a purity by weight of 60 % or more	0
ex 2922 21 00	20	4-Hydroxy-7-methylaminonaphthalene-2-sulphonic acid	0

▼ **M6**

ex 2922 21 00	30	6-Amino-4-hydroxynaphthalene-2-sulfonic acid	0
ex 2922 21 00	40	7-Amino-4-hydroxynaphthalene-2-sulfonic acid	0

▼ **M5**

ex 2922 22 00	10	<i>o</i> -Anisidine	0
ex 2922 29 00	10	2-Methyl- <i>N</i> -phenyl- <i>p</i> -anisidine	0
ex 2922 29 00	20	3-Aminophenol	0
ex 2922 29 00	30	4-Amino-5-methoxy-2-methylbenzenesulphonic acid	0
ex 2922 29 00	40	2-Amino-4- <i>tert</i> -pentyl-6-nitrophenol	0
ex 2922 29 00	50	6-Methoxy- <i>m</i> -toluidine	0
ex 2922 29 00	60	3,5-Dichloro-4-(1,1,2,2-tetrafluoroethoxy)aniline	0
ex 2922 29 00	70	4-Nitro- <i>o</i> -anisidine	0
ex 2922 30 00	10	1-Amino-4-bromo-9,10-dioxoanthracene-2-sulphonic acid and its salts	0
ex 2922 30 00	20	1-Aminoanthraquinone	0
ex 2922 50 00	50	2-(4-Dibutylaminosalicyloyl)benzoic acid	0
ex 2923 90 00	10	Tetramethylammonium hydroxide, in the form of an aqueous solution containing: — (25 ± 0,5) % by weight of tetramethylammonium hydroxide, — 500 mg/kg or less of carbonate, — 200 mg/kg or less of chloride and — 5 mg/kg or less of potassium	0
ex 2924 10 00	20	2-Acrylamido-2-methylpropanesulphonic acid and its sodium or ammonium salts	0
ex 2924 10 00	30	<i>N</i> -(1,1-Dimethyl-3-oxobutyl)acrylamide	0

▼ **M6**

ex 2924 21 90	10	4,4'-Dihydroxy-7,7'-ureylenedi(naphthalene-2-sulphonic acid) and its sodium salts	0
ex 3824 90 95	62		

▼ **M5**

ex 2924 29 90	10	Alachlor (ISO)	0
ex 2924 29 90	15	Acetochlor (ISO)	0
ex 2924 29 90	20	3'-Amino-4'-methoxyacetanilide	0
ex 2924 29 90	25	3'-Diethylaminoacetanilide	0
ex 2924 29 90	30	5-Amino- <i>N,N'</i> -bis(2,3-dihydroxypropyl)-2,4,6-triiodoisophthalamide	0
ex 2924 29 90	35	Propachlor (ISO)	0
ex 2924 29 90	40	Diethofencarb (ISO)	0

▼ **M6**

ex 2924 29 90	45	7-Acetamido-4-hydroxynaphthalene-2-sulfonic acid and its sodium salts	0
---------------	----	---	---

▼ **M5**

ex 2924 29 90	50	3'-Diethylamino-4'-methoxyacetanilide	0
ex 2924 29 90	60	5-[ <i>N</i> -(2-Acetoxyethyl)acetoxyacetamido]- <i>N,N'</i> -bis(2,3-diacetoxy-propyl)-2,4,6-triiodoisophthalamide	0
ex 2924 29 90	70	4'-Amino- <i>N</i> -methylacetanilide	0

## ▼M5

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 2924 29 90	80	5-Acetylsalicylamide	0
ex 2925 11 00	20	Saccharin and its sodium salt	0
ex 2925 19 80	10	<i>N</i> -Phenylmaleimide	0
ex 2925 20 00	10	Dicyclohexylcarbodiimide	0
ex 2926 90 99	10	Methacrylonitrile	0
ex 2926 90 99	30	2-Amino-5-nitrobenzotrile	0
ex 2926 90 99	40	Chlorothalonil (ISO)	0
ex 2926 90 99	45	2-Cyanoacetamide	0
ex 2926 90 99	50	Alkyl or alkoxyalkyl esters of cyanoacetic acid	0
ex 2926 90 99	60	Cyanoacetic acid in crystalline form	0
ex 2926 90 99	65	Malononitrile	0
ex 2927 00 00	10	2,2'-Dimethyl-2,2'-azodipropionamide dihydrochloride	0
ex 2927 00 00	20	4-Anilino-2-methoxybenzenediazonium hydrogen sulphate	0
ex 2928 00 90	10	3,3'-Bis(3,5-di- <i>tert</i> -butyl-4-hydroxyphenyl)- <i>N,N'</i> -bipropionamide	0
ex 2928 00 90	20	2,4,6-Trichlorophenylhydrazine	0
ex 2928 00 90	30	<i>tert</i> -Butylhydrazine hydrochloride, for the manufacture of goods of subheading 3808 10 (*)	0
ex 2929 10 90	10	Methylenedicyclohexyl diisocyanate, mixed isomers	0
ex 2929 10 90	30	3,3'-Dimethylbiphenyl-4,4'-diyl diisocyanate	0
ex 2929 10 90	40	<i>m</i> -Isopropenyl- $\alpha,\alpha$ -dimethylbenzyl isocyanate	0
ex 2929 10 90	50	<i>m</i> -Phenylenediisopropylidene diisocyanate	0
ex 2929 10 90	60	Trimethylhexamethylene diisocyanate, mixed isomers	0
ex 2930 90 70	10	Thiophenol	0
ex 2930 90 70	15	Ethoprophos (ISO)	0
ex 2930 90 70	20	3,3-Dimethyl-1-methylthiobutanone oxime	0
ex 2930 90 70	25	Thiophanate-methyl (ISO)	0
ex 2930 90 70	30	4-(4-Isopropoxyphenylsulphonyl)phenol	0
ex 2930 90 70	40	3,3'-Thiodi(propionic acid)	0
ex 2930 90 70	45	2-[( <i>p</i> -Aminophenyl)sulphonyl]ethyl hydrogen sulphate	0
ex 2930 90 70	50	2-Chlorophenylsulfonyl isocyanate, in the form of a solution in xylene	0
ex 3824 90 95	51		
ex 2930 90 70	55	Methyl 2-(isocyanatosulfonyl)methylbenzoate, in the form of a solution in xylene	0
ex 3824 90 95	52		
▼M6			
ex 2930 90 70	60	Methyl phenyl sulfide	0
▼M5			
2931 00 10		Dimethyl methylphosphonate	0
ex 2931 00 95	10	2-Diphenylphosphinobenzoic acid	0
ex 2931 00 95	15	Chlorodiphenylphosphine	0
ex 2931 00 95	20	Bis(2-chloroethyl) 2-chloroethylphosphonate	0
ex 2931 00 95	25	Sodium phenylphosphinate	0
ex 2931 00 95	30	Bis(2-chloroethyl)vinylphosphonate	0
ex 2931 00 95	35	Sodium tetraphenylborate	0
ex 2931 00 95	40	<i>N</i> -(Phosphonomethyl)iminodiacetic acid	0
ex 2931 00 95	45	Tributylphosphine	0
ex 2931 00 95	50	Bis(2,4,4-trimethylpentyl)phosphinic acid	0
ex 2931 00 95	55	Dimethyl[dimethylsilyldiindenyl]hafnium	0
ex 2931 00 95	60	Trioctylphosphine oxide	0

▼ M5

CN code	TARIC	Description	Rate of autonomous duty (%)
<b>▼ <u>M6</u></b>			
ex 2931 00 95	65	Triethylborane	0
<b>▼ <u>M5</u></b>			
ex 2932 11 00	10	Tetrahydrofuran, containing not more than 40 mg per litre in total of tetrahydro-2-methylfuran and tetrahydro-3-methylfuran, for the manufacture of <i>α</i> -4-hydroxybutyl- <i>ω</i> -hydroxypoly(oxytetramethylene) (*)	0
ex 2932 13 00	10	Tetrahydrofurfuryl alcohol	0
ex 2932 19 00	40	Furan of a purity by weight of 99 % or more	0
ex 2932 19 00	50	2,3-Dihydrofuran	0
ex 2932 29 80	10	2'-Anilino-6'-[ethyl(isopentyl)amino]-3'-methylspiro[isobenzofuran-1(3 <i>H</i> ),9'-xanthen]-3-one	0
ex 2932 29 80	15	13,14,15,16-Tetranorlabdano-12,8 $\alpha$ -lactone	0
ex 2932 29 80	25	2'-(2-Chloroanilino)-6'-dibutylaminospiro[isobenzofuran-1(3 <i>H</i> ),9'-xanthen]-3-one	0
ex 2932 29 80	30	2'-Anilino-3'-methyl-6'-methyl(propyl)aminospiro[isobenzofuran-1(3 <i>H</i> ),9'-xanthen]-3-one	0
ex 2932 29 80	35	6'-Diethylamino-3'-methyl-2'-(2,4-xylydino)spiro[isobenzofuran-1(3 <i>H</i> ),9'-xanthen]-3-one	0
ex 2932 29 80	40	2'-Anilino-6'-( <i>N</i> -ethyl- <i>p</i> -toluidino)-3'-methylspiro[isobenzofuran-1(3 <i>H</i> ),9'-xanthen]-3-one	0
ex 2932 29 80	45	2'-Anilino-6'-ethyl(isobutyl)amino-3'-methylspiro[isobenzofuran-1(3 <i>H</i> ),9'-xanthen]-3-one	0
ex 2932 29 80	50	2'-Anilino-6'-cyclohexyl(methyl)amino-3'-methylspiro[isobenzofuran-1(3 <i>H</i> ),9'-xanthen]-3-one	0
ex 2932 29 80	55	6-Dimethylamino-3,3-bis(4-dimethylaminophenyl)phthalide	0
ex 2932 99 70	10	Bendiocarb (ISO)	0
ex 2932 99 70	20	Androsta-1,4-diene-3,17-dione 17-(2,2-dimethylpropylene) acetal	0
ex 2933 21 00	10	Hydantoin	0
ex 2933 21 00	20	2-(3-Benzyl-2,5-dioxoimidazolidin-1-yl)-2'-chloro-5'-(3-dodecyl-sulphonyl-2-methylpropionamido)-4,4-dimethyl-3-oxovaleranimide	0
ex 2933 21 00	30	3'-[4,4-Dimethyl-2-(4,4-dimethyl-2,5-dioxoimidazolin-1-yl)-3-oxovaleryl-amino]-4'-methoxystearanimide	0
ex 2933 21 00	40	1-[1,3-Bis(hydroxymethyl)-2,5-dioxoimidazolidin-4-yl]-1,3-bis(hydroxymethyl)urea	0
ex 2933 29 90	20	Reaction product consisting of the methyl esters of ( $\pm$ )-6-(4-isopropyl-4-methyl-5-oxo-2-imidazolin-2-yl)- <i>m</i> -toluic acid and ( $\pm$ )-2-(4-isopropyl-4-methyl-5-oxo-2-imidazolin-2-yl)- <i>p</i> -toluic acid (Imazamethabenz-methyl)	4
ex 2933 29 90	40	Triflumizole (ISO)	0
ex 2933 39 95	10	Cloperastine fendizoate (INNMI)	0
ex 2933 39 95	15	Pyridine-2,3-dicarboxylic acid	0
ex 2933 39 95	20	5-Methyl-2-pyridylamine	0
ex 2933 39 95	25	Imazethapyr (ISO)	0
ex 2933 39 95	30	4,4'-Trimethylenedipiperidine	0
<b>▼ <u>M6</u></b>			
ex 2933 39 95	35	3,5-Dimethylpiperidine	0
<b>▼ <u>M5</u></b>			
ex 2933 40 10	10	Quinmerac (ISO)	0
ex 2933 40 90	20	5,7-Dichloro-4-(4-fluorophenoxy)quinoline	0
ex 2933 40 90	30	1,2,3,4-Tetrahydroisoquinoline-3-carboxylic acid	0
ex 2933 40 90	40	<i>N</i> -Ethyl-5,6,7,8-tetrahydroquinolinium <i>p</i> -toluenesulphonate, in the form of a solution in water	0

▼ M5

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 2933 59 70	10	1-Ethyl-6-fluoro-1,4-dihydro-4-oxo-7-piperazin-1-yl-1,8-naphthyridine-3-carboxylic acid and its salts and esters	0
▼ <u>M6</u>			
ex 2933 59 70	20	2,4-Diamino-6-chloropyrimidine	0
▼ <u>M5</u>			
ex 2933 69 80	10	1,3,5-Tris(4- <i>tert</i> -butyl-3-hydroxy-2,6-dimethylbenzyl)-1,3,5-triazine-2,4,6(1 <i>H</i> ,3 <i>H</i> ,5 <i>H</i> )-trione	0
ex 2933 69 80	20	1,3,5-Tris[(3,5-di- <i>tert</i> -butyl-4-hydroxyphenyl)methyl]-1,3,5-triazine-2,4,6(1 <i>H</i> ,3 <i>H</i> ,5 <i>H</i> )-trione	0
ex 2933 69 80	40	Cyanazine (ISO)	0
ex 2933 90 50	10	Azepane, for the manufacture of goods of subheading 3808 30 (*)	0
ex 2933 90 95	10	2-(2 <i>H</i> -Benzotriazol-2-yl)-4,6-di- <i>tert</i> -butylphenol	0
ex 2933 90 95	15	2-(2 <i>H</i> -Benzotriazol-2-yl)-4,6-di- <i>tert</i> -pentylphenol	0
ex 2933 90 95	20	2-(2 <i>H</i> -Benzotriazol-2-yl)-4,6-bis(1-methyl-1-phenylethyl)-phenol	0
ex 2933 90 95	25	6,6'-Di-2 <i>H</i> -benzotriazol-2-yl-4,4'-bis(1,1,3,3-tetramethylbutyl)-2,2'-methylenediphenol	0
ex 2933 90 95	30	Quizalofop-P-ethyl (ISO)	0
ex 2933 90 95	35	Indoline	0
ex 2933 90 95	45	Maleic hydrazide (ISO)	0
ex 2933 90 95	50	Metconazole (ISO)	3,2
ex 2933 90 95	55	5-Nitroindole	0
ex 2933 90 95	60	1,3-Bis(3-isocyanatomethylphenyl)-1,3-diazetidone-2,4-dione (dimeric 2,4-toluene diisocyanate)	0
ex 2933 90 95	65	Candesartan cilexetil (INN)	0
ex 2934 10 00	10	Hexythiazox (ISO)	0
ex 2934 10 00	20	2-(4-Methylthiazol-5-yl)ethanol	0
ex 2934 20 80	10	4-Chloro-1,3-benzothiazol-2(3 <i>H</i> )-one	0
ex 2934 90 96	10	7-Chloro-5-methyl-2 <i>H</i> -1,4-benzothiazin-3-(4 <i>H</i> )-one	0
ex 2934 90 96	15	Carboxin (ISO)	0
ex 2934 90 96	20	4-[4-(Tridecyl[branched]oxy)phenyl]-1,4-thiazinane 1,1-dioxide	0
ex 2934 90 96	25	Oxycarboxin (ISO)	0
ex 2934 90 96	30	Etridiazole (ISO)	0
ex 2934 90 96	35	Dimethenamide (ISO)	0
ex 2934 90 96	40	2,3,5,6-Tetrahydroxy-1,4-diisobutyl-1,4-dioxo-1,4-diphosphinane	0
ex 2934 90 96	45	Tris(2,3-epoxypropyl)-1,3,5-triazinetrione	0
ex 2934 90 96	50	1-[2-(1,3-Dioxan-2-yl)ethyl]-2-ethylpyridinium bromide	0
▼ <u>M6</u>			
ex 2934 90 96	55	Naphth[1,2- <i>d</i> ][1,2,3]oxadiazole-5-sulfonic acid	0
▼ <u>M5</u>			
ex 2935 00 90	10	Salts of sulfathiazole (INN)	0
ex 2935 00 90	20	Toluenesulphonamides	0
ex 2935 00 90	30	Mixture of isomers consisting of <i>N</i> -ethyltoluene-2-sulphonamide and <i>N</i> -ethyltoluene-4-sulphonamide	0
ex 2935 00 90	40	1-(4,6-Dimethoxypyrimidin-2-yl)-3-(2-ethylsulphonylimidazo[1,2- <i>a</i> ]pyridin-3-ylsulphonyl)urea (sulfosulfuron)	0
ex 2935 00 90	50	4,4'-Oxydi(benzenesulfonohydrazide)	0
ex 2935 00 90	60	5-Amino- <i>N</i> -(2,6-dichloro- <i>m</i> -tolyl)-1 <i>H</i> -1,2,4-triazole-3-sulphonamide	0
ex 2935 00 90	70	Methyl 3-aminosulphonylthiophene-2-carboxylate	0



## ▼M5

CN code	TARIC	Description	Rate of autonomous duty (%)
		— 13-ethyl-3-[4-(morpholino)phenyl]-3-phenyl-3,13-dihydrobenzo-[h]indeno[2,1-f]chromen-13-ol	0
ex 3215 90 80	10	Ink formulation, for use in the manufacture of ink-jet cartridges <sup>(a)</sup>	0
3301 12 10		Essential oil of orange, not deterpenated	0
ex 3402 90 10	20	Mixture of docusate sodium (INN) and sodium benzoate	0
ex 3402 90 10	30	Non-aqueous surface-active preparation, containing: — polyethylene glycol alkylphenyl ether, — 2,4,7,9-tetramethyldec-5-yne-4,7-diol and — phosphoric acid esters	0
ex 3402 90 90	10	Crystalline powder obtained by the reaction of trisodium phosphate with a mixture of sodium hypochlorite and sodium chloride (chlorinated trisodium phosphate), containing by weight: — 3,5 % or more of available chlorine, measured iodometrically and — 17,0 % or more of phosphorus evaluated as P <sub>2</sub> O <sub>5</sub>	0
ex 3504 00 00	10	Purified antigens obtained from genetically manipulated yeast cells, for the manufacture of detection tests for hepatitis-C <sup>(a)</sup>	0
ex 3504 00 00	20	Glycoprotein 160 obtained from Human Immunodeficiency Virus, HIV-1 strain	0
ex 3505 10 50	20	<i>O</i> -(2-Hydroxyethyl)-derivative of hydrolysed waxy maize starch	0
ex 3506 91 00	10	Adhesive based on an aqueous dispersion of a mixture of dimerised rosin and a copolymer of ethylene and vinyl acetate (EVA)	0
ex 3506 91 00	20	Heat-activated adhesive based on phenolic resin and rubber, in the form of a film on a release paper, for use in the manufacture of brake pads for the automotive industry <sup>(a)</sup>	0
ex 3507 90 90	10	Asparaginase	0
ex 3507 90 90	20	Enzymatic preparation based on thermolysine	0
ex 3507 90 90	40	Avian myeloblastosis virus (AMV) reverse transcriptase	0
ex 3701 30 00	10	Letterpress printing plates, consisting of a metal substrate covered with a photopolymer layer, of a total thickness of 0,5 mm or more but not exceeding 0,8 mm	0
ex 3701 99 00	10	Plate of quartz or of glass, covered with a film of chromium and coated with a photosensitive or electron-sensitive resin, for the manufacture of masks for the goods of heading No 8541 or 8542 <sup>(a)</sup>	0
ex 3702 43 00	10	Photographic film, of a nominal width of 459, 669 or 761 mm, composed of several layers, including two polyester films, a carbon layer, an adhesive layer and a layer of a copolymer of styrene with acrylonitrile	0
ex 3702 44 00	10		
ex 3703 90 10	10	Paper sheet, coated with silver halide emulsion, for the manufacture of goods of subheading 3701 20 00 <sup>(a)</sup>	0
ex 3707 10 00	10	Photosensitive emulsion for the sensitisation of silicon discs <sup>(a)</sup>	0
ex 3707 90 30	10	Toner, in the form of powder, consisting of a copolymer of styrene and butyl acrylate and magnetite, for use as a developer in the manufacture of cartridges for facsimile machines <sup>(a)</sup>	0
3805 20 00		Pine oil	1,7
ex 3808 20 80	10	Fungicide in the form of a powder, containing by weight 65 % or more but not more than 75 % of hymexazole (ISO), not put up for retail sale	0

## ▼M5

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 3808 40 20	10	Preparation containing by weight: — 58 % or more but not more than 62 % of 1-bromo-3-chloro-5,5-dimethylhydantoin, — 26 % or more but not more than 29 % of 1,3-dichloro-5,5-dimethylhydantoin, — 10 % or more but not more than 12 % of 1,3-dichloro-5-ethyl-5-methylhydantoin,  for the manufacture of swimming-pool disinfectants (a)	0
ex 3808 40 90	10	1-Dodecylguanidine hydrochloride, in the form of a solution in isopropanol and water, containing by weight 40 % or less of 1-dodecylguanidine hydrochloride	0
ex 3809 91 00	10	Mixture of 5-ethyl-2-methyl-2-oxo-1,3,2λ <sup>5</sup> -dioxaphosphoran-5-ylmethyl methyl methylphosphonate and bis(5-ethyl-2-methyl-2-oxo-1,3,2λ <sup>5</sup> -dioxaphosphoran-5-ylmethyl) methylphosphonate	0
ex 3809 92 00	10	Paper anti-fading agent, consisting of a mixture of magnesium trisilicate and monosodium salt of 2,2'-methylenebis(4,6-di- <i>tert</i> -butylphenyl) phosphate	0
ex 3811 21 00	10	Salts of dinonylnaphthalenesulphonic acid, in the form of a solution in mineral oils	0
ex 3812 30 80	10	Tetraaluminium nonamagnesium dicarbonate hexacosahydroxide heptahydrate, coated with a surface-active agent	0
ex 3812 30 80	20	Mixture containing predominantly bis(2,2,6,6-tetramethyl-1-octyloxy-4-piperidyl) sebacate	0
ex 3812 30 80	30	Compound stabilisers containing by weight 15 % or more but not more than 40 % of sodium perchlorate and not more than 70 % of 2-(2-methoxyethoxy)ethanol	0
ex 3812 30 80	40	Dialuminium tetramagnesium monocarbonate dodecahydroxide monohydrate, coated with a surface-active agent	0
ex 3812 30 80	50	Aluminium magnesium zinc hydroxide carbonate hydrate, coated with a surface-active agent	0
ex 3814 00 90	10	Mixture containing by weight 25 % or more but not more than 35 % of dimethyl sulfoxide and 65 % or more but not more than 75 % of monoethanolamine	3
ex 3815 12 00	10	Catalyst, in the form of granules or rings of a diameter of 3 mm or more but not exceeding 10 mm, consisting of silver on an aluminium oxide support and containing by weight 8 % or more but not more than 20 % of silver	0
ex 3815 12 00	20	Catalyst consisting of palladium and rhenium, fixed on a support of active carbon, in the form of powder, containing: — 0,5 % or more but not more than 1,5 % by weight of palladium, — 3 % or more but not more than 5 % by weight of rhenium and — 0,1 mole % or more but not more than 1 mole % of alkaline metals,  for use in the manufacture of tetrahydrofuran (a)	0
ex 3815 19 90	10	Catalyst, consisting of chromium trioxide or dichromium trioxide fixed on a support of silicon dioxide, of a pore volume, as determined by the nitrogen absorption method, of 2 cm <sup>3</sup> /g or more	0
ex 3815 19 90	15	Catalyst, in the form of a powder, consisting of a mixture of metal oxides fixed on a support of silicon dioxide, containing by weight 20 % or more but not more than 40 % of molybdenum, bismuth and iron evaluated together, for use in the manufacture of acrylonitrile (a)	0
ex 3815 19 90	20	Catalyst consisting of chromium oxides and titanium dioxide fixed on a support of silicon dioxide, aluminium oxide or aluminium phosphate	0

## ▼M5

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 3815 19 90	30	Catalyst containing titanium tetrachloride supported on magnesium dichloride, for use in the manufacture of polypropylene (*)	0
ex 3815 19 90	40	Catalyst, in the form of spheres of a diameter of 4,2 mm or more but not exceeding 9 mm, consisting of a mixture of oxides of molybdenum, tungsten, vanadium, copper and strontium, on a support of silicon dioxide and/or aluminium oxide, for use in the manufacture of acrylic acid (*)	0
▼M6 ex 3815 19 90	45	Catalyst, consisting predominantly of dichromium copper tetraoxide and copper (II) oxide, containing by weight 38 % or more but not more than 48 % of copper, evaluated as copper (II) oxide, fixed on a support of silicon dioxide, for the hydrogenation of acetophenones (*)	0
▼M5 ex 3815 19 90	50	Catalyst consisting of organo-metallic compounds of titanium, magnesium and aluminium on a support of silicon dioxide, in the form of a suspension in tetrahydrofuran	0
ex 3815 19 90	55	Catalyst consisting of a mixture of metal oxides containing chromium trioxide, fixed on a support of silicon dioxide	0
ex 3815 19 90	60	Catalyst consisting of dichromium trioxide, fixed on a support of aluminium oxide	0
ex 3815 19 90	65	Catalyst consisting of phosphoric acid chemically bonded to a support of silicon dioxide	0
ex 3815 19 90	70	Catalyst consisting of organo-metallic compounds of aluminium and zirconium, fixed on a support of silicon dioxide	0
ex 3815 19 90	75	Catalyst consisting of organo-metallic compounds of aluminium and chromium, fixed on a support of silicon dioxide	0
ex 3815 19 90	80	Catalyst consisting of organo-metallic compounds of magnesium and titanium, fixed on a support of silicon dioxide, in the form of a suspension in mineral oil	0
ex 3815 19 90	85	Catalyst consisting of organo-metallic compounds of aluminium, magnesium and titanium, fixed on a support of silicon dioxide, in the form of powder	0
ex 3815 90 90	15	Catalyst, consisting of a mixture of oxides containing by weight more than 96 % of oxides of molybdenum, vanadium, nickel and antimony, whether or not mixed with porcelain balls, for use in the manufacture of acrylic acid (*)	0
ex 3815 90 90	20	Catalyst, in powder form, consisting of a mixture of titanium trichloride and aluminium chloride, containing by weight: — 20 % or more but not more than 30 % of titanium and — 55 % or more but not more than 72 % of chlorine	0
ex 3815 90 90	25	Catalyst, consisting of a mixture of oxides containing by weight more than 96 % of oxides of molybdenum, bismuth, nickel, iron and silicon, whether or not mixed with porcelain balls, for use in the manufacture of acrylaldehyde (*)	0
ex 3815 90 90	30	Catalyst, in the form of a powder, containing by weight 82 % or more of copper and of a specific surface of 0,5 m <sup>2</sup> /g or more but not exceeding 8 m <sup>2</sup> /g	0
ex 3815 90 90	35	Catalyst, in the form of a suspension in oil, consisting of titanium trichloride and aluminium trichloride, containing by weight (on an oil-free basis): — 15 % or more but not more than 30 % of titanium and — 40 % or more but not more than 72 % of chlorine	0

▼ M5

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 3815 90 90	40	Catalyst, in the form of rodlets of a length of 5 mm or more but not exceeding 8 mm, consisting of a mixture of oxides of iron, molybdenum and bismuth, for use in the manufacture of acrylic acid (*)	0
ex 3815 90 90	50	Catalyst containing titanium trichloride, in the form of a suspension in hexane or heptane containing by weight, in the hexane- or heptane-free material, 9 % or more but not more than 30 % of titanium	0
ex 3815 90 90	55	Reaction initiator, consisting of a mixture of <i>N,N,N',N'</i> -tetramethyl-2,2'-oxybis(ethylamine) and dipropylene glycols	0
ex 3815 90 90	60	Catalyst, in the form of rodlets, consisting of an acid aluminosilicate (zeolite): — with a mole-ratio of silicon dioxide: dialuminium trioxide of not less than 500: 1 and — containing by weight 0,2 % or more but not more than 0,8 % of platinum	0
ex 3815 90 90	65	Catalyst based on a mordenite zeolite, in the form of granules, for use in the manufacture of mixtures of methylamines containing by weight 50 % or more of dimethylamine (*)	0
ex 3815 90 90	70	Catalyst, consisting of a mixture of (2-hydroxypropyl)trimethylammonium formate and dipropylene glycols	0
▼ <u>M6</u>			
ex 3815 90 90	75	Catalyst, consisting of a mixture of 1,4-diazabicyclo[2.2.2]octane, 2-hydroxyethyliminodi(acetic acid) and dibutyltin di(acetate), containing by weight 5 % or more but not more than 10 % of 1,4-diazabicyclo[2.2.2]octane	0
▼ <u>M5</u>			
ex 3815 90 90	80	Catalyst consisting predominantly of dinonylnaphthalene-disulphonic acid in the form of a solution in isobutanol	0
▼ <u>M6</u>			
ex 3815 90 90	81	Catalyst, containing by weight 38 % or more but not more than 48 % of (2-hydroxy-1-methylethyl)trimethylammonium 2-ethylhexanoate	0
ex 3815 90 90	82	Catalyst, containing by weight 35 % or more but not more than 55 % of (2-hydroxy-1-methylethyl)trimethylammonium formate and formic acid	0
ex 3815 90 90	83	Catalyst, in the form of powder, containing aluminium magnesium hydroxide hydrate, rare-earth metals oxides and divanadium pentaoxide	0
ex 3815 90 90	85	Catalyst based on aluminosilicate (zeolite), for the transalkylation of alkylaromatic hydrocarbons or the oligomerisation of olefins (*)	0
▼ <u>M5</u>			
ex 3818 00 10	10	Silicon discs, with phosphorus diffused into one side, of a thickness not exceeding 310 µm, for use in the manufacture of semiconductor devices of heading No 8541 (*)	0
ex 3818 00 10	20	Wafer of monocrystalline silicon, with a layer of silicon oxide covered with a layer of deposited silicon, with a diameter of more than 98 mm but not exceeding 202 mm	0
ex 3818 00 90	10	Wafers of gallium phosphide, with epitaxial layers of gallium arsenide phosphide, doped, for the manufacture of goods of subheading 8541 40 19 (*)	0
ex 3818 00 90	20	Wafers of indium phosphide, doped	0

## ▼M5

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 3823 19 10	91	Mixture of fatty acids containing by weight: — 2 % or more but not more than 6 % of hexanoic acid, — 53 % or more but not more than 60 % of octanoic acid, — 34 % or more but not more than 42 % of decanoic acid and — not more than 2 % of dodecanoic acid	0
ex 3824 90 15	10	Acid aluminosilicate (artificial zeolite of the Y type) in the sodium form, containing by weight not more than 11 % of sodium evaluated as sodium oxide, in the form of rodlets	0
ex 3824 90 64	01	Intermediate products of the antibiotics manufacturing process obtained from the fermentation of <i>Micromonospora purpurea</i> , whether or not dried	0
ex 3824 90 64	02	Cholic acid and 3 $\alpha$ ,12 $\alpha$ -dihydroxy-5 $\beta$ -cholan-24-oic acid (deoxycholic acid), crude	0
ex 3824 90 64	03	Products obtained by the <i>N</i> -ethylation of sisomycin (INN)	0
ex 3824 90 64	04	Intermediate products of the antibiotics manufacturing process obtained from the fermentation of <i>Micromonospora inyoensis</i> , whether or not dried	0
ex 3824 90 64	05	Residues of manufacture containing by weight 40 % or more of 11 $\beta$ ,17,20,21-tetrahydroxy-6-methylpregna-1,4-dien-3-one 21-acetate	0
ex 3824 90 95	01	Colloidal diantimony pentaoxide	0
ex 3824 90 95	02	Mixture of nitromethane and 1,2-epoxybutane	0
ex 3824 90 95	03	Grains or granules, consisting of a mixture of dialuminium trioxide and zirconium dioxide, containing by weight: — 70 % or more but not more than 78 % of dialuminium trioxide, and — 19 % or more but not more than 26 % of zirconium dioxide	5,2
ex 3824 90 95	04	Crude lithium hypochlorite	0
ex 3824 90 95	06	Preparation, in the form of powder, containing by weight 75 % or more of zinc bis[3,5-bis(1-phenylethyl)salicylate]	0
ex 3824 90 95	07	Film consisting of the oxides of either barium or calcium and either titanium or zirconium, mixed with binding materials	0
ex 3824 90 95	08	Preparation consisting essentially of alkaline asphalt sulphonate, of: — a specific gravity of 0,9 or more but not exceeding 1,5, and — a solubility in water of 70 % by weight or more	0
ex 3824 90 95	09	Anti-corrosion preparations consisting of salts of dinonylnaphthalenesulphonic acid, either: — on a support of mineral wax, whether or not modified chemically, or — in the form of a solution in an organic solvent	0
ex 3824 90 95	10	Calcined bauxite (refractory grade)	0
ex 3824 90 95	11	Magnetisable iron oxide, in the form of powder, containing by weight: — 30 % or more but not more than 38 % of bivalent iron in relation to the total iron, and — 1 % or more but not more than 4 % of cobalt	0

## ▼M5

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 3824 90 95	12	Spent catalyst, in the form of rodlets of diameter of 1 mm or more but not exceeding 3 mm, containing a mixture of sulphides of tungsten and of nickel on a support of zeolite, containing by weight not more than 10 % of tungsten and not more than 10 % of nickel, for regeneration as a catalyst for hydrocarbon cracking (*)	0
ex 3824 90 95	13	Mixture containing by weight: — 7 % or more but not more than 9 % of 2-methyl-1,3-phenylene diisocyanate, — 31 % or more but not more than 34 % of 4-methyl-1,3-phenylene diisocyanate, — 10 % or more but not more than 13 % of 2,4'-methylenediphenyl diisocyanate, — 46 % or more but not more than 49 % of 4,4'-methylenediphenyl diisocyanate	0
ex 3824 90 95	14	Mixture of magnesium bromide 2-oxoperhydroazepin-1-ide and $\epsilon$ -caprolactam	0
ex 3824 90 95	15	Mixture of disodium <i>N</i> -benzyloxycarbonyl-L-aspartate and sodium chloride, in the form of a solution in water	0
ex 3824 90 95	16	Disodium 9,10-dihydro-9,10-dioxanthracene-2,7-disulphonate, containing by weight 10 % or more but not more than 20 % of sodium sulphate	0
ex 3824 90 95	17	Eutectic alloy wholly of potassium and sodium, containing by weight 77 % or more but not more than 79 % of potassium	0
ex 3824 90 95	18	Blend of terephthaloyl dichloride and isophthaloyl dichloride	0
ex 3824 90 95	20	Preparation consisting by weight of 90 % or more of 3a,4,7,7a-tetrahydro-4,7-methanoindene (dicyclopentadiene), a synthetic rubber and: — either an aluminium-alkyl compound, — or an organic complex of tungsten	0
ex 3824 90 95	21	Mixture of tris[2-chloro-1-(chloromethyl)ethyl] phosphate and oligomers of methylphosphonic acid and phosphoric acid with ethane-1,2-diol	0
ex 3824 90 95	22	Mixture of tris[2-chloro-1-(chloromethyl)ethyl] phosphate and oligomers of 2-chloroethyl phosphate with ethane-1,2-diol	0
ex 3824 90 95	23	Mixture of sucrose esters, derived from the esterification of sucrose with industrial stearic acid	0
ex 3824 90 95	24	Preparations consisting predominantly of phosphabicyclononanes and P-alkyl derivatives thereof, in the form of a solution in 4- <i>tert</i> -butyltoluene	0
ex 3824 90 95	25	Lithium tantalate wafers, undoped	0
ex 3824 90 95	28	Preparation consisting predominantly of ethylene glycol and <i>N,N</i> -dimethylformamide or ethylene glycol and $\gamma$ -butyrolactone, for the manufacture of electrolytic capacitors (*)	0
ex 3824 90 95	29	Preparation consisting predominantly of $\gamma$ -butyrolactone and quaternary ammonium salts, for the manufacture of electrolytic capacitors (*)	0
ex 3824 90 95	30	2,4,7,9-Tetramethyldec-5-yne-4,7-diol, hydroxyethylated	0
ex 3824 90 95	31	Copper zinc ferrite, coated with a silicone resin, in the form of granules of a size not exceeding 120 $\mu$ m	0
ex 3824 90 95	32	Styrene oligomer	0
ex 3824 90 95	33	Preparation consisting of $\alpha$ -(4-allyloxycarbonylbenzoyl)- $\omega$ -allyloxypoly-[oxy(2-methylethylene)oxyterephthaloyl] and either diallyl-2,2'-oxydiethyl dicarbonate or diallyl isophthalate	0

## ▼M5

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 3824 90 95	39	Mixture containing by weight 40 % or more but not more than 50 % of 2-hydroxyethyl methacrylate and 40 % or more but not more than 50 % of glycerol ester of boric acid	0
ex 3824 90 95	40	Azelaic acid of a purity by weight of 75 % or more but not exceeding 85 %	0
ex 3824 90 95	41	7-Nitronaphth[1,2- <i>d</i> ][1,2,3]oxadiazole-5-sulphonic acid of a purity by weight of 60 % or more but not exceeding 85 %	0
ex 3824 90 95	42	Mixed metals oxides, in the form of powder, containing by weight: — either 5 % or more of barium, neodymium or magnesium and 15 % or more of titanium, — or 30 % or more of lead and 5 % or more of niobium, for use in the manufacture of dielectric films or for use as dielectric materials in the manufacture of multilayer ceramic capacitors (°)	0
ex 3824 90 95	43	7-Aminonaphthalene-1,3,6-trisulphonic acid and its salts, of a purity by weight of 65 % or more	0
ex 3824 90 95	44	Mixture containing by weight: — 60 % or more of 2-[ <i>N</i> -(2-cyanoethyl)anilino]ethyl acetate and — 20 % or more of acetic acid	0
ex 3824 90 95	45	Preparations consisting predominantly of ethylene glycol and either: — diethylene glycol, dodecandioic acid and ammonia water, — or silicon oxide, — or ammonium hydrogen azelate, or ammonium hydrogen azelate and silicon oxide, — or dodecandioic acid, ammonia water and silicon oxide, for the manufacture of electrolytic capacitors (°)	0
ex 3824 90 95	46	Carboxylic acid anhydride based hardener for epoxyde resin, in liquid form, of a specific weight at 25 °C of 1,15 g/cm <sup>3</sup> or more but not exceeding 1,18 g/cm <sup>3</sup>	0
ex 3824 90 95	49	Mixed oxides of metals, in the form of powder, containing by weight: — 70 % or more but not more than 75 % of iron oxide, — 10 % or more but not more than 20 % of zinc oxide, — 10 % or more but not more than 15 % of magnesium oxide, — 1 % or more but not more than 5 % of manganese oxide and — 1 % or more but not more than 3 % of copper oxide	0
ex 3824 90 95	50	Zeolites consisting of oxides of barium, aluminium and silicon, containing by weight 30 % or more but not more than 40 % of barium oxide, in the form of spheres of which 80 % or more by weight have a diameter of 0,3 mm or more but not more than 1,2 mm	0
ex 3824 90 95	53	Sodium 4-hydroxynaphthalene-1-sulfonate, of a purity by weight of 70 % or more but not exceeding 80 %	0
ex 3824 90 95	54	2-Hydroxybenzonitrile, in the form of a solution in <i>N,N</i> -dimethylformamide, containing by weight 45 % or more but not more than 50 % of 2-hydroxybenzonitrile	0
ex 3824 90 95	55	Mixture containing by weight 75 % or more of pentaerythritol triallyl ether	0
ex 3824 90 95	57	Mixture of trialkylphosphine oxides	0
ex 3824 90 95	58	Platinum oxide fixed on a porous support of aluminium oxide, containing by weight 0,1 % or more but not more than 1 % of platinum and 0,5 % or more but not more than 5 % of ethylaluminium dichloride	0

▼ **M5**

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 3824 90 95	60	$\alpha$ -Phenoxycarbonyl- $\omega$ -phenoxypoly[oxy(2,6-dibromo-1,4-phenylene)-isopropylidene(3,5-dibromo-1,4-phenylene)oxycarbonyl]	0
ex 3824 90 95	61	Mixture of metal oxides, in the form of powder, containing by weight: — 20 % or more of barium, — 10 % or more of titanium and — 4 % or more of lead or 3 % or more of niobium or 0,7 % or more of zirconium,  for use as dielectric material in the manufacture of multilayer ceramic capacitors <sup>(a)</sup>	0

▼ **M6**

ex 3824 90 95	63	Triethylborane, in the form of a solution in tetrahydrofuran	0
ex 3824 90 95	64	Aluminium sodium silicate, in the form of spheres of a diameter of: — either 1,6 mm or more but not exceeding 3,4 mm, — or 4 mm or more but not exceeding 6 mm	0
ex 3824 90 95	65	Mixture of tris(alkoxycarbonylamino)-1,3,5-triazines in which alkoxy groups are methoxy and butoxy	0
ex 3824 90 95	66	Mixture of primary <i>tert</i> -alkylamines	0
ex 3824 90 95	67	Preparation consisting of indium tin oxide dispersed in organic solvents	0

▼ **M5**

ex 3901 10 10	10	Linear polyethylene, of a specific gravity of 0,928 or more but not exceeding 0,935 and of a melt flow index of less than 0,6 g/min, for the manufacture of shrinkmelt binder fibres <sup>(a)</sup>	0
ex 3901 10 90	10	Polyethylene for the manufacture of photo-resist film for semiconductors or printed circuits <sup>(a)</sup>	0
ex 3901 10 90	20	Polyethylene, in the form of granules, of a specific gravity of 0,925 ( $\pm$ 0,0015), a melt flow index of 0,3 g/10 min ( $\pm$ 0,05 g/10 min), for the manufacture of blown films of a Haze value not exceeding 6 % and an elongation at break (MD/TD) of 210/340 <sup>(a)</sup>	0
ex 3901 20 90	10	Polyethylene, in one of the forms mentioned in note 6 <sup>(b)</sup> to Chapter 39, of a specific gravity of 0,945 or more but not exceeding 0,985, for the manufacture of films for typewriter ribbon or similar ribbon <sup>(a)</sup>	0
ex 3901 20 90	20	Polyethylene, containing by weight 35 % or more but not more than 45 % of mica	0
ex 3901 90 90	91	Ionomer resin consisting of a salt of a copolymer of ethylene with methacrylic acid	4
ex 3901 90 90	93	Copolymer of ethylene, vinyl acetate and carbon monoxide, for use as a plasticizer in the manufacture of roof sheets <sup>(a)</sup>	0
ex 3901 90 90	94	Mixtures of A-B block copolymer of polystyrene and ethylene-butylene copolymer and A-B-A block copolymer of polystyrene, ethylene-butylene copolymer and polystyrene, containing by weight not more than 35 % of styrene	0
ex 3901 90 90 ex 3902 90 90	95 95	Copolymer of ethylene and butylene, having hydroxyl or acrylate end-groups, containing by weight 40 % or more but not more than 60 % of butylene	0
ex 3901 90 90 ex 3902 90 90 ex 3903 90 90	96 96 50	Linear A-B block copolymer of polyisoprene, whether or not epoxidized, and either ethylene-butylene copolymer or styrene-ethylene-butylene copolymer, having hydroxyl end-groups	0

## ▼M5

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 3902 10 00	10	Polypropylene containing no plasticizer and not more than: — 7 mg/kg of aluminium, — 2 mg/kg of iron, — 1 mg/kg of magnesium, — 8 mg/kg of chloride	0
ex 3902 10 00	20	Polypropylene, containing no plasticiser, — of a melting point of more than 150 °C (as determined by the ASTM D 3417 method), — of a heat of fusion of 15 J/g or more but not exceeding 70 J/g, — of an elongation at break of 1 000 % or more (as determined by the ASTM D 638 method), — of a tensile modulus of 69 MPa or more but not exceeding 379 MPa (as determined by the ASTM D 638 method)	0
ex 3902 30 00 ex 3903 90 90	91 25	A-B Block copolymer of polystyrene and an ethylene-propylene copolymer, containing by weight 40 % or less of styrene, in one of the forms mentioned in note 6 <sup>(b)</sup> to Chapter 39	0
ex 3902 30 00	92	Copolymer of propylene, butylene and ethylene, containing by weight more than 65 % but less than 80 % of propylene and not less than 20 % of butylene	0
ex 3902 90 90	92	Polymers of 4-methylpent-1-ene	0
ex 3903 19 00	20	Polystyrene of a molecular weight ( $M_n$ ) not exceeding 5 000	0
ex 3903 90 90	10	Copolymer, entirely of styrene with maleic anhydride, or entirely of styrene with maleic anhydride and an acrylic monomer, whether or not containing a styrene-butadiene block copolymer, in one of the forms mentioned in note 6 <sup>(b)</sup> to Chapter 39, for the manufacture of sheetings for head-liners for cars <sup>(a)</sup>	0
ex 3903 90 90	15	Copolymer, entirely of styrene with maleic anhydride, or entirely of styrene with maleic anhydride and an acrylic monomer, also partially esterified, of an average molecular weight ( $M_n$ ) not exceeding 3 000, in one of the forms mentioned in note 6 <sup>(a)</sup> and <sup>(b)</sup> to Chapter 39	0
ex 3903 90 90	20	Copolymer of styrene with 2-ethylhexyl acrylate or with n-butyl acrylate, containing: — 10 mole % or more but not more than 16 mole % of acrylate, — 0,2 mg/kg or less of sodium and — 0,1 mg/kg or less of calcium	0
ex 3903 90 90 ex 3911 90 99	35 30	Copolymer of $\alpha$ -methylstyrene and styrene, having a softening point exceeding 113 °C	0
ex 3903 90 90 ex 3906 90 90 ex 3911 90 99	40 40 50	Copolymer of styrene with $\alpha$ -methylstyrene and acrylic acid, of a molecular weight ( $M_n$ ) of 500 or more but not exceeding 6 000	0
ex 3903 90 90 ex 3906 90 90	55 45	Copolymer of styrene, methyl methacrylate, butyl acrylate and either acrylic acid or hydroxyethyl methacrylate, of a molecular weight ( $M_n$ ) of 500 or more but not exceeding 6 000	0
ex 3903 90 90	65	Copolymer of styrene, butyl acrylate, butyl methacrylate, methyl methacrylate and acrylic acid, in the form of powder, containing by weight (81 $\pm$ 1) % of styrene, (6 $\pm$ 1) % of butyl acrylate, (5 $\pm$ 1) % of butyl methacrylate, (7 $\pm$ 1) % of methyl methacrylate and (1 $\pm$ 0,5) % of acrylic acid	0
ex 3903 90 90	70	Ammonium polystyrenesulfonate, in the form of an aqueous solution	0

▼ M5

CN code	TARIC	Description	Rate of autonomous duty (%)
<b>▼ <u>M6</u></b>			
ex 3904 30 00	10	Copolymer of vinyl chloride with vinyl acetate and maleic acid, containing by weight: — 81,5 % or more but not more than 84,5 % of vinyl chloride, — 13,8 % or more but not more than 16,2 % of vinyl acetate and — 0,8 % or more but not more than 1,2 % of maleic acid, for the manufacture of goods of heading No 3215 or for use in the manufacture of coatings for containers and closures of a kind used for preserving food and drink <sup>(a)</sup>	0
<b>▼ <u>M5</u></b>			
ex 3904 40 00	91	Copolymer of vinyl chloride with vinyl acetate and vinyl alcohol, containing by weight: — 87 % or more but not more than 92 % of vinyl chloride, — 2 % or more but not more than 9 % of vinyl acetate, and — 1 % or more but not more than 8 % of vinyl alcohol, in one of the forms mentioned in note 6 <sup>(a)</sup> or <sup>(b)</sup> to Chapter 39, for the manufacture of goods of heading No 3215 or 8523 or for use in the manufacture of coatings for containers and closures of a kind used for preserving food and drink <sup>(a)</sup>	0
ex 3904 40 00	92	Copolymer of vinyl chloride, vinyl acetate, hydroxypropyl acrylate and maleic acid, containing by weight 80 % or more but not more than 83 % of vinyl chloride, 1,6 % or more but not more than 2 % of hydroxy groups and 0,25 % or more but not more than 0,38 % of carboxyl groups	0
ex 3904 50 90	91	Copolymer of vinylidene chloride with vinyl chloride, containing by weight 79,5 % or more of vinylidene chloride, in one of the forms mentioned in note 6 <sup>(a)</sup> or <sup>(b)</sup> to Chapter 39, for the manufacture of fibres, monofilament or strip <sup>(a)</sup>	0
ex 3904 61 00	10	Mixture of polytetrafluoroethylene and mica, in one of the forms mentioned in note 6 <sup>(b)</sup> to Chapter 39	0
ex 3904 61 00	20	Copolymer of tetrafluoroethylene and trifluoro(heptafluoropropoxy)ethylene, containing 3,2 % or more but not more than 4,6 % by weight of trifluoro(heptafluoropropoxy)ethylene and less than 1 mg/kg of extractable fluoride ions	0
ex 3904 69 90	92	Copolymer of tetrafluoroethylene and trifluoro(trifluoromethoxy)ethylene	0
ex 3904 69 90	93	Copolymer of ethylene with chlorotrifluoroethylene, in one of the forms mentioned in note 6 <sup>(b)</sup> to Chapter 39	0
ex 3904 69 90	94	Copolymer of ethylene and tetrafluoroethylene	0
ex 3904 69 90	96	Polychlorotrifluoroethylene, in one of the forms mentioned in note 6 <sup>(a)</sup> and <sup>(b)</sup> to Chapter 39	0
ex 3905 91 00	91	Copolymer of <i>N</i> -vinylcaprolactam, <i>N</i> -vinyl-2-pyrrolidone and dimethylaminoethyl methacrylate	0
ex 3905 91 00	93	Copolymer of ethylene and vinyl alcohol (EVOH)	0
ex 3905 99 90	93	Polyvinyl acetate phthalate	0
ex 3905 99 90	94	Polymer of vinylpyrrolidone and dimethylaminoethyl methacrylate, containing by weight 97 % or more but not more than 99 % of vinylpyrrolidone, in the form of a solution in water	0
ex 3905 99 90	95	Hexadecylated or eicosylated polyvinylpyrrolidone	0

▼ **M5**

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 3905 99 90	96	Poly(vinyl formal), in one of the forms mentioned in note 6 <sup>(b)</sup> to Chapter 39, of a molecular weight ( $M_w$ ) of 25 000 or more but not exceeding 150 000 and containing by weight: — 9,5 % or more but not more than 13 % of acetyl groups evaluated as vinyl acetate, and — 5 % or more but not more than 6,5 % of hydroxy groups evaluated as vinyl alcohol	0
ex 3906 10 00	10	Polymethyl methacrylate, in the form of expansible beads containing 2-methylpentane as blowing agent	0
▼ <b>M6</b>			
3906 90 60		Copolymer of methyl acrylate with ethylene and a monomer containing a non-terminal carboxy group as a substituent, containing by weight 50 % or more of methyl acrylate, whether or not mixed with silicon dioxide	0
▼ <b>M5</b>			
ex 3906 90 90	10	Polymerisation product of acrylic acid with small quantities of a polyunsaturated monomer, for the manufacture of medicaments of heading No 3003 or 3004 <sup>(a)</sup>	0
ex 3906 90 90	20	Polymerisation product of acrylic acid with small quantities of a polyunsaturated monomer, for use as a stabiliser in emulsions or dispersions with a pH of more than 13 <sup>(a)</sup>	6
ex 3906 90 90	30	Copolymer of styrene with hydroxyethyl methacrylate and 2-ethylhexyl acrylate, of a molecular weight ( $M_n$ ) of 500 or more but not exceeding 6 000	0
▼ <b>M6</b>			
ex 3906 90 90	50	Acrylic polymers, containing by weight 2,5 % or more of chloroethyl vinyl ether or chloromethyl acrylate, in one of the forms mentioned in note 6(b) to Chapter 39	0
▼ <b>M5</b>			
ex 3907 20 11	10	Poly(ethylene oxide) of an average molecular weight ( $M_n$ ) of 100 000 or more	0
ex 3907 20 29	10	Polymer of dextrose, sorbitol and citric or phosphoric acid, containing by weight 90 % or more of dextrose monomer units	0
ex 3907 20 29	20	Poly[oxy-1,4-phenyleneisopropylidene-1,4-phenyleneoxy-(2-hydroxytrimethylene)], of an average molecular weight ( $M_w$ ) of more than 26 000, in one of the forms mentioned in note 6 <sup>(b)</sup> to Chapter 39	0
ex 3907 20 99	10	Bis{2-[ $\omega$ -hydroxy-poly(ethyleneoxy)]ethyl} hydroxy-methylphosphonate	0
ex 3907 20 99	15	Poly(oxypropylene) having alkoxy-silyl end-groups	0
ex 3907 20 99	25	$\alpha$ -4-Hydroxybutyl- $\omega$ -hydroxypoly(oxytetramethylene), containing less than 1 mg/kg of halogen and less than 1 mg/kg of metal, and of a colour not exceeding 20 units on the Hazen scale	0
ex 3907 20 99	30	Homopolymer of 1-chloro-2,3-epoxypropane (epichlorohydrin)	0
ex 3907 30 00	20	Epoxyde resin in the form of powder, containing by weight 44 % or more but not more than 55 % of quartz and 0,5 % or more but not more than 1 % of diantimony trioxide, for the coating of film capacitors <sup>(a)</sup>	0
ex 3907 30 00	30	Epoxyde resin, without solvent, containing mineral fillers (silica), without glass fibre, of a specific weight at 25 °C of 1,55 g/cm <sup>3</sup> or more but not exceeding 1,60 g/cm <sup>3</sup>	0
ex 3907 30 00	40	Epoxyde resin, containing by weight 70 % or more of silicon dioxide, for the encapsulation of goods of heading No 8533, 8535, 8536, 8541, 8542 or 8548 <sup>(a)</sup>	0
ex 3907 40 00	10	Copolymer of hexane-1,6-diol, cyclohexane-1,4-dimethanol and ethylene carbonate	0
ex 3907 91 90	10	Diallyl phthalate prepolymer, in the form of powder	0

▼ **M5**

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 3907 99 19	10	Poly(oxy-1,4-phenylenecarbonyl), in the form of powder	0
ex 3907 99 99	10		0
ex 3907 99 19	20	Liquid crystal copolyester with a melting point of not less than 270 °C, whether or not containing fillers	0
ex 3908 90 00	10	Poly(iminomethylene-1,3-phenylenemethyleneiminoadi-poyl), in one of the forms mentioned in note 6 <sup>(b)</sup> to Chapter 39	0
ex 3909 40 00	10	Polycondensation product of phenol with formaldehyde, in the form of hollow spheres of a diameter of less than 150 µm	0
ex 3910 00 00	10	3-[(2-Aminoethyl)amino]propyl(methyl)cyclosiloxane	0
ex 3910 00 00	20	Block copolymer of poly(methyl-3,3,3-trifluoropropylsiloxane) and poly[methyl(vinyl)siloxane]	0
ex 3911 90 19	10	Poly(oxy-1,4-phenylenesulfonyl-1,4-phenyleneoxy-4,4'-biphenylene)	0
▼ <b>M6</b>			
ex 3911 90 19	20	Hydrocarbon prepolymer, obtained by the reaction of cyclopentadiene and 1,3-pentadiene	0
▼ <b>M5</b>			
ex 3911 90 99	20	Copolymer of dibutyl maleate and <i>N</i> -vinyl-2-pyrrolidone, in one of the forms mentioned in note 6 <sup>(c)</sup> of Chapter 39	0
ex 3911 90 99	25	Copolymer of vinyltoluene and $\alpha$ -methylstyrene	0
ex 3911 90 99	40	Mixed calcium and sodium salt of a copolymer of maleic acid and methyl vinyl ether, having a calcium content of 9 % or more but not more than 16 % by weight	0
ex 3911 90 99	45	Copolymer of maleic acid and methyl vinyl ether	0
ex 3911 90 99	55	Solution containing: — (36 ± 0,5) % by weight of polyamide with lateral ester groups, — (2 ± 0,5) % by weight of acrylic ester, — (48 ± 0,5) % by weight of 1-methyl-2-pyrrolidone, — (12 ± 0,5) % by weight of bis(2-methoxyethyl) ether, — 500 µg/kg or less of potassium, and — 500 µg/kg or less of iron, for use in the manufacture of goods of heading No 8542 <sup>(d)</sup>	0
ex 3912 11 00	10	Non-plasticised cellulose triacetate, in the form of flakes, for the manufacture of cellulose triacetate yarn <sup>(e)</sup>	0
ex 3912 39 10	10	Ethylcellulose, not plasticized	0
ex 3912 39 80	10	Cellulose, both hydroxyethylated and ethylated, insoluble in water	0
ex 3912 39 80	20	Cellulose, both hydroxyethylated and alkylated with alkyl chain-lengths of 3 or more carbon atoms	0
ex 3912 90 10	10	Cellulose acetate propionate, non-plasticised, in the form of powder: — containing by weight 25 % or more of propionyl (as determined by the ASTM D 817-72 method) and — of a viscosity not exceeding 120 poise (as determined by the ASTM D 817-72 method), for the manufacture of printing inks, paints, lacquers and other coatings, and reprographic coatings <sup>(f)</sup>	0
ex 3913 90 80	30	Chondroitinsulphuric acid, sodium salt	0

▼ **M5**

CN code	TARIC	Description	Rate of autonomous duty (%)
<b>▼ M6</b>			
ex 3915 90 93	30	Waste, parings and scrap of photographic, cinematographic and radiographic films	0
<b>▼ M5</b>			
ex 3917 32 10	10	Flexible pipe of silicone foam, with continuous channels, of a Shore A hardness of 7 or more but not exceeding 48 and a density of 0,28 g/cm <sup>3</sup> or more but not exceeding 0,92 g/cm <sup>3</sup>	0
ex 3917 32 39	20	Pipe consisting of a block copolymer of polytetrafluoroethylene and polyperfluoroalkoxytrifluoroethylene, having a length of not more than 570 mm, a diameter of not more than 50 mm and a wall-thickness of not less than 30 and not more than 110 µm	0
ex 3919 10 38	10	Self-adhesive tape of metallised polyurethane containing glass beads for use in the manufacture of marine life-saving equipment (*)	0
ex 3919 90 10	10	Shaped sheet of plastic, with an adhesive layer containing polyisobutylene and pectin, for the manufacture of colostomy bags (*)	0
ex 3919 90 31	40	Reflecting polyester sheeting embossed in a regular pyramidal pattern, for the manufacture of safety stickers and badges, safety clothing and accessories thereof, or of school satchels, bags or similar containers (*)	0
ex 3920 62 19	20		
ex 3920 62 90	20		
ex 3920 63 00	30		
ex 3920 69 00	30		
ex 3919 90 61	92	Polyvinyl chloride sheeting, of a thickness of less than 1 mm, coated with an adhesive in which are embedded glass balls of a diameter not exceeding 100 µm	0
ex 3919 90 69	92		
ex 3919 90 61	93	Adhesive film consisting of a base of a copolymer of ethylene and vinyl acetate (EVA) of a thickness of 120 µm or more and an adhesive part of acrylic type of a thickness of 10 µm or more, for the protection of the surface of silicon discs (*)	0
ex 3919 90 69	93		
ex 3920 10 89	25		
<b>▼ M6</b>			
ex 3919 90 69	94	Reflecting laminated sheet, consisting of a film of polymethyl methacrylate embossed on one side in a regular pyramidal or other shaped pattern, a film of polymethyl methacrylate containing glass microprisms or microspheres, an adhesive layer and a release sheet	0
<b>▼ M5</b>			
ex 3920 10 26	20	Film of polyethylene, of a thickness of 20 µm or more but not exceeding 45 µm, containing calcium carbonate in the mass, for the manufacture of napkins for babies or of sanitary towels or of tampons or of disposable surgical gowns (*)	0
ex 3920 10 26	30	Film of a thickness not exceeding 0,20 mm, of a blend of polyethylene and a copolymer of ethylene with oct-1-ene, embossed in a regular rhomboidal pattern, for coating both sides of a layer of unvulcanized rubber (*)	0
ex 3920 10 89	20		
ex 3920 10 40	91	Synthetic paper pulp, in the form of moist sheets, made from unconnected finely-branched polyethylene fibrils, whether or not blended with cellulose fibres in a quantity not exceeding 15 %, containing polyvinyl alcohol dissolved in water as the moistening agent	0
ex 3920 10 40	92	Laminated sheet or strip consisting of a film composed of a blend of a copolymer of ethylene with vinyl acetate and a modified ethylene-propylene-elastomer (EPM) or a modified ethylene-propylene-diene elastomer (EPDM), coated or covered on both sides with a film of a copolymer of ethylene with vinyl acetate	0
ex 3920 20 90	91	Synthetic paper pulp, in the form of moist sheets, made from unconnected finely-branched polypropylene fibrils, whether or not blended with cellulose fibres in a quantity not exceeding 15 %, containing polyvinyl alcohol dissolved in water as the moistening agent	0

▼ **M5**

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 3920 20 90	92	Laminated sheet or strip, consisting of a film of a thickness of 181 µm or more but not exceeding 223 µm composed of a blend of a copolymer of propylene with ethylene and a copolymer of styrene-ethylene-butylene-styrene (SEBS) coated or covered on one side with a layer of a copolymer of styrene-ethylene-butylene-styrene (SEBS) and a layer of polyester	0

▼ **M6**

ex 3920 30 00	20	Laminated sheet or strip, consisting of a film composed of a blend of a thermoplastic elastomer (TPE) of styrene-butadiene-styrene (SBS) with polyethylene or polypropylene, of a thickness of 100 µm or more but not exceeding 200 µm, coated or covered on both sides with a film of polypropylene of a thickness not exceeding 20 µm	0
---------------	----	---	---

▼ **M5**

ex 3920 42 11	92	Reflecting sheeting, consisting solely of a single layer of polyvinyl chloride, wholly embossed on one side in a regular pyramidal pattern	0
ex 3920 42 91	92	Reflecting sheeting, consisting solely of a single layer of polyvinyl chloride, wholly embossed on one side in a regular pyramidal pattern	0
ex 3920 42 91	93	Sheeting of polyvinyl chloride, stabilised against ultraviolet rays, without any holes, even microscopic, of a thickness of 60 µm or more but not exceeding 80 µm, containing 30 or more but not more than 40 parts of plasticiser to 100 parts of polyvinyl chloride	0
ex 3920 42 91	94	Polyvinyl chloride sheet, with relief printing, for the manufacture of templates for textile printing (*)	0
ex 3920 51 00	10	Polymethyl methacrylate plate, with an antistatic coating, of dimensions of 738 × 972 mm (± 1,5 mm)	0

▼ **M6**

ex 3920 51 00	20	Plate of polymethyl methacrylate containing aluminium trihydroxide, of a thickness of 3,5 mm or more but not exceeding 19 mm	0
---------------	----	--	---

▼ **M5**

ex 3920 61 00	10	Polycarbonate film of a thickness not exceeding 15 µm, for the manufacture of film capacitors (*)	0
ex 3920 62 19	10	Polyethylene terephthalate film, of a thickness of less than 11 µm, for the manufacture of audiodigital tapes for cassettes (*)	0
ex 3920 62 19	15	Polyethylene terephthalate film, not coated with an adhesive, of a thickness not exceeding 25 µm, either: — only dyed in the mass, or — dyed in the mass and metallised on one side	0
ex 3920 62 19	25	Film of polyethylene terephthalate only, of a total thickness not exceeding 120 µm, consisting of one or two layers each containing a colouring and/or UV-absorbing material throughout the mass, uncoated with an adhesive or any other material	0
ex 3920 62 19	30	Polyethylene terephthalate film, of a thickness of 20 µm or more but not exceeding 30 µm, coated on one side with silicone, for use in the manufacture of window film (*)	5,6
ex 3920 62 19	35	Laminated film of polyethylene terephthalate only, of a total thickness not exceeding 120 µm, consisting of one layer which is metallised only and one or two layers each containing a colouring and/or UV-absorbing material throughout the mass, uncoated with an adhesive or any other material	0
ex 3920 62 19	40	Film of polyethylene terephthalate, coated or covered on one side or on both sides with a layer of modified polyester, of a total thickness of 7 µm or more but not exceeding 11 µm, for the manufacture of video tapes with a magnetic layer of metallic pigments and a width of 8 mm or of 12,7 mm (*)	0

## ▼M5

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 3920 62 19	45	Single ply film of polyethylene terephthalate only, of a thickness not exceeding 120 µm, which only: — contains a colouring and/or UV-absorbing material throughout the mass, and — is metallised on one side,  whether or not coated on one or both sides with a vinyl acrylate polymer but having no other coating or adhesive	0
ex 3920 62 19	50	Film of polyethylene terephthalate, of a total thickness not exceeding 120 µm, of a width of 100 mm or more but not exceeding 115 mm, coated on both sides with one or more layers containing different chemicals, for the manufacture of goods of subheading 3701 20 00 (*)	0
ex 3920 62 19	55	Film of polyethylene terephthalate, on one side metallised and coated with white ink and a protective layer and on the other side coated with a thermosensitive seal layer, of a width of 100 mm or more but not exceeding 150 mm, for the manufacture of goods of subheading 3701 20 00 (*)	0
ex 3920 62 19	60	Film of polyethylene terephthalate, coated on one side with a layer of modified polyester, of a thickness of 20 µm (± 0,7 µm) or of 30 µm (± 0,9 µm), for the manufacture of audio magnetic tapes of a total thickness of 33 µm or more (*)	0
ex 3920 62 19	65	Polyethylene terephthalate film, of a thickness not exceeding 19 µm or of a weight of 20 g/m <sup>2</sup> or more but not exceeding 26,7 g/m <sup>2</sup> , for use in the manufacture of photo-resist film (*)	0
ex 3920 62 19	70	Film of polyethylene terephthalate, coated on both sides with a layer of epoxy acrylic resin, of a total thickness of 37 µm (± 3 µm)	0
ex 3920 62 19	75	Film of polyethylene terephthalate, coated on one side with metal and/or metal oxides, containing by weight less than 0,1 % of aluminium, of a thickness not exceeding 300 µm and having a surface resistivity not exceeding 10 000 ohms (per square) (as determined by the ASTM D 257-93 method)	0
ex 3920 62 19	80	Mat film of polyethylene terephthalate, of a gloss of 15 at an angle of 45 ° and 18 at an angle of 60 ° (as determined by the ASTM D 523 method) and a width of 1 600 mm or more	0
ex 3920 62 19	81	Film of white polyethylene terephthalate, dyed in the mass, of a thickness of 185 µm or more but not exceeding 253 µm, coated on both sides with an antistatic layer	0
ex 3920 62 19	85	Film of a total thickness of 4,5 µm (± 0,16 µm), consisting of a biaxially-oriented polyethylene terephthalate film, of a thickness of 4,4 µm, an elastic modulus (in the machine direction) of 12 kg/mm <sup>2</sup> (± 2 kg/mm <sup>2</sup> ) and a tensile strength (in the machine direction) of more than 28 kg/mm <sup>2</sup> , and of an anti-adherent coating of a thickness of 0,1 µm	0
ex 3920 62 19	87	Polyethylene terephthalate film, coated with a wax layer, a scratch resistant layer and a thermoadhesive layer, of a nominal width of 790 mm and a total thickness of 23 µm or more but not exceeding 26 µm	0
ex 3920 62 19	89	Multilayer film of a thickness not exceeding 150 µm, consisting of a polyester film coated on one side with polycarbonate resin, metallized on the other side with titanium coated with polycarbonate resin and other layers containing <i>N,N'</i> -diphenyl- <i>N,N'</i> -di- <i>m</i> -tolylbiphenyl-4,4-ylenediamine	0

## ▼M6

## ▼M5

▼ M5

CN code	TARIC	Description	Rate of autonomous duty (%)
▼ <u>M6</u> ex 3920 62 90	30	Film of polyethylene terephthalate, of a thickness of 500 µm (± 25 µm)	0
▼ <u>M5</u> ex 3920 69 00	20	Film of polyethylene naphthalene-2,6-dicarboxylate, of a thickness of 82 µm or more but not exceeding 88 µm	0
ex 3920 69 00	40	Iridescent film of polyester and polymethyl methacrylate	0
ex 3920 69 00	50	Polycondensation product of terephthalic acid with a mixture of cyclohex-1,4-ylenedimethanol and ethane-1,2-diol, in the form of a film	0
ex 3920 69 00	60	Film of a copolymer of ethylene terephthalate and ethylene isophthalate, of a thickness not exceeding 2 µm	0
ex 3920 91 00	91	Polyvinyl butyral film having a graduated coloured band	6
ex 3920 91 00	92	Plasticized film of polyvinyl butyral, containing by weight: — either 14,5 % or more but not more than 17,5 % of dihexyl adipate, — or 14,5 % or more but not more than 28,5 % of dibutyl sebacate	0
▼ <u>M6</u> ex 3920 91 00	93	Film of polyethylene terephthalate, metallised on one or both sides, or laminated film of polyethylene terephthalate films, metallised on the external sides only, and having the following characteristics: — a visible light transmission of 50 % or more, — coated on both sides with a layer of polyvinyl butyral but not coated with an adhesive or any other material except polyvinyl butyral, — a total thickness not exceeding 0,2 mm without taking the presence of polyvinyl butyral into account,  for use in the manufacture of heat-reflecting laminated glass <sup>(a)</sup>	0
▼ <u>M5</u> ex 3920 99 28	10	Reflecting sheet of metallised polyurethane, containing glass beads, coated with a hot-melt adhesive layer, covered on one or both sides with a release sheet, in rolls of a width of 1 020 mm (± 20 mm), for slitting into safety clothing reflecting strip <sup>(a)</sup>	0
ex 3920 99 59	20	Film entirely of polyvinyl alcohol, of a thickness not exceeding 1 mm and containing by weight: — 2 % or less of unhydrolysed acetate groups evaluated as vinyl acetate and — 5 % or more but not more than 25 % of glycerol as plasticizer,  for the manufacture of roof-windows <sup>(a)</sup>	0
ex 3920 99 59	25	Poly(1-chlorotrifluoroethylene) film	0
ex 3920 99 59	30	Film and sheet of a copolymer of ethylene with chlorotrifluoroethylene, of a thickness of 12 µm or more but not exceeding 400 µm	0
ex 3920 99 59	35	Film entirely of polyvinyl alcohol, of a thickness not exceeding 1 mm and of a width of 2,20 m or more, with an extension at break, in the transverse direction, of 350 % or more	0
ex 3920 99 59	40	Biaxially-oriented film of polyvinyl alcohol, coated on both sides, of a total thickness of less than 1 mm	0
ex 3920 99 59	45	Iridescent film of polyester, polyethylene and an ethylene-vinyl acetate copolymer	0
ex 3920 99 59	50	Polytetrafluoroethylene film, non-microporous, in the form of rolls, of a thickness of 0,019 mm or more but not exceeding 0,14 mm, impermeable to water vapour	0



▼ **M5**

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 4811 21 00	10	Impregnated paper coated or covered with a pressure-sensitive self-adhesive layer, the whole: — of a tensile of 2 700 N/m or more but not exceeding 3 700 N/m in the machine direction (as determined by the DIN 53112 method), — of a stretch factor of 1,5 % or more but not exceeding 3,0 % in the machine direction (as determined by the DIN 53112 method) and — of adhesivity on stainless steel (as determined by the DIN 30646 method) of 50 N/m or more but not exceeding 225 N/m, at a temperature of 23 °C (± 3 °C) and a relative humidity of 50 % (± 5 %)	0
ex 4811 31 00	10	Paper coated with acrylic polymer, with a gloss of 75 or more but not exceeding 90 (as determined by the Hunter method), of a weight of 160 g/m <sup>2</sup> or more but not exceeding 180 g/m <sup>2</sup> , for use as casting paper in the manufacture of films of plastics (*)	0
ex 4811 39 00	10	Kraft paper impregnated with an acrylic polymer, of a nominal weight of 85 g/m <sup>2</sup>	0
ex 4823 90 50	10	Paper coated with dye retention and dye releasing agents used to produce a positive image, for the manufacture of goods of subheading 3701 20 00 (*)	0
ex 4823 90 50	20	Honeycomb filter, of paper impregnated with carbon, of a thickness greater than 10 mm but not exceeding 30 mm	0
ex 4823 90 90	12	Strips of paper glued to one another to form a honeycomb of a height not exceeding 13 cm, for agricultural purposes (*)	0
ex 4911 99 00	10	Polyester film, partially coated with a magnetic metal layer showing a regular repeating logo or motif, for the manufacture of security threads (*)	0
5002 00 00		Rawsilk (not thrown)	0
ex 5004 00 10	10	Yarn spun entirely from silk, not put up for retail sale	2,5
ex 5004 00 90	10		
ex 5005 00 10	10	Yarn spun entirely from silk waste (noil), not put up for retail sale	0
ex 5005 00 90	10		
▼ <b>M6</b>			
▼ <b>M5</b>			
ex 5402 41 00	10	Polyamide yarn, not textured, untwisted or with a twist not exceeding 22 turns per metre, of crimpable bicomponent filaments consisting of poly(hexamethylene adipamide) with a copolyamide, for the manufacture of: — knee-length stockings of subheadings 6115 20 11 and 6115 93 30, — women's stockings of subheadings 6115 20 19 and 6115 93 91, or — panty hose (tights) of subheading 6115 11 00 (*)	0
ex 5402 41 00	20	Yarn of synthetic textile fibres solely of aromatic polyamides obtained by the polycondensation of m-phenylenediamine and isophthalic acid	0
ex 5402 43 00	20	Synthetic bicomponent filament yarn, not textured, untwisted, measuring 1 650 decitex, consisting of 110 filaments each having a core of polyethylene terephthalate and a skin of polyamide-6, containing by weight 75 % or more but not exceeding 77 % of polyethylene terephthalate, for use in the manufacture of roofings (*)	0
ex 5402 49 99	10	Multifilaments yarn of polytetrafluoroethylene	0
ex 5402 69 90	20		0
ex 5402 49 99	30	Yarn of a copolymer of glycollic acid with lactic acid, for the manufacture of surgical sutures (*)	0

▼ **M5**

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 5402 49 99	50	Non-textured filament yarn of polyvinyl alcohol	0
ex 5402 59 90	20		
ex 5402 69 90	40		
ex 5402 49 99	60	Yarn wholly of polyglycollic acid	0
ex 5402 69 90	10		
ex 5402 49 99	70	Synthetic filament yarn, single, containing by weight 85 % or more of acrylonitrile, in the form of a wick containing 1 000 continuous filaments or more but not more than 25 000 continuous filaments, of a weight per metre of 0,12 g or more but not exceeding 3,75 g and of a length of 100 m or more, for the manufacture of carbon-fibre yarn (*)	0
ex 5402 49 99	80	Polyethylene filament yarn, untwisted, of either 55, 110, 165 or 1 760 decitex, for the manufacture of goods of heading No 5607 (*)	0
ex 5402 49 99	85	Synthetic filament yarn, single, untwisted, wholly of poly(thio-1,4-phenylene)	0
ex 5404 10 90	10	Monofilament of polytetrafluoroethylene	0
ex 5404 10 90	20	Monofilament of poly(1,4-dioxanone)	0
ex 5404 10 90	30	Monofilament of a copolymer of 1,3-dioxan-2-one with 1,4-dioxan-2,5-dione, for the manufacture of surgical sutures (*)	0
ex 5407 71 00	10	Woven fabrics of polyvinyl alcohol fibres, for machine embroidery	0

▼ **M6**▼ **M5**

ex 5501 90 90	10	Polyvinyl alcohol tow	0		
ex 5503 20 00	10	Polyester staple fibres, loaded with zeolite impregnated with a mixture of salts of copper and silver or of salts of zinc and silver	4		
ex 5503 90 10	10	Acetalized, multicomponent spun fibres with a matrix fibril structure, consisting of emulsion-polymerised polyvinyl alcohol and polyvinyl chloride	0		
ex 5503 90 90	30				
ex 5503 90 90	10	Textile fibres of polytetrafluoroethylene	4		
ex 5503 90 90	20	Polyvinyl alcohol fibres, whether or not acetalised	0		
ex 5506 90 90	10				
ex 5601 30 00	10				
ex 5503 90 90	40	Fibres wholly of poly(thio-1,4-phenylene)	0		
ex 5601 30 00	20	Polyester fibres, measuring 0,56 decitex, of a length of 3 mm or more but not exceeding 5 mm	0		
ex 5601 30 00	30	Acrylic fibres, measuring 0,11 and 0,56 decitex, of a length of 3 mm or more but not exceeding 5 mm	0		
ex 5603 11 10	10	Polyvinyl alcohol non-wovens, in the piece or cut into rectangles: — of a thickness of 200 µm or more but not exceeding 280 µm, and — of a weight of 20 g/m <sup>2</sup> or more but not exceeding 50 g/m <sup>2</sup>	0		
ex 5603 11 90	10				
ex 5603 12 10	10				
ex 5603 12 90	10				
ex 5603 91 10	10				
ex 5603 91 90	10				
ex 5603 92 10	10				
ex 5603 92 90	10				
ex 5603 11 10	20			Non-wovens, containing spunbonded fibres of polypropylene or of polypropylene and polyethylene, for the manufacture of napkins and napkin liners for babies and similar sanitary articles (*)	0
ex 5603 11 90	20				
ex 5603 12 10	20				
ex 5603 12 90	50				
ex 5603 12 90	30	Non-wovens of aromatic polyamide fibres obtained by polycondensation of <i>m</i> -phenylenediamine and isophthalic acid, in the piece or cut into rectangles	0		
ex 5603 13 90	30				
ex 5603 14 90	10				
ex 5603 13 90	40	Non-wovens consisting of a central layer of polycarbonate fibres, laminated on each side with spunbonded filaments of polyester, of a weight of more than 130 g/m <sup>2</sup> but not exceeding 200 g/m <sup>2</sup>	0		
ex 5603 14 90	20				

▼ **M5**

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 5603 92 90	20	Non-wovens consisting of a melt-blown central layer of a thermoplastic elastomer laminated on each side with spunbonded fibres of polypropylene	0
ex 5603 93 90	20		
ex 5603 92 90	40	Non-wovens of polypropylene consisting of a melt-blown central layer, laminated on each side with spun-bonded fibres, of a thickness not exceeding 550 µm and of a weight not exceeding 80 g/m <sup>2</sup> , in the piece or simply cut into rectangular shape, not impregnated	0
ex 5603 93 90	10		
ex 5603 92 90	50	Non-wovens of staple fibres, in rolls, of a width of 78 mm or more but not exceeding 252 mm, for the manufacture of floppy discs <sup>(*)</sup>	0
ex 5603 94 90	20	Acrylic fibre rods, having a length of not more than 50 cm, for the manufacture of pen tips <sup>(*)</sup>	0

▼ **M6**

ex 5607 50 90	10	Twine, unsterilised, wholly of polyglycolic acid, plaited or braided, with an inner core, for the manufacture of surgical sutures <sup>(*)</sup>	0
---------------	----	--	---

▼ **M5**

ex 5903 10 90	10	Knitted or woven fabrics, coated or covered on one side with artificial plastic material in which are embedded microspheres	0
ex 5903 20 90	10		
ex 5903 90 99	20		
ex 5903 20 90	20	Tape of polyester fabric laminated with a metallised polyurethane film containing glass beads, for use in the manufacture of marine life-saving equipment <sup>(*)</sup>	0

▼ **M6**

ex 5907 00 90	10	Textile fabrics, coated with adhesive in which are embedded spheres of a diameter not exceeding 75 µm	0
---------------	----	---	---

▼ **M5**

ex 5911 10 00	10	Needle-punched synthetic-fibre felts on a woven synthetic-fibre base not containing polyester, coated or covered on one side with polytetrafluoroethylene film, for the manufacture of filtration products <sup>(*)</sup>	0
ex 5911 90 90	10	Yarn and strip of impregnated polytetrafluoroethylene, whether or not oiled or graphited	0
ex 5911 90 90	30	Parts of equipment for the purification of water by reverse osmosis, consisting essentially of plastic-based membranes, supported internally by woven or non-woven textile materials which are wound round a perforated tube, and enclosed in a cylindrical plastic casing of a wall-thickness not exceeding 4 mm, whether or not housed in a cylinder of a wall-thickness of 5 mm or more	0
ex 8421 99 00	92		
6305 10 10		Sacks and bags, of a kind used for the packing of goods, used, of jute or of other textile bast fibres of heading No 5303	0
ex 6305 90 00	10	Sacks and bags, of a kind used for the packing of goods, used, of flax or of sisal	0
ex 6305 90 00	91		
ex 6903 20 90	10	Yarn of continuous ceramic filaments, each filament containing by weight: — 12 % or more of diboron trioxide, — 26 % or less of silicon dioxide, and — 60 % or more of dialuminium trioxide	0
ex 6903 90 80	10	Beryllium oxide, of a purity by weight of more than 99 %, in the form of blanks, bars, blocks or plates	0
ex 6909 19 00	40		
ex 6909 12 00	20	Plate, of dialuminium trioxide and titanium carbide, of dimensions not exceeding 48 × 48 mm, or of a diameter not exceeding 125 mm, for the manufacture of magnetic heads <sup>(*)</sup>	0

## ▼M5

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 6909 19 00	30	Supports for catalysts, consisting of porous cordierite or mullite ceramic pieces, of an overall volume not exceeding 65 l, having, per cm <sup>2</sup> of the cross-section, not less than one continuous channel which may be open at both ends or stopped at one end	0
ex 6909 19 00 ex 8102 99 00	50 10	Disc (target) with deposition material, consisting of molybdenum silicide: — containing 1 mg/kg or less of sodium, and — mounted on a metal support	0
ex 7006 00 90	10	Glass plate, coated on one side with chromium and/or with a mixture of diindium trioxide and tin dioxide, of dimensions of 260 × 320 mm or more but not exceeding 400 × 400 mm, of a thickness not exceeding 1,2 mm, for the manufacture of liquid crystal displays (*)	0
ex 7006 00 90	20	Colour filter, consisting of a glass plate with red, blue and green pixels, having a total thickness of 1,1 mm (± 0,1 mm) and exterior dimensions of 320 × 352 mm or more but not exceeding 320 × 400 mm, for the manufacture of liquid crystal displays (*)	0
ex 7006 00 90	30	Glass plate, uncoated, of dimensions of 320 × 352 mm or more but not exceeding 320 × 400 mm, of a thickness of 0,6 mm or more but not exceeding 1,2 mm, for the manufacture of liquid crystal displays (*)	0
ex 7006 00 90	40	Disk of aluminosilicate glass, manufactured from float or pressed glass, with a hole in the centre, with the edges having been ground and bevelled, of a total thickness not exceeding 0,66 mm	0
ex 7011 10 00	10	Glass lenses with a stippled front refractor or with a front refractor composed of prismatic elements, with an external diameter of more than 121 mm but not exceeding 125 mm	0
ex 7011 10 00	20	Parabolic glass reflectors, with an external diameter of more than 121 mm but not exceeding 125 mm	0
ex 7011 20 00	40	Glass face-plate: — with a diagonal measurement of 366,4 mm (± 1,5 mm) and of dimensions of 246,4 × 315,4 mm (± 1,5 mm), — with a diagonal measurement of 391 mm (± 1,5 mm) and of dimensions of 261,4 × 326,8 mm (± 1,5 mm), — with a diagonal measurement of 442 mm (± 1,5 mm) and of dimensions of 293,4 × 369,2 mm (± 1,5 mm), — with a diagonal measurement of 544,5 mm (± 1,6 mm) and of dimensions of 358 × 454 mm (± 1,6 mm), having a cylindrical curvature, — with a diagonal measurement of 570,5 mm (± 1,6 mm) and of dimensions of 360 × 486 mm (± 1,6 mm), — with a diagonal measurement of 629,8 mm (± 3 mm) and of dimensions of 406,5 × 519 mm (± 2 mm), having a cylindrical curvature, or — with a diagonal measurement of 753 mm (± 1,6 mm) and of dimensions of 471 × 640 mm (± 1,6 mm), and with a raised edge, for the manufacture of colour cathode-ray tubes (*)	0
ex 7011 20 00	75	Glass face-plate: — with a diagonal measurement of 604,5 mm (± 3 mm) and of dimensions of 340 × 541 mm (± 2 mm), — with a diagonal measurement of 639,3 mm (± 3 mm) and of dimensions of 413,6 × 527 mm (± 2 mm), — with a diagonal measurement of 708 mm (± 3 mm) and of dimensions of 404 × 633 mm (± 2 mm), — with a diagonal measurement of 723 mm (± 3 mm) and of dimensions of 477 × 602 mm (± 2 mm), or	

▼ M5

CN code	TARIC	Description	Rate of autonomous duty (%)
		— with a diagonal measurement of 812,8 mm ( $\pm$ 3 mm) and of dimensions of 463,8 $\times$ 725,5 mm ( $\pm$ 2 mm), having a cylindrical curvature, for the manufacture of colour cathode-ray tubes <sup>(*)</sup>	0
ex 7014 00 00	10	Optical elements of glass (other than those of heading No 7015), not optically worked, other than signalling glass-ware	0
ex 7019 19 10	10	Yarn of 33 tex or a multiple thereof, $\pm$ 7,5 %, obtained from continuous spun-glass filaments of a nominal diameter of 3,5 $\mu$ m or of 4,5 $\mu$ m, in which filaments of a diameter of 3 $\mu$ m or more but not exceeding 5,2 $\mu$ m predominate, other than those treated so as to improve their adhesion to elastomers	0
ex 7019 19 10	30	Yarn of 22 tex $\pm$ 7,5 %, obtained from continuous spun-glass filaments of a nominal diameter of 5 $\mu$ m, in which filaments of a diameter of 4,2 $\mu$ m or more but not exceeding 5,8 $\mu$ m predominate	0
ex 7019 19 10	40	Yarn of 33, 34 or 51 tex or a multiple thereof, $\pm$ 7,5 %, obtained from continuous spun-glass filaments of a nominal diameter of 6 $\mu$ m, in which filaments of a diameter of 5,1 $\mu$ m or more but not exceeding 6,9 $\mu$ m predominate	0
ex 7019 32 00	10	Non-woven product of non-textile glass fibre, for the manufacture of air-filters or of air-filtration products <sup>(*)</sup>	0
ex 7019 39 10	10		
ex 7019 39 90	10		
ex 7019 90 10	10	Non-textile glass fibres in which fibres of a diameter of less than 3,5 $\mu$ m predominate	0
ex 7019 90 10	20	Non-textile E-glass fibres, of a length not exceeding 3 mm and a diameter of 5 $\mu$ m, for the manufacture of catalysts for the purification of smokes <sup>(*)</sup>	0
ex 7116 20 90	10	Disc of silicon on sapphire	0
7202 50 00		Ferro-silico-chromium	0
ex 7212 50 91	10	Perforated steel strip, plated or coated with nickel, of a width of 140 mm or more but not exceeding 400 mm and a thickness of 60 $\mu$ m or more but not exceeding 90 $\mu$ m	0
▼ <u>M6</u>			
ex 7212 50 99	10	Cold-rolled steel, coated on both sides with a nickel-zinc layer, in the form of strip of a width of 40,15 ( $\pm$ 0,08) mm and a thickness of 0,3 ( $\pm$ 0,01) mm, containing by weight: — not more than 0,1 % of carbon, — not more than 0,04 % of phosphorus, — not more than 0,05 % of sulphur and — 0,2 % or more but not more than 0,5 % of manganese	0
▼ <u>M5</u>			
ex 7306 30 29	91	Non-alloy steel precision tube, welded and cold finished, of an external diameter exceeding 160 mm and a wall thickness exceeding 2 mm	0
ex 7409 19 00	10	Sheet or plate of polytetrafluoroethylene, with aluminium oxide or titanium dioxide as a filler or reinforced with glass-fibre fabric, laminated on both sides with copper foil	0
ex 7410 21 00	10	Sheet or plate of polytetrafluoroethylene, with aluminium oxide or titanium dioxide as a filler or reinforced with glass-fibre fabric, laminated on both sides with copper foil, or sheet of polyimide, laminated on one side or on both sides with copper foil	0
ex 7616 99 90	40	Discs of aluminium alloy, coated or covered on both sides with a nickel-phosphorus layer, having a total thickness not exceeding 3,02 mm	0
ex 7616 99 90	50	Discs of aluminium alloy, of a thickness not exceeding 0,84 mm, for the manufacture of goods of subheadings 8523 20 11 and 8523 20 19 <sup>(*)</sup>	0

## ▼M5

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 7905 00 00	10	Plate of an alloy of zinc, ground and polished on one surface and coated with an epoxide resin on the other surface, of rectangular or square shape, of a length of 300 mm or more but not exceeding 2 000 mm and of a width of 300 mm or more but not exceeding 1 000 mm, and containing: — 10 mg/kg or less of iron, — 10 mg/kg or less of lead, — 700 mg/kg or more but not more than 900 mg/kg of aluminium and — 500 mg/kg or more but not more than 900 mg/kg of magnesium,  for the manufacture of sensitised printing plates <sup>(a)</sup>	0
ex 8101 99 00	10	Disc (target) with deposition material, of tungsten or an alloy containing by weight 90 % of tungsten and 10 % of titanium:  — containing 100 µg/kg or less of sodium and — mounted on a copper or aluminium support	0
ex 8103 90 90	10	Welded tube solely of tantalum, or solely of an alloy of tantalum with tungsten containing by weight 3,5 % or less of tungsten	0
ex 8104 11 00	30	Unwrought magnesium, of a purity by weight of 99,95 % or more, in the form of ingots, for the manufacture of zirconium sponge or elements used in the nuclear industry <sup>(a)</sup>	0
ex 8104 90 00	10	Ground and polished magnesium sheets, of dimensions not exceeding 1 500 × 2 000 mm, coated on one side with an epoxy resin insensitive to light	0
ex 8108 10 10	10	Titanium sponge	0
8108 10 90		Waste and scrap of titanium	0
ex 8108 90 90	92	Disc (target) with deposition material, of titanium:  — containing 50 µg/kg or less of sodium and — mounted on a copper or aluminium support	0
ex 8109 10 10	10	Non-alloy zirconium, in the form of ingots, containing by weight more than 0,01 % of hafnium, for use in the manufacture of tubes for the chemical industry <sup>(a)</sup>	0
ex 8110 00 11	10	Antimony in the form of ingots	0
ex 8112 19 00	10	Beryllium, of a purity by weight of 94 % or more, in the form of bars, plates and sheets	0
ex 8112 99 30	10	Alloy of niobium (columbium) and titanium, in the form of bars and rods	0
ex 8414 90 90	10	Aluminium pistons, partially covered with polytetrafluoroethylene, for incorporation into compressors of air conditioning machines of motor vehicles <sup>(a)</sup>	0
ex 8414 90 90	20	Pressure-regulating system, for incorporation into compressors of air conditioning machines of motor vehicles <sup>(a)</sup>	0
ex 8418 99 90	91	Welded cooling micro-elements, of an alloy of aluminium, for the manufacture of condensers <sup>(a)</sup>	0
ex 8419 19 00	10	Heat accumulator for motor vehicles, of a coolant capacity of 4 l or more but not exceeding 10 l	0
ex 8419 89 98	10	Immersion-tube (coils) bundles, consisting of an assembly of plastic tubes terminating at each end in a honeycomb-structure (end-fitting) surrounded by a pipe-connector	0
ex 8419 89 98	20	Sputtering machines and apparatus, comprising disk handling equipment, for use in the manufacture of products falling within subheading 8523 20 11 or 8523 20 19 <sup>(a)</sup>	0
ex 8543 89 95	58		0

▼ **M5**

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 8421 99 00	91	Parts of equipment, for the purification of water by reverse osmosis, consisting of a bundle of hollow fibres of artificial plastic material with permeable walls, embedded in a block of artificial plastic material at one end and passing through a block of artificial plastic material at the other end, whether or not housed in a cylinder	0
ex 8421 99 00	93	Components of separators for the separation or purification of gases from gas mixtures, consisting of a bundle of permeable hollow fibres enclosed within a container, whether or not perforated, of an overall length of 300 mm or more but not exceeding 3 700 mm and a diameter not exceeding 500 mm	0
ex 8421 99 00	95	Parts of equipment for the filtration of magnetic dispersions, consisting essentially of nylon-6 fibres, enclosed in a plastic casing of a diameter of 70 mm ( $\pm 2$ mm) and a length of 520 mm ( $\pm 5$ mm)	0
ex 8424 89 95	10	Machines and apparatus providing automated lapping, polishing, grinding, cleaning or surface lubrication of disks, comprising disk handling equipment, for use in the manufacture of products falling within subheading 8523 20 11 or 8523 20 19 <sup>(a)</sup>	0
ex 8460 21 90	10		
ex 8460 40 10	10		
ex 8460 90 90	10		
ex 8464 20 19	10		
ex 8479 89 98	10		
ex 8424 89 95	20	Machines and apparatus providing automated cleaning or cleaning and drying of disks, by means of de-ionised water, ultra sonic waves, chemical solutions, heat or a combination of these processes, comprising disk handling equipment, for use in the manufacture of products falling within subheading 8523 20 11 or 8523 20 19 <sup>(a)</sup>	0
ex 8479 89 98	30		
ex 8424 89 95	30	Machines and apparatus for the application of adhesives, soldering pastes or epoxy dots on printed circuit boards	0
ex 8479 89 98	50		
ex 8439 99 10	10	Suction-roll shells, not drilled, in the form of alloy-steel tubes, of a length of 5 207 mm or more and an external diameter of 754 mm or more, for use in machinery for making paper or paperboard <sup>(a)</sup>	0
ex 8439 99 90	10		
ex 8455 90 00	10	Helical turn device for cold-rolling mill	0
ex 8456 10 90	10	Machine-tool operating by laser beam, for the cutting of slots on the surface of a cylindrical tube for use in the manufacture of endo-vascular prosthesis (so-called 'stents') <sup>(a)</sup>	0
ex 8460 90 90	20	Machine-tool providing automated creation of a texture (a head landing zone) on the surface of disks by means of abrasion or exposure to laser beams, comprising disk handling equipment, for use in the manufacture of products falling within subheading 8523 20 11 or 8523 20 19 <sup>(a)</sup>	0
ex 8463 90 00	10		
ex 8479 89 98	20		
ex 8473 40 19	20	Thermal printer head	0
ex 8479 89 98	40	Motor, whether or not mounted on a baseplate, for use in the manufacture of products falling within subheading 8525 20 91 or 8527 90 92 <sup>(a)</sup>	0
ex 8501 10 99	78		
ex 8479 89 98	60	Machines and apparatus for the placement or removal of active/passive components or connecting elements on/from printed circuit boards	0
ex 8481 80 59	10	Air control valve, consisting of a stepping motor and a valve pintle, for the regulation of idle air flow in fuel injection engines	0
ex 8483 10 80	10	Integrally forged and roughly shaped generator and turbine shafts of a weight exceeding 215 tonnes	0
ex 8501 10 99	54	DC motor, brushless, with an external diameter not exceeding 25,4 mm, a rated speed of 2 260 ( $\pm 15$ %) or 5 420 ( $\pm 15$ %) rpm, a supply voltage of 1,5 or 3 V	0

## ▼M5

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 8501 10 99	59	DC stepping motor, with an angle of step of 1,8 ° (±0,09 °), a holding torque of 0,156 Nm or more, a coupling flange the exterior dimensions of which do not exceed 43 × 43 mm, a chuck of a diameter of 4 mm (± 0,1 mm), a two-phase winding and an output not exceeding 5 W	0
ex 8501 10 99	73	DC motor, whether or not mounted on a baseplate, for use in the manufacture of products falling within subheading 8471 70 53 (a)	0
ex 8501 10 99	77	DC motor, with brushes, with a typical running torque of 0,004 Nm (± 0,001 Nm), with a coupling flange of a diameter of 32 mm (± 0,5 mm) and a chuck of a diameter of 2 mm (± 0,004 mm), with an internal rotor, a three-phase winding, a rated speed of 2 800 (± 10 %) rpm and a supply voltage of 12 V (± 15 %)	0
ex 8502 40 90	10	Rotary converter, with a ferrite core, having coils with 2 or 6 windings and a diameter of 0,1 mm, connected to a flexible printed circuit	0
ex 8503 00 91	31	Rotor, at the innerside provided with one or two magnetic rings whether or not incorporated in a steel ring	0
ex 8503 00 99	32		
ex 8503 00 99	31	Stamped collector of an electric motor, having an external diameter not exceeding 16 mm	0
ex 8504 40 99	20	Direct current to direct current converter	0
ex 8504 50 30	10	Inductor with an inductance not exceeding 62 mH	0
ex 8504 50 80	30		
ex 8504 50 80	40	Multilayer monolithic inductors, contained in a housing of the SMD (surface mounted device) type the exterior dimensions of which do not exceed 1,8 × 3,4 mm, for use in the manufacture of products falling within subheading 8517 11 00, 8525 20 91 or 8527 90 92 (a)	0
8504 90 11		Ferrite cores	0
ex 8504 90 18	32	Part of a rotary transformer, comprising a ferrite core provided with circular grooves with copper wire windings	0
ex 8505 11 00	31	Ferrite magnet having a remanence of 455 mT (± 15 mT)	0
ex 8505 19 90	31	Neodymium-ferro ring with an external diameter not exceeding 13 mm, an internal diameter not exceeding 9 mm and a thickness not exceeding 0,9 mm	0
ex 8505 90 10	91	Solenoid with a plunger, operating at a nominal supply voltage of 24 V at a nominal DC of 0,08 A, for use in the manufacture of products falling within heading No 8517 (a)	0
ex 8505 90 10	92	Electro-mechanical throttle plate actuator for automotive engines	0
ex 8506 50 90	10	Lithium iodine single cell battery the dimensions of which do not exceed 9 × 23 × 45 mm and a voltage not exceeding 2,8 V	0
ex 8506 50 90	20	Unit consisting of not more than 2 lithium batteries embedded in a socket for integrated circuits (battery-buffered socket), with not more than 32 connections and incorporating a control circuit	0
ex 8507 30 91	20	Rectangular accumulator, with a length not exceeding 69 mm, a width not exceeding 36 mm and a thickness not exceeding 12 mm, for use in the manufacture of rechargeable batteries (a)	0
ex 8507 80 91	10		
ex 8507 80 99	10		
ex 8507 30 91	30	Cylindrical nickel-cadmium accumulator, with a length of 65,3 mm (± 1,5 mm) and a diameter of 14,5 mm (± 1 mm), having a nominal capacity of 1 000 mAh or more, for use in the manufacture of rechargeable batteries (a)	0
ex 8507 80 91	20	Cylindrical nickel-hydride accumulator, with a length of 44 mm (± 0,5 mm) and a diameter of 10 mm (± 0,5 mm), having a nominal capacity of 450 mAh or more, for use in the manufacture of rechargeable batteries (a)	0

## ▼M5

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 8507 80 91	30	Cylindrical nickel-hydrate accumulator, with a length of 42,5 mm ( $\pm 0,5$ mm) and a diameter of 14 mm ( $\pm 0,5$ mm), having a nominal capacity of 855 mAh or more, for use in the manufacture of rechargeable batteries <sup>(a)</sup>	0
ex 8507 80 91	40	Cylindrical nickel-hydrate accumulator, with a length of 49,5 mm ( $\pm 0,5$ mm) and a diameter of 10 mm ( $\pm 0,5$ mm), having a nominal capacity of 540 mAh or more, for use in the manufacture of rechargeable batteries <sup>(a)</sup>	0
ex 8507 80 99	20	Cylindrical lithium-ion accumulator, with a length of 64,6 mm or more and a diameter of 18,1 mm or more, having a nominal capacity of 1 200 mAh or more, for use in the manufacture of rechargeable batteries <sup>(a)</sup>	0
ex 8516 90 00	31	Dual diode, consisting of a power rectifying diode connected with a transformer protector diode through a wire, with a peak reverse power rate of 2 J or more, for use in the manufacture of products falling within subheading 8516 50 00 <sup>(a)</sup>	0
ex 8517 50 90 ex 8517 80 90	10 30	Transmitter, capable of converting electrical signals into light pulses, operating at a nominal wavelength of 820 nm, comprising a light-emitting diode, contained in a plastic housing with 8 connections and bearing:  — an identification marking consisting of or including (one of) the following combination(s):  HFBR 1412 HFBR 1414  or  — other identification markings relating to devices complying with the abovementioned description	0
ex 8517 50 90 ex 8517 80 90	20 40	Receive unit, capable of converting light pulses into electrical signals, operating at a nominal wavelength of 820 nm, comprising a photodiode and an amplifier, contained in a plastic housing with 8 connections and bearing:  — an identification marking consisting of or including (one of) the following combination(s):  HFBR 2412 HFBR 2414 HFBR 2416  or  — other identification markings relating to devices complying with the abovementioned description	0
ex 8517 50 90 ex 8517 80 90	30 10	Transmitter, capable of converting electrical signals into light pulses, operating at a nominal wavelength of 850 nm, comprising a light-emitting diode, a current switch, an input buffer and a distortion/compensation circuit, contained in a housing bearing:  — an identification marking consisting of or including (one of) the following combination(s):  DM-231-TA  or  — other identification markings relating to devices complying with the abovementioned description	0
ex 8517 50 90 ex 8517 80 90	40 20	Receive unit, capable of converting light pulses into electrical signals, operating at a nominal wavelength of 850 nm, comprising a photodiode, 2 decision circuits, an amplifier and an integrator, contained in a housing bearing:  — an identification marking consisting of or including (one of) the following combination(s):  DM-231-RA  or  — other identification markings relating to devices complying with the abovementioned description	0

## ▼M5

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 8517 50 90 ex 8517 80 90	50 50	Receive and transmit unit, only for cables with optical fibres, capable of converting light pulses into electrical signals and converting electrical signals into light pulses, operating at a nominal wavelength of 1 300 nm	0
ex 8517 50 90	60	Electro-optic modulator with a lithium-niobate crystal, contained in a housing equipped with optical fibre cables and radiofrequency (RF) connectors	0
ex 8517 90 11	07	Modulator/demodulator (modem), consisting of 2 or more monolithic integrated circuits mounted on a support, contained in a housing the exterior dimensions of which do not exceed 32 × 82 mm	0
ex 8517 90 82	10	Assembly for telephonic apparatus comprising a microphone, a protection circuit and a four-way connecting socket, mounted on a printed circuit the dimensions of which do not exceed 22 × 40 mm	0
ex 8517 90 82	20	16 × 16- or 32 × 32-bit differential crosspoint switch of gallium arsenide (GaAs) semiconductor material, capable of switching at a data rate per second of at least 800 Mbits, in the form of a monolithic integrated circuit contained in a housing combined with decoupling capacitors, the whole mounted on a substrate the exterior dimensions of which do not exceed 35 × 35 mm, with not more than 196 connections and bearing: — an identification marking consisting of or including (one of) the following combination(s): TQ 8016 TQ 8032 or — other identification markings relating to devices complying with the abovementioned description	0
ex 8517 90 82	30	Assembly consisting of a laser diode operating at a nominal wavelength of 780 nm, a photodiode and a lens, contained in a housing with a diameter of not more than 9 mm and a height of not more than 20 mm, with not more than 3 connections	0
ex 8517 90 82	50	Assembly comprising light-emitting diodes	0
ex 8517 90 88	10	Assembly consisting of a laser diode operating at a nominal wavelength of 980 nm, a photodiode, a thermistor and a cooling plate, contained in a housing with an optical fibre cable connection and bearing: — an identification marking consisting of or including (one of) the following combination(s): QLM9S470 or — other identification markings relating to devices complying with the abovementioned description	0
ex 8517 90 88 ex 8548 90 90	20 38	Parts, for use in the manufacture or the repair of products falling within subheading 8517 21 00 (*)	0
ex 8518 29 20 ex 8518 29 80	10 20	Loudspeaker having a power of 5 W and an impedance of 4 ohms, with a diameter not exceeding 50 mm, for use in the manufacture of portable phones (*)	0
ex 8518 30 80	20	Headphone and earphone for hearing aids, contained in a housing the exterior dimensions of which, excluding connecting points, do not exceed 5 × 6 × 8 mm	0
ex 8518 90 00	91	Integrally cold-upsetted steel coreplate, in the form of a disk on one side provided with a cylinder, for use in the manufacture of loudspeakers (*)	0

▼ M5

CN code	TARIC	Description	Rate of autonomous duty (%)
<b>▼ <u>M6</u></b>			
ex 8520 90 90	20	Drive-unit capable of magneto-optical signal recording and optical signal reproducing, comprising at least an optical unit, DC motors and a printed circuit on which are mounted integrated circuits providing drive and signal processing functions for reading optical discs having an external diameter not exceeding 70 mm, not comprising circuits with amplification functions or power supply drive functions	0
<b>▼ <u>M5</u></b>			
ex 8522 90 59	93	Optical unit consisting of a laser diode with one photodiode, emitting light of a nominal wavelength of 780 nm, contained in a housing with a diameter of not more than 10 mm and a height of not more than 9 mm, with not more than 10 connections and bearing: — an identification marking consisting of or including (one of) the following combination(s):  LDGU LT 022  or — other identification markings relating to devices complying with the abovementioned description	0
ex 8522 90 59	94	Electronic assembly for a laser read-head of a compact disc player, comprising: — a printed circuit, — a photo-detector, in the form of a monolithic integrated circuit, contained in a housing, — not more than 3 connectors, — not more than 1 transistor, — not more than 3 variable and 4 fixed resistors, — not more than 5 capacitors,  the whole mounted on a support	0
ex 8522 90 98	31	Thin-film recording and reproducing device, having at least 9 parallel channels for digital signals and at least 2 channels for analogue signals, to which a non-magnetic ceramic substrate is fixed, the whole rounded at one side, for use in the manufacture of magnetic heads for digital sound recording and digital/analogue sound reproducing apparatus of the cassette-type <sup>(a)</sup>	0
ex 8522 90 98	32	Sound reproducing assembly, consisting of a compact disc mechanism, comprising an optical reading system and 3 DC motors, for use in the manufacture of products falling within subheading 8527 21 20 or 8527 21 70 <sup>(a)</sup>	0
ex 8522 90 98	34	Cassette-deck sub-assembly for sound recording and reproducing apparatus, for use in the manufacture of telephone answering machines <sup>(a)</sup>	0
ex 8522 90 98	35	Sound reproducing assembly, comprising a tape deck mechanism of the cassette type, comprising a DC motor, for use in the manufacture of products falling within heading No 8519 <sup>(a)</sup>	0
ex 8522 90 98	36	Roll for magnetic tape guiding and winding, for use in the manufacture of products falling within heading No 8521 or 8522 <sup>(a)</sup>	0
ex 8522 90 98	37	Magnetic head for erasing video tapes, for use in the manufacture of products falling within heading No 8521 or 8522 <sup>(a)</sup>	0
ex 8522 90 98	38	Read-head assembly, comprising a laser read-head, 2 motors, a flexible printed circuit, the whole mounted on a plastic support, for use in the manufacture of products falling within subheading 8519 99 12 or 8519 99 18 <sup>(a)</sup>	0
ex 8522 90 98	39	Assembly consisting of a driver circuit, a tacho-sensor and a brushless DC motor	0

## ▼M5

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 8522 90 98	40	Compact disc changing and selection mechanism, comprising electronic components, not comprising circuits with amplification functions or power supply drive functions, for use in the manufacture of products falling within subheading 8527 31 91 (*)	0
ex 8522 90 98	41	Assembly consisting of a drive-unit, comprising at least an optical unit, DC motors and a printed circuit on which are mounted integrated circuits providing drive and signal processing functions for reading optical discs, not capable of recording, for use in the manufacture of products falling within heading No 8521 (*)	0
ex 8522 90 98	42	Sound reproducing assembly, consisting of a compact disc changing and selection mechanism, comprising an optical reading system, DC motors and an electronic assembly not comprising circuits with amplification functions or power drive functions, for use in the manufacture of products falling within heading No 8527 (*)	0
ex 8522 90 98	43	Analogue sound recording and reproducing assembly, comprising a record/playback head and a twin tape deck mechanism of the cassette type, not comprising circuits with amplification functions or power supply drive functions, for use in the manufacture of products falling within subheading 8527 31 98 (*)	0
ex 8523 12 00	10	Magnetic tape, with a thickness not exceeding 16 µm and a width of 6,274 (± 0,013 mm), on reels, not mounted in a cartridge	0
ex 8523 20 19	40	Rigid magnetic disks, pre-lubricated, oxide type, with a coercivity of 300 Oe or more, not mounted in a cartridge	0
ex 8528 22 00	10	Video monitor comprising: — a flat screen monochrome cathode-ray tube with a diagonal measurement of the screen not exceeding 110 mm and equipped with a deflector yoke, and — a printed circuit on which are mounted a deflection unit, a video-amplifier and a transformer,  the whole mounted on a chassis, for the manufacture of video entry-phones, video telephones or surveillance apparatus (*)	0
ex 8529 10 70	10	Ceramic filter package comprising 2 ceramic filters and 1 ceramic resonator for a frequency of 10,7 MHz (± 30 kHz), contained in a housing	0
ex 8529 10 70	15	Ceramic filter for a centre frequency of 10,7 MHz, with a bandwidth not exceeding 330 kHz at 3 dB and not exceeding 950 kHz at 20 dB, contained in a housing	0
ex 8529 10 70	20	Ceramic filters for frequencies of 4,5 MHz or more but not exceeding 6,6 MHz contained in a housing	0
ex 8529 10 70	25	Ceramic filter for a centre frequency of 450 kHz or more but not exceeding 470 kHz, with a bandwidth not exceeding 13 kHz at 3 dB, contained in a housing	0
ex 8529 10 70	30	Ceramic filter for a frequency of 450 kHz, with a bandwidth not exceeding 18 kHz at 10 dB, contained in a housing	0
ex 8529 10 70	35	Ceramic filter for a centre frequency of 455 kHz (± 1,5 kHz), with a bandwidth not exceeding 25 kHz at 6 dB and not exceeding 60 kHz at 40 dB, contained in a housing	0
ex 8529 10 70	40	Radio frequency (RF) signal isolator for frequencies of 890 MHz or more but not exceeding 1 880 MHz, having an insertion loss not exceeding 0,7 dB, contained in a housing	0
ex 8529 10 70	45	Ceramic filter for a centre frequency of 450 kHz (± 1,5 kHz) or 455 kHz (± 1,5 kHz), with a bandwidth not exceeding 30 kHz at 6 dB and not exceeding 70 kHz at 40 dB, contained in a housing	0

## ▼M5

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 8529 10 70	75	Bandpass filter, excluding surface acoustic wave filters, for a centre frequency of 485, 1 212, 1 747,5, 1 842,5, 1 880 or 1 960 MHz, with an insertion loss not exceeding 3,5 dB, contained in a housing	0
ex 8529 10 70	80	Ceramic filter package, excluding surface acoustic wave filters, consisting of: — a transmit filter with a centre frequency of 1 747,5 MHz and an insertion loss not exceeding 2,3 dB at a bandwidth of 75 MHz and — a receive filter with a centre frequency of 1 842,5 MHz and an insertion loss not exceeding 3,3 dB at a bandwidth of 75 MHz, the whole contained in a housing	0
ex 8529 10 70	85	Ceramic filter package, excluding surface acoustic wave filters, comprising 2 filters with one of the following combinations of characteristics: — a transmit centre frequency of 902,5 MHz, a receive centre frequency of 947,5 MHz and an insertion loss not exceeding 3,2 dB at a bandwidth of 25 MHz or — a transmit centre frequency of 1 747,5 MHz, a receive centre frequency of 1 842,5 MHz and an insertion loss not exceeding 3,5 dB at a bandwidth of 75 MHz, the whole contained in a housing	0
ex 8529 10 90	10	Antenna switch, comprising: — a transmit filter with a centre frequency of 942,5 MHz or more but not exceeding 1 441 MHz and — a receive filter with a centre frequency of 847,5 MHz or more but not exceeding 1 489 MHz, the whole contained in a housing	0
ex 8529 90 40	30	Filter, consisting of 2 piezo-electric crystals each with a frequency of 21 MHz or more but not exceeding 30 MHz and separately mounted on a bracket, with not more than 7 connections	0
ex 8529 90 81	37		
ex 8529 90 88	33		
ex 8529 90 40	40	Ceramic intermediate frequency (IF) filter, excluding surface acoustic wave filters, for a centre frequency of 13 MHz and an insertion loss not exceeding 6 dB, contained in a housing	0
ex 8529 90 81	31	Demagnetisation coil, with at least one of following characteristics: — an internal diameter of less than 375 mm, — an internal linear dimension measured on the surface profile of less than 1 178 mm, with cables and connectors	0
ex 8529 90 81	32	Optical unit for video projection, comprising a colour separation system, a positioning mechanism and lenses, for use in the manufacture of products falling within heading No 8528 (*)	0
ex 8529 90 81	34	Assembly consisting of a lens unit, having an adjustable focal length of 4 mm or more but not exceeding 69 mm and comprising a zoom encoder, a stepping motor unit, a zoom motor unit, an iris motor unit and a photo interrupter	0
ex 8529 90 81	35	Video recording and reproducing assembly, comprising a tape deck mechanism of the cassette type, comprising a DC motor, for use in the manufacture of products falling within heading No 8525 (*)	0

## ▼M5

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 8529 90 81	36	Assembly consisting of a monochrome cathode-ray tube with a diagonal measurement of the screen of 165 mm or more but not exceeding 230 mm and a concave focus lens mounted on a liquid-filled cooling armature, for use in the manufacture of television projection equipment <sup>(*)</sup>	0
ex 8531 20 30	10	Dot matrix display consisting of a line of 8 characters, each character composed of 35 light-emitting diodes (LED), comprising electronic components for interface and drive functions, contained in a housing the exterior dimensions of which do not exceed 26 × 90 mm, with not more than 28 connections and bearing:  — an identification marking consisting of or including (one of) the following combination(s):  HDSP 2107 HDSP 2111 HDSP 2112 HDSP 2113 PDSP 2110 PDSP 2111 PDSP 2112 PDSP 2113 SDA 5708-24  or  — other identification markings relating to devices complying with the abovementioned description	0
ex 8531 20 30	20	Digital displays, consisting of a printed circuit board of a size not exceeding 35 × 90 mm with a single line of characters, not less than 3 in number, comprising light-emitting diodes (LED) made from gallium-based semiconductor materials mounted thereon. Each character is composed of up to 8 segments with or without a decimal point and the line of characters has a protective cover of plastic	0
ex 8531 20 50	10	Liquid crystal colour display (LCD) with an active matrix and 480 × 640 or 600 × 800 pixels, consisting of a layer of liquid crystals between two glass sheets or plates, comprising electronic components providing drive and/or control functions, for use in the manufacture of products falling within subheading 8471 30 99 <sup>(*)</sup>	0
ex 8531 20 50	20	Liquid crystal colour display (LCD) with an active matrix and 768 × 1 024 or 900 × 1 152 pixels, consisting of a layer of liquid crystals between two glass sheets or plates, comprising electronic components providing drive and/or control functions	0
ex 8531 20 50	30	Liquid crystal colour display (LCD) with an active matrix and 1 024 × 1 280 pixels, consisting of a layer of liquid crystals between two glass sheets or plates, mounted on a printed circuit comprising electronic components providing drive and/or control functions	0
ex 8531 20 50	40	Liquid crystal monochrome display (LCD) with an active matrix and 900 × 1 152 pixels, consisting of a layer of liquid crystals between two glass sheets or plates, comprising electronic components providing drive and/or control functions	0
ex 8531 20 80	20	Liquid crystal display (LCD), other than with an active matrix, comprising one or more monolithic integrated circuits mounted on the glass (so-called 'chip on glass' technology)	0
ex 8531 20 80	30	Liquid crystal display (LCD), other than with an active matrix, having 256 000 pixels or more, comprising electronic components	0
ex 8531 80 30	10	Plasma display	0
ex 8531 80 30	20	Vacuum fluorescent display, comprising electronic components providing drive and/or control functions	0

## ▼M5

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 8531 80 30	30	Monochrome electroluminescent display, with a diagonal measurement of the screen not exceeding 36 cm, mounted on a printed circuit, comprising electronic components providing drive and/or control functions	0
ex 8531 80 80	01	Indicator lamp, consisting of 4 light-emitting diodes made from silicon-carbide (SiC) semiconductor material, operating at a nominal wavelength of 481, 560 or 630 nm, contained in a housing	0
ex 8531 80 80	15	Indicator lamp, consisting of 2 light-emitting diodes made from aluminium-gallium-arsenic (AlGaAs) or gallium-phosphor (GaP) semiconductor material, having a rectangular base, contained in a housing of the SMD (surface mounted device) type and having a lens	0
ex 8531 80 80	25	Electro-acoustic transducer	0
ex 8531 80 80	30	An electromagnetic display, consisting of 7 electromagnetic coils which by means of the residual magnetism in the stators provide that the last indication remains available (set state), and 7 pivoting light-reflecting segments each of which is attached to a bar magnet; assembly comprising such displays	0
ex 8531 90 10	91	Backlight unit, comprising a lampholder with a cathode tube, a reflection sheet and a diffuse substrate, the exterior dimensions of which do not exceed 7 × 250 × 300 mm, for use in the manufacture of liquid crystal displays (LCD) (°)	0
ex 8532 22 00	95	Aluminium electrolytic capacitors, with a fixed nominal capacity not exceeding 470 µF and an operating voltage not exceeding 50 V, operating within a temperature range of -40 °C to + 85 °C, having a diameter not exceeding 8 mm and a height not exceeding 6 mm	0
ex 8532 22 00	96	Aluminium electrolytic capacitors, with a fixed nominal capacity of 2,2 µF and an operating voltage of 385 V, operating within a temperature range of -40 °C to + 85 °C	0
ex 8532 22 00	97	Aluminium electrolytic capacitor, with a fixed nominal capacity not exceeding 3,3 F and an nominal operating voltage of 2,5 or 5,5 V, operating within a temperature range of -25 °C to + 85 °C	0
ex 8532 22 00	98	Aluminium electrolytic capacitors, with a nominal capacity of 0,1 µF or more but not exceeding 1 000 µF and an operating voltage of 4 V or more but not exceeding 50 V, operating within a temperature range of -40 °C to + 105 °C, contained in a housing of the SMD (surface mounted device) type	0
ex 8532 23 00	91	One layer ceramic dielectric capacitor, with a fixed nominal capacity of 1 pF or more but not exceeding 1 µF and a nominal operating voltage not exceeding 50 V, operating within a temperature range of -25 °C to + 85 °C	0
ex 8532 24 00	31	Multilayer ceramic dielectric capacitor, contained in a housing of the SMD (surface mounted device) type the exterior dimensions of which do not exceed 0,55 × 0,55 × 1,05 mm	0
ex 8532 29 00	31	Capacitor with 2 dielectric materials, one in ceramic, the other in epoxy resin, having an initial capacitance of 500 pF (± 35 %) and a dissipation factor not exceeding 2,5 %	0
ex 8532 90 00	32	Anode or cathode, for use in the manufacture of aluminium electrolytic capacitors (°)	0
ex 8533 10 00	92	Fixed carbon composition resistor, with an operating voltage not exceeding 350 V and a dissipation rate not exceeding 0,5 W	0

▼ **M5**

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 8533 21 00	32	Thermistor with a positive temperature coefficient, with at least one of the following characteristics: — a thickness of less than 1 mm, — a hold current of more than 0,75 A, contained in a housing of the SMD (surface mounted device) type, — a hold current of more than 3 A	0
<b>▼ M6</b>			
ex 8533 40 10	31	Package of potentiometers (so-called focus block), with a supply voltage of 9,3 kV or more but not exceeding 28 kV, contained in a housing with connectors	0
<b>▼ M5</b>			
ex 8534 00 11	91	Single-face printed circuit the dimensions of which do not exceed 30 × 30 mm, for the manufacture of products falling within Chapter 91 <sup>(a)</sup>	0
ex 8534 00 19	91		
ex 8534 00 11	92	Multiple printed circuit, consisting of 24 layers, including 5 layers with buried vias of bismaleimide triazine, the exterior dimensions of which do not exceed 64 × 65 cm	0
ex 8534 00 11	93	Multiple printed circuit, with connectors, and in an aluminium casing	0
ex 8534 00 19	92	Single-face printed circuits fixed on a plastic tape with sprocket holes on both edges, for use in the manufacture of ink jet printer cartridges <sup>(a)</sup>	0
ex 8534 00 19	94	Printed circuit, consisting of 29 or 31 conductor elements fixed on a flexible plastic film, for use in the manufacture of magnetic heads for digital sound recording and digital/analogue sound reproducing apparatus of the cassette-type <sup>(a)</sup>	0
ex 8534 00 19	96	Printed circuit on an aluminium oxide support, only with gold plated conductor elements of thick film technology, for use in the manufacture of products falling within subheading 8542 40 00 <sup>(a)</sup>	0
ex 8534 00 90	93	Printed circuit on one or both sides of a ceramic substrate, consisting of conductor elements, contacts and resistors, incorporating connections isolated in vitrified layers, the dimensions of which do not exceed 45 × 45 mm, with not more than 550 connections	0
ex 8534 00 90	94	Printed circuit, consisting of pressure sensitive resistor zones	0
ex 8534 00 90	95	Bandpass filter for a centre frequency of 1 627,5, 1 743, 1 842,5 or 1 960 MHz, in the form of a printed circuit, only consisting of a ceramic insulating base and of resonance elements, for use in the manufacture of products of subheading 8525 20 91 <sup>(a)</sup>	0
ex 8534 00 90	96	Bandpass filter for centre frequencies of 732,5 and 947,5 MHz or of 1 627,5 and 1 842,5 MHz or of 1 738 and 1 960 MHz, in the form of a printed circuit, only consisting of a ceramic insulating base and of resonance elements, for use in the manufacture of products of subheading 8525 20 91 <sup>(a)</sup>	0
ex 8536 30 30	11	Thermo-electric switch with a cut-off current of 50 A or more, comprising a snap action switch, for direct mounting on an electric motor coil, contained in a hermetically sealed housing	0
ex 8536 30 90	31		
ex 8536 50 80	96		
ex 8536 41 10	91	Thermal relays contained in a hermetically sealed glass cartridge not exceeding 35 mm in length excluding wires, with a maximum leakage rate of 10 <sup>-6</sup> cm <sup>3</sup> He/sec at one bar in the temperature range 0 to 160 °C, to be incorporated into compressors for refrigerating equipment <sup>(a)</sup>	0
ex 8536 41 90	91		
ex 8536 49 00	91		
ex 8536 50 11	31	Switch of the printed circuit mount type, operating at a force of 4,9 N (± 0,9 N), contained in a housing	0

▼ M5

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 8536 50 19	91	Hall effect switch, comprising 1 magnet, 1 Hall effect sensor and 2 capacitors, contained in a housing with 3 connections and bearing: — an identification marking consisting of or including (one of) the following combination(s):  2AV28E 2AV31E 2AV56 or — other identification markings relating to devices complying with the abovementioned description	0
▼ <u>M6</u>			
ex 8536 50 19	92	Hydraulic pressure switch, incorporating a pressure sensitive snap action disc, operating at a supply voltage of 6 V or more but not exceeding 18 V	0
▼ <u>M5</u>			
ex 8536 50 80	93	Switch unit for coaxial cable, comprising 3 electromagnetic switches, with a switching time not exceeding 50 ms and an actuating current not exceeding 500 mA at a voltage of 12 V	0
▼ <u>M6</u>			
▼ <u>M5</u>			
ex 8536 50 80	95	Reed switch having a switching power of 20 W or more within the range of 17-43 A.turn, in the form of a glass capsule, not containing mercury, the dimensions of which do not exceed 3 × 21 mm, for use in the manufacture of automotive airbag shock-sensors (*)	0
ex 8536 69 30	31	Male or female connectors, capable of interconnecting printed circuits, consisting of 6 rows of phosphor-bronze or beryllium-copper connections plated with gold over nickel, contained in a plastic housing	0
ex 8536 90 85	92	Metallic stamped frame with connections	0
ex 8536 90 85	93	Contact element with a hold-force of more than 3 N, in the form of 2 rectangular plastic frames interconnected by electric conductors	0
▼ <u>M6</u>			
ex 8536 90 85	94	Elastomeric connector, consisting of one or more conductor elements and of a rubber or silicon substrate	0
ex 8544 49 80	10		
▼ <u>M5</u>			
ex 8537 10 99	92	Touch sensitive screen panel, consisting of a conductive grid between two glass or plastic plates or sheets, fitted with electric conductors and connectors	0
ex 8538 90 99	92	Part of an electrothermal fuse, consisting of a tin coated copper wire attached to a cylindrical casing, the exterior dimensions of which do not exceed 5 × 48 mm	0
ex 8540 11 11	91	Colour cathode-ray tube with a slit or slot mask, equipped with electron guns placed side by side (in-line technology) and with a diagonal measurement of the screen of 12 cm or more but not exceeding 26 cm	0
ex 8540 11 11	93	Colour cathode-ray tube, equipped with 1 gun with 3 rays and with a diagonal measurement of the screen of 22 cm or more but not exceeding 26 cm	0
ex 8540 11 13	91	Colour cathode-ray tube with a slit or slot mask, having a distance between stripes of the same colour of less than 0,42 mm and a diagonal measurement of the screen of 49 cm, for use in the manufacture of professional video monitors including security and medical monitor applications (*)	0
ex 8540 11 19	91	Colour cathode-ray tube equipped with electron guns placed side by side (in-line technology), with a diagonal measurement of the screen of 85 cm or more	0

▼ **M5**

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 8540 11 70	31	Colour cathode-ray tube with a screen width/height ratio of 16/9 and a diagonal measurement of the screen of 39,8 cm ( $\pm 0,3$ cm)	0
▼ <b>M6</b>			
ex 8540 11 70	32	Colour cathode-ray tube with a diagonal measurement of the screen of 85,5 cm or more	0
▼ <b>M5</b>			
ex 8540 12 00	82	Monochrome cathode-ray tube with a diagonal measurement of the screen of 250 mm or more but not exceeding 320 mm and an anode voltage of 18 kV or more but not exceeding 22 kV	0
ex 8540 12 00	83	Monochrome cathode-ray tube, with a diagonal measurement of the screen of 150 mm or more but not exceeding 182 mm, a neck diameter of less than 30 mm and an anode voltage of 25 kV or more but not exceeding 32 kV	0
ex 8540 12 00	84	Flat screen monochrome cathode-ray tube, with a diagonal measurement of the screen not exceeding 102 mm	0
ex 8540 20 80	91	Photomultiplier consisting of a photocathode tube with 9 dynodes, for light of a wavelength of 160 nm or more but not exceeding 930 nm, of a diameter not exceeding 14 mm and a height not exceeding 94 mm	0
ex 8540 40 00 ex 8540 60 00	31 31	Colour cathode-ray tube with a dot mask, equipped with 3 electron guns placed side by side (in-line technology) or 1 gun with 3 rays, with a diagonal measurement of the screen of more than 72 cm and a distance of less than 0,5 mm between dots of the same colour	0
ex 8540 40 00 ex 8540 60 00	32 32	Colour cathode-ray tube with a dot mask, equipped with 3 electron guns placed side by side (in-line technology) or 1 gun with 3 rays, having a diagonal measurement of the screen not exceeding 72 cm	0
ex 8540 40 00	33	Colour cathode-ray tube with a slit or slot mask, having a distance between stripes of the same colour of less than 0,35 mm and a diagonal measurement of the screen not exceeding 53 cm	0
ex 8540 40 00	34	Colour cathode-ray tube with a slit or slot mask, having a distance between stripes of the same colour of less than 0,39 mm and a diagonal measurement of the screen of 33 cm or more but not exceeding 38 cm	0
ex 8540 40 00	35	Colour cathode-ray tube with a slit or slot mask, having a distance between stripes of the same colour of less than 0,35 mm and a diagonal measurement of the screen not exceeding 72 cm, for use in the manufacture of monitors (*)	0
ex 8540 40 00	36	Colour cathode-ray tube with a slit or slot mask, having a distance between stripes of the same colour of less than 0,30 mm and a diagonal measurement of the screen not exceeding 58 cm	0
ex 8540 50 00 ex 8540 60 00	31 33	Flat screen monochrome cathode-ray tube, with a diagonal measurement of the screen of 142 mm or more but not exceeding 190 mm, a luminescence of 300 lumen or more but not exceeding 2 000 lumen, a resolution of 0,06 mm or more but not exceeding 0,1 mm, phosphor types P1 or P22 or P53 or P55 or P56, an anode voltage of more than 34 kV, a focus voltage of more than 7 kV and a cathode current of 3 mA or more	0
ex 8540 50 00 ex 8540 60 00	32 34	Monochrome cathode-ray tube with a diagonal measurement of the screen of 176 mm or more but not exceeding 520 mm and a neck diameter not exceeding 21 mm	0

## ▼M5

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 8540 89 00	91	Displays in the form of a tube consisting of a glass housing mounted on a board the dimensions of which do not exceed 300 × 350 mm excluding leads. The tube contains one or more rows of characters or lines arranged in rows, each character or line consisting of fluorescent or phosphorescent elements. These elements are mounted on a metallised base which is covered with fluorescent substances or phosphorescent salts which give off light when bombarded with electrons	0
ex 8540 89 00	92	Vacuum fluorescent display tube	0
ex 8540 91 00	31	Electron gun, for use in the manufacture of colour cathode-ray tubes of subheading 8540 40 00 with a diagonal measurement of the screen of 34 cm or more but not exceeding 39 cm (*)	0
ex 8540 91 00	91	Deflector yoke for cathode-ray tubes with an operating frequency of 31 250 Hz or more but not exceeding 64 000 Hz, incorporating a quadripolar magnet	0
ex 8540 91 00	92	Slit or slot mask, excluding masks with continuously vertical slits, with a diagonal measurement of 39 cm or less	0
ex 8540 91 00	93	Electron gun for the production of monochrome cathode-ray tubes with a diagonal measurement of the screen of 7,6 cm or more but not exceeding 30,5 cm (*)	0
ex 8540 91 00	94	Deflector yoke for colour cathode-ray tubes, with an operating frequency of 15 625 or 31 250 Hz, comprising 2 two-pole ring magnets, 2 four-pole ring magnets and 2 six-pole ring magnets	0
ex 8540 91 00	96	Assembly for cathode-ray tubes with 2 or more but not more than 6 coils, a plastic support and a metal fixing ring, for the adjustment of display sharpness and/or convergence	0
ex 8540 91 00	97	Slit mask, consisting of continuously vertical slits measuring more than 275 mm in the length	0
ex 8540 91 00	98	Frame of molybdenum chrome steel, for use in the manufacture of cathode-ray tubes (*)	0
ex 8540 99 00	91	Anode, cathode or output part, or an assembly comprising these components (magnetron core tube), for the manufacture of magnetrons of subheading 8540 71 00 (*)	0
ex 8543 89 95	46	<p>Amplifier, consisting of active and passive elements mounted on a printed circuit, contained in a housing bearing:</p> <p>— an identification marking consisting of or including (one of) the following combination(s):</p> <p>FA 01314 FA 01317 FA 01321 FMC 1717 FMC 1819 ISO 122 MHW 105 MHW 1815 MHW 2701 MHW 2707 MHW 607 MHW 704 MHW 707 MHW 720 MHW 803 MHW 820-1 MHW 820-2 MHW 9002 MHW 910 MHW 914 MHW 915 MHW 916 MHW 926 MHW 927 MHW 953</p>	

## ▼M5

CN code	TARIC	Description	Rate of autonomous duty (%)
		PF 0144 PF 0146 PF 0148 PF 0412 PHW 2905 PHW 2907 PHW 5113 PHW 9012 PHW 902 PHW 925 SHW 5115 XHW 105 XHW 2803 XHW 2902 XHW 5115 XHW 903 or — other identification markings relating to devices complying with the abovementioned description	0
ex 8543 89 95	48	Radio frequency (RF) modulator, operating with a frequency range of 43 MHz or more but not exceeding 870 MHz, capable of switching VHF and UHF signals, consisting of active and passive elements mounted on a printed circuit, contained in a housing	0
ex 8543 89 95	49	Rectifier assembly of power barrier diodes, consisting of 2 diodes with an average forward current not exceeding 600 A and a repetitive reverse peak voltage not exceeding 40 V, each contained in a housing and connected by a common cathode	0
ex 8543 89 95	50	Piezo-electric crystal clock oscillator with a fixed frequency, within a frequency range of 1,8 MHz to 67 MHz, contained in a housing bearing: — an identification marking consisting of or including (one of) the following combination(s): R4 000.8 R4 000.9, or — other identification markings relating to devices complying with the abovementioned description	0
ex 8543 89 95	51	Mechanical vibratory gyroscope driven by a 25 or 26 kHz oscillator, comprising a differential amplifier and a detector circuit, contained in a housing bearing: — an identification marking consisting of or including (one of) the following combination(s): ENC05D, or — other identification markings relating to devices complying with the abovementioned description	0
ex 8543 89 95	52	Opto-electronic circuit comprising one or more light-emitting diodes (LEDs) and one photodiode with amplifier circuit and an integrated logic gate arrays circuit or one or more light-emitting diodes and at least 2 photodiodes with an amplifier circuit, contained in a plastic housing bearing: — an identification marking consisting of or including (one of) the following combination(s): HC PL 2400 HC PL 2730, or — other identification markings relating to devices complying with the abovementioned description	0

▼ **M5**

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 8543 89 95	53	Oscillator, with a centre frequency of 20 GHz or more but not exceeding 42 GHz, consisting of active and passive elements not mounted on a substrate, contained in a housing bearing: — an identification marking consisting of or including (one of) the following combination(s): 372-02 372-03, or — other identification markings relating to devices complying with the abovementioned description	0
ex 8543 89 95	55	Audio recording and reproducing circuit, capable of stereo audio data storage and simultaneous record and playback, comprising 2 or 3 monolithic integrated circuits mounted on a printed circuit or a lead frame, contained in a housing bearing: — an identification marking consisting of or including (one of) the following combination(s): RWA010 RWA100 RWA200 RWA300, or — other identification markings relating to devices complying with the abovementioned description	0
ex 8543 89 95	56	Overvoltage suppression assembly, comprising 8 diodes, having a reverse stand-off voltage not exceeding 4,5 V, a reverse leakage current not exceeding 10 µA, a peak pulse current not exceeding 30 A and a nominal capacitance of 50 pF, contained in a housing	0
<b>▼ M6</b>			
ex 8543 89 95	57	Frequency converter, not comprising a dipole aerial, for the conversion of frequencies of 10,7 GHz or more but not exceeding 12,75 GHz to frequencies of 950 MHz or more but not exceeding 3 GHz and operating at a supply voltage of 11 V or more but not exceeding 20 V	0
<b>▼ M5</b>			
ex 8543 89 95	59	Charged coupled device (CCD) scanner assembly, for a real-time film scanning system, having optical functions, illumination functions and signal processing functions	0
ex 8543 90 80	40	Stainless steel cathode in the form of a plate with a hanger bar and plastic side strips	0
ex 8543 90 80	50	Assembly of products falling within heading No 8541 or 8542 mounted on a printed circuit, contained in a housing	0
ex 8545 90 90	01	Cell and battery carbon, in the form of rods, with a length of 34 mm or more but not exceeding 160 mm and a diameter not exceeding 12 mm	0
8548 90 10		Memory in multicombinational forms such as stack D-RAMs and modules	0
ex 8548 90 90	39	Optical unit, consisting of a laserdiode and a photodiode, operating at a typical wavelength of 635 or 670 nm	0
ex 8548 90 90	40	Infrared signal receiver unit, consisting of a photodiode and at least an amplifier in the form of a monolithic integrated circuit, contained in a housing bearing: — an identification marking consisting of or including (one of) the following combination(s): GPIU58XB SBX 1610, or — other identification markings relating to devices complying with the abovementioned description	0

## ▼M5

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 8548 90 90	41	Unit, consisting of a resonator operating within a frequency range of 1,8 MHz or more but not exceeding 40 MHz and a capacitor, contained in a housing	0
ex 8548 90 90 ex 9110 90 00	42 94	Clock/calendar circuit, consisting of a printed circuit on which are mounted at least a quartz oscillator and a monolithic integrated circuit, the whole contained in a housing bearing: — an identification marking consisting of or including (one of) the following combination(s):  DS 1287 DS 12887A DS 1387 MK 48T02 MK 48T08 MK 48T12 MK 48T18 RTC 63421 RTC 65271 RTC 72423 or — other identification markings relating to devices complying with the abovementioned description	0
ex 8548 90 90	43	Contact image sensor	0
ex 9001 10 90	10	Image reverser made up from an assembly of optical fibres	0
ex 9001 20 00	10	Material consisting of a polarising film, supported on one or both sides by transparent material	0
ex 9001 90 90	20	Rear projection screen, comprising a Fresnel lens of plastic and a polarising sheet of plastic, for use in the manufacture of products falling within heading No 8528 (*)	0
ex 9001 90 90	30	Lens of plastic, unmounted, having a focal length of 3,86 mm ( $\pm 0,1$ mm) and with a diameter not exceeding 8 mm, for use in the manufacture of compact disc players (*)	0
ex 9001 90 90	40	Optical fibre plate, for use in the manufacture of screens and photocathodes for image intensifiers (*)	0
ex 9001 90 90	50	Rear projection screen, comprising a lenticular plastic plate	0
ex 9001 90 90	60	Prism for the splitting of light, unmounted, for use in the manufacture of charged-coupled image (CCD) cameras (*)	0
ex 9001 90 90	70	Rod of neodymium-doped yttrium-aluminium garnet (YAG) material, polished at both ends	0
ex 9001 90 90	80	Lens of plastic, unmounted, for use in the manufacture of products falling within subheading 9006 40 00 (*)	0
ex 9002 11 00	10	Adjustable lens unit, having a focal length of 90 mm or more but not exceeding 180 mm and comprising a combination of between 4 and 8 glass or methacrylic lenses with a diameter of 120 mm or more but not exceeding 180 mm, each lens coated on at least one side with a magnesium fluoride layer, for use in the manufacture of video projectors (*)	0
ex 9002 11 00	50	Lens unit, having a focal length of 75 mm or more but not exceeding 94 mm, consisting of glass or plastic lenses, with a diameter of 60 mm or more but not exceeding 180 mm	0
ex 9002 11 00	60	Optical element, comprising one or more mounted lenses of plastic, for use in the manufacture of products falling within subheading 9006 40 00 (*)	0
ex 9002 19 00	10	Lens unit, having a focal length of 24,96 mm ( $\pm 0,1$ mm), a diameter of 16 mm and a length of 16 mm, for use in the manufacture of products falling within subheading 8517 21 00 (*)	0
ex 9002 20 00	10	Filter, consisting of a plastic polarising membrane, a glass plate and a transparent protective film, mounted on a metal	

▼ **M5**

CN code	TARIC	Description	Rate of autonomous duty (%)
		frame, for use in the manufacture of products falling within heading 8528 (°)	0
ex 9002 90 90	10	Optical element comprising an octagonal Fresnel lens, for use in the manufacture of overhead projectors (°)	0
ex 9002 90 90	20	Lens, mounted, having a fixed focal length of 3,8 mm ( $\pm 0,19$ mm) or 8 mm ( $\pm 0,4$ mm), with a relative aperture of F2.0 and a diameter not exceeding 33 mm, for use in the manufacture of charged-coupled (CCD) cameras (°)	0
ex 9002 90 90	30	Optical unit, comprising 1 or 2 rows of optical glass fibres in the form of lenses and with a diameter of 0,85 mm or more but not exceeding 1,15 mm, embedded between 2 plastic plates	0
ex 9002 90 90	50	Lens and image gate assembly, for a real-time film scanning system, comprising a lens consisting of 9 or 11 elements and having an illumination function	0
ex 9006 91 90	10	Parts, for use in the manufacture of products falling within subheading 9006 40 00 (°)	0
ex 9013 80 20	10	Monochrome liquid crystal display (LCD) with an active matrix, having a diagonal measurement of the screen not exceeding 3,4 cm, consisting of a layer of liquid crystals between two glass sheets or plates	0
ex 9013 80 30	10	Liquid crystal colour device, other than with an active matrix, having crystals encapsulated in polymer droplets, consisting of 4 plastic layers one of which having the function of an interactive switch panel	0
ex 9013 80 90	10	Polarisation insensitive fibre-optic isolator, operating at a wavelength of 1 200 nm or more, contained in a cylindrical housing	0
ex 9017 90 90	20	Thermal printer head, comprising at least 7 168 heater elements mounted on 2 or more ceramic supports, the whole contained in a housing the exterior dimensions of which exceed 21 × 39 × 639 mm	0
<b>▼ M6</b>			
ex 9022 30 00	10	X-ray tube with a target voltage of 4 kV or more but not exceeding 30 kV, a power not exceeding 9 W and a target current not exceeding 2 mA	0
ex 9026 20 30	10	Pressure measurement device for automotive applications, comprising active and passive elements mounted on a printed circuit and a sensor, the whole contained in a housing	0
ex 9026 90 90	10	Ceramic pressure sensitive module, containing passive components and a printed circuit, for use in the manufacture of pressure measurement devices for automobiles (°)	0
<b>▼ M5</b>			
ex 9027 30 00	10	Machines and apparatus providing automated quality inspection of rigid magnetic disks, for use in the manufacture of products falling within subheading 8523 20 11 or 8523 20 19 (°)	0
ex 9031 80 34	10		
ex 9031 80 39	30		
ex 9031 80 99	10		
ex 9031 80 39	10	Acceleration measurement device for automotive applications, comprising one or more active and/or passive elements and a sensor, the whole contained in a housing	0
<b>▼ M6</b>			
<b>▼ M5</b>			
ex 9031 90 80	20	Read and write test head for checking the quality of rigid magnetic disks, mounted on a carrier arm	0
ex 9031 90 80	30	Assembly for a laser align sensor, in the form of a printed circuit comprising optical filters and a charge-coupled image (CCD) sensor, the whole contained in a housing	0
ex 9031 90 80	40	Test head for checking the mechanical quality of rigid magnetic disks, mounted on a carrier arm	0

▼ **M5**

CN code	TARIC	Description	Rate of autonomous duty (%)
ex 9031 90 80	50	Burnishing head, for removing asperities on and polishing of the surface of rigid magnetic disks, mounted on a carrier arm	0
ex 9032 10 91	10	Thermostat, comprising a snap-action switch, for direct mounting on an electric motor coil, contained in a hermetically sealed housing	0
ex 9032 89 90	10	Automotive airbag shock-sensor, comprising a contact capable of switching a current of 12 A at a voltage of 30 V, having a typical contact resistance of 80 mohm	0

▼ **M6**

ex 9110 12 00	91	Assembly consisting of a printed circuit on which are mounted one quartz oscillator, at least one watch circuit and, whether or not integrated, at least one capacitor, of a thickness not exceeding 5 mm	0
ex 9110 90 00 ex 9114 90 00	92 91	Assembly consisting of a printed circuit on which is mounted a watch circuit or a watch circuit and a quartz oscillator, of a thickness not exceeding 5 mm	0
ex 9110 90 00	93	Assembly consisting of a printed circuit on which is mounted at least one watch circuit, a quartz oscillator and a piezo-electric sound element, with a thickness exceeding 5 mm	0

▼ **M5**

ex 9608 91 00	10	Non-fibrous plastic pen-tips with an internal channel	0
ex 9608 91 00	20	Felt tips and other porous-tips for markers, without internal canal	0
ex 9613 90 00	20	Piezo-electric ignition mechanism	0

(<sup>a</sup>) Use for this special purpose shall be carried out pursuant to the relevant Community provisions.

(<sup>b</sup>) However, the suspension is not allowed where processing is carried out by retail or catering undertakings.