

This text is meant purely as a documentation tool and has no legal effect. The Union's institutions do not assume any liability for its contents. The authentic versions of the relevant acts, including their preambles, are those published in the Official Journal of the European Union and available in EUR-Lex. Those official texts are directly accessible through the links embedded in this document

► **B****COMMISSION REGULATION (EU) No 10/2011****of 14 January 2011****on plastic materials and articles intended to come into contact with food****(Text with EEA relevance)****(OJ L 12, 15.1.2011, p. 1)**Amended by:

		Official Journal		
		No	page	date
► <u>M1</u>	Commission Implementing Regulation (EU) No 321/2011 of 1 April 2011	L 87	1	2.4.2011
► <u>M2</u>	Commission Regulation (EU) No 1282/2011 of 28 November 2011	L 328	22	10.12.2011
► <u>M3</u>	Commission Regulation (EU) No 1183/2012 of 30 November 2012	L 338	11	12.12.2012
► <u>M4</u>	Commission Regulation (EU) No 202/2014 of 3 March 2014	L 62	13	4.3.2014
► <u>M5</u>	Commission Regulation (EU) No 865/2014 of 8 August 2014	L 238	1	9.8.2014
► <u>M6</u>	Commission Regulation (EU) 2015/174 of 5 February 2015	L 30	2	6.2.2015
► <u>M7</u>	Commission Regulation (EU) 2016/1416 of 24 August 2016	L 230	22	25.8.2016
► <u>M8</u>	Commission Regulation (EU) 2017/752 of 28 April 2017	L 113	18	29.4.2017
► <u>M9</u>	Commission Regulation (EU) 2018/79 of 18 January 2018	L 14	31	19.1.2018
► <u>M10</u>	Commission Regulation (EU) 2018/213 of 12 February 2018	L 41	6	14.2.2018
► <u>M11</u>	Commission Regulation (EU) 2018/831 of 5 June 2018	L 140	35	6.6.2018
► <u>M12</u>	Commission Regulation (EU) 2019/37 of 10 January 2019	L 9	88	11.1.2019

Corrected by:► **C1** Corrigendum, OJ L 349, 19.12.2012, p. 77 (1183/2012)

**COMMISSION REGULATION (EU) No 10/2011****of 14 January 2011****on plastic materials and articles intended to come into contact with food****(Text with EEA relevance)**

CHAPTER I

GENERAL PROVISIONS*Article 1***Subject matter**

1. This Regulation is a specific measure within the meaning of Article 5 of Regulation (EC) No 1935/2004.
2. This Regulation establishes specific requirements for the manufacture and marketing of plastic materials and articles:
 - (a) intended to come into contact with food; or
 - (b) already in contact with food; or
 - (c) which can reasonably be expected to come into contact with food.

*Article 2***Scope**

1. This Regulation shall apply to materials and articles which are placed on the EU market and fall under the following categories:
 - (a) materials and articles and parts thereof consisting exclusively of plastics;
 - (b) plastic multi-layer materials and articles held together by adhesives or by other means;
 - (c) materials and articles referred to in points a) or b) that are printed and/or covered by a coating;
 - (d) plastic layers or plastic coatings, forming gaskets in caps and closures, that together with those caps and closures compose a set of two or more layers of different types of materials;
 - (e) plastic layers in multi-material multi-layer materials and articles.
2. This Regulation shall not apply to the following materials and articles which are placed on the EU market and are intended to be covered by other specific measures:
 - (a) ion exchange resins;
 - (b) rubber;
 - (c) silicones.

▼B

3. This Regulation shall be without prejudice to the EU or national provisions applicable to printing inks, adhesives or coatings.

*Article 3***Definitions**

For the purpose of this Regulation, the following definitions shall apply:

- (1) 'plastic materials and articles' means:
 - (a) materials and articles referred to in points (a), (b) and (c) of Article 2(1); and
 - (b) plastic layers referred to in Article 2(1)(d) and (e);
- (2) 'plastic' means polymer to which additives or other substances may have been added, which is capable of functioning as a main structural component of final materials and articles;
- (3) 'polymer' means any macromolecular substance obtained by:
 - (a) a polymerisation process such as polyaddition or polycondensation, or by any other similar process of monomers and other starting substances; or
 - (b) chemical modification of natural or synthetic macromolecules; or
 - (c) microbial fermentation;
- (4) 'plastic multi-layer' means a material or article composed of two or more layers of plastic;
- (5) 'multi-material multi-layer' means a material or article composed of two or more layers of different types of materials, at least one of them a plastic layer;
- (6) 'monomer or other starting substance' means:
 - (a) a substance undergoing any type of polymerisation process to manufacture polymers; or
 - (b) a natural or synthetic macromolecular substance used in the manufacture of modified macromolecules; or
 - (c) a substance used to modify existing natural or synthetic macromolecules;
- (7) 'additive' means a substance which is intentionally added to plastics to achieve a physical or chemical effect during processing of the plastic or in the final material or article; it is intended to be present in the final material or article;

▼B

- (8) ‘polymer production aid’ means any substance used to provide a suitable medium for polymer or plastic manufacturing; it may be present but is neither intended to be present in the final materials or articles nor has a physical or chemical effect in the final material or article;
- (9) ‘non-intentionally added substance’ means an impurity in the substances used or a reaction intermediate formed during the production process or a decomposition or reaction product;
- (10) ‘aid to polymerisation’ means a substance which initiates polymerisation and/or controls the formation of the macromolecular structure;
- (11) ‘overall migration limit’ (OML) means the maximum permitted amount of non-volatile substances released from a material or article into food simulants;
- (12) ‘food simulant’ means a test medium imitating food; in its behaviour the food simulant mimics migration from food contact materials;
- (13) ‘specific migration limit’ (SML) means the maximum permitted amount of a given substance released from a material or article into food or food simulants;
- (14) ‘total specific migration limit’ (SML(T)) means the maximum permitted sum of particular substances released in food or food simulants expressed as total of moiety of the substances indicated;
- (15) ‘functional barrier’ means a barrier consisting of one or more layers of any type of material which ensures that the final material or article complies with Article 3 of Regulation (EC) No 1935/2004 and with the provisions of this Regulation;

▼M7

- (16) ‘non-fatty food’ means a food for which in migration testing only food simulants other than food simulants D1 or D2 are laid down in Table 2 of Annex III to this Regulation;

▼B

- (17) ‘restriction’ means limitation of use of a substance or migration limit or limit of content of the substance in the material or article;

▼M7

- (18) ‘specification’ means composition of a substance, purity criteria for a substance, physico-chemical characteristics of a substance, details concerning the manufacturing process of a substance or further information concerning the expression of migration limits;

▼M7

- (19) ‘hot-fill’ means the filling of any article with a food with a temperature not exceeding 100 °C at the moment of filling, after which the food cools down to 50 °C or below within 60 minutes, or to 30 °C or below within 150 minutes.

▼B*Article 4***Placing on the market of plastic materials and articles**

Plastic materials and articles may only be placed on the market if they:

- (a) comply with the relevant requirements set out in Article 3 of Regulation (EC) No 1935/2004 under intended and foreseeable use; and
- (b) comply with the labelling requirements set out in Article 15 of Regulation (EC) No 1935/2004; and
- (c) comply with the traceability requirements set out in Article 17 of Regulation (EC) No 1935/2004; and
- (d) are manufactured according to good manufacturing practice as set out in Commission Regulation (EC) No 2023/2006 ⁽¹⁾; and
- (e) comply with the compositional and declaration requirements set out in Chapters II, III and IV of this Regulation.

CHAPTER II

COMPOSITIONAL REQUIREMENTS

SECTION 1

*Authorised substances**Article 5***Union list of authorised substances**

1. Only the substances included in the Union list of authorised substances (hereinafter referred to as the Union list) set out in Annex I may be intentionally used in the manufacture of plastic layers in plastic materials and articles.
2. The Union list shall contain:
 - (a) monomers or other starting substances;
 - (b) additives excluding colorants;
 - (c) polymer production aids excluding solvents;
 - (d) macromolecules obtained from microbial fermentation.

⁽¹⁾ OJ L 384, 29.12.2006, p. 75.

▼B

3. The Union list may be amended in accordance with the procedure established by Articles 8 to 12 of Regulation (EC) No 1935/2004.

*Article 6***Derogations for substances not included in the Union list**

1. By way of derogation from Article 5, substances other than those included in the Union list may be used as polymer production aids in the manufacture of plastic layers in plastic materials and articles subject to national law.

2. By way of derogation from Article 5, colorants and solvents may be used in the manufacture of plastic layers in plastic materials and articles subject to national law.

3. The following substances not included in the Union list are authorised subject to the rules set out in Articles 8, 9, 10, 11 and 12:

▼M7

(a) all salts of aluminium, ammonium, barium, calcium, cobalt, copper, iron, lithium, magnesium, manganese, potassium, sodium, and zinc of authorised acids, phenols or alcohols;

▼B

(b) mixtures obtained by mixing authorised substances without a chemical reaction of the components;

(c) when used as additives, natural or synthetic polymeric substances of a molecular weight of at least 1 000 Da, except macromolecules obtained from microbial fermentation, complying with the requirements of this Regulation, if they are capable of functioning as the main structural component of final materials or articles;

(d) when used as monomer or other starting substance, pre-polymers and natural or synthetic macromolecular substances, as well as their mixtures, except macromolecules obtained from microbial fermentation, if the monomers or starting substances required to synthesise them are included in the Union list.

4. The following substances not included in the Union list may be present in the plastic layers of plastic materials or articles:

(a) non-intentionally added substances;

(b) aids to polymerisation.

5. By derogation from Article 5, additives not included in the Union list may continue to be used subject to national law after 1 January 2010 until a decision is taken to include or not to include them in the Union list provided they are included in the provisional list referred to in Article 7.

▼B*Article 7***Establishment and management of the provisional list**

1. The provisional list of additives that are under evaluation by the European Food Safety Authority (hereinafter referred to as the Authority) that was made public by the Commission in 2008 shall be regularly updated.
2. An additive shall be removed from the provisional list:
 - (a) when it is included in the Union list set out in Annex I; or
 - (b) when a decision is taken by the Commission not to include it in the Union list; or
 - (c) if during the examination of the data, the Authority calls for supplementary information and that information is not submitted within the time limits specified by the Authority.

*SECTION 2****General requirements, restrictions and specifications****Article 8***General requirement on substances**

Substances used in the manufacture of plastic layers in plastic materials and articles shall be of a technical quality and a purity suitable for the intended and foreseeable use of the materials or articles. The composition shall be known to the manufacturer of the substance and made available to the competent authorities on request.

*Article 9***Specific requirements on substances**

1. Substances used in the manufacture of plastic layers in plastic materials and articles shall be subject to the following restrictions and specifications:
 - (a) the specific migration limit set out in Article 11;
 - (b) the overall migration limit set out in Article 12;
 - (c) the restrictions and specifications set out in column 10 of Table 1 of point 1 of Annex I;
 - (d) the detailed specifications set out in point 4 of Annex I.
2. Substances in nanoform shall only be used if explicitly authorised and mentioned in the specifications in Annex I.

▼B*Article 10***General restrictions on plastic materials and articles**

General restrictions related to plastic materials and articles are laid down in Annex II.

*Article 11***Specific migration limits**

1. Plastic materials and articles shall not transfer their constituents to foods in quantities exceeding the specific migration limits (SML) set out in Annex I. Those specific migration limits (SML) are expressed in mg of substance per kg of food (mg/kg).

▼M7

3. By derogation from paragraph 1, additives which are also authorised as food additives by Regulation (EC) No 1333/2008 or as flavourings by Regulation (EC) No 1334/2008 shall not migrate into foods in quantities having a technical effect in the final foods and shall not:

- (a) exceed the restrictions provided for in Regulation (EC) No 1333/2008 or in Regulation (EC) No 1334/2008 or in Annex I to this Regulation for foods for which their use is authorised as food additive or flavouring substances; or
- (b) exceed the restrictions set out in Annex I to this Regulation in foods for which their use is not authorised as food additive or flavouring substances.

4. Where it is specified that no migration of a particular substance is permitted, compliance shall be established using appropriate migration test methods selected in accordance with Article 11 of Regulation (EC) No 882/2004 that can confirm the absence of migration above a specified limit of detection.

For the purposes of the first subparagraph, unless specific detection limits have been set for particular substances or groups of substances, a detection limit of 0,01 mg/kg shall apply.

▼B*Article 12***Overall migration limit**

1. Plastic materials and articles shall not transfer their constituents to food simulants in quantities exceeding 10 milligrams of total constituents released per dm² of food contact surface (mg/dm²).

▼B

2. By derogation from paragraph 1, plastic materials and articles intended to be brought into contact with food intended for infants and young children, as defined by Commission Directives 2006/141/EC ⁽¹⁾ and 2006/125/EC ⁽²⁾, shall not transfer their constituents to food simulants in quantities exceeding 60 milligrams of total of constituents released per kg of food simulant.

CHAPTER III

SPECIFIC PROVISIONS FOR CERTAIN MATERIALS AND ARTICLES

*Article 13***Plastic multi-layer materials and articles**

1. In a plastic multi-layer material or article, the composition of each plastic layer shall comply with this Regulation.

2. By derogation from paragraph 1, a plastic layer which is not in direct contact with food and is separated from the food by a functional barrier, may:

- (a) not comply with the restrictions and specifications set out in this Regulation except for vinyl chloride monomer as provided in Annex I; and/or
- (b) be manufactured with substances not listed in the Union list or in the provisional list.

▼M7

3. Substances under paragraph 2(b) shall not migrate into food or food simulant, in accordance with Article 11(4). The detection limit set out in the second subparagraph of Article 11(4) shall apply to groups of substances if they are structurally and toxicologically related, including isomers or substances with the same relevant functional group, or to individual substances that are not related, and shall include possible set-off transfer.

▼B

4. The substances not listed in the Union list or provisional list referred to in paragraph 2(b) shall not belong to either of the following categories:

- (a) substances classified as ‘mutagenic’, ‘carcinogenic’ or ‘toxic to reproduction’ in accordance with the criteria set out in sections 3.5, 3.6. and 3.7 of Annex I to Regulation (EC) No 1272/2008 of the European Parliament and the Council ⁽³⁾;
- (b) substances in nanoform.

⁽¹⁾ OJ L 401, 30.12.2006, p. 1.

⁽²⁾ OJ L 339, 6.12.2006, p. 16.

⁽³⁾ OJ L 353, 31.12.2008, p. 1.

▼B

5. The final plastic multi-layer material or article shall comply with the specific migration limits set out in Article 11 and the overall migration limit set out in Article 12 of this Regulation.

*Article 14***Multi-material multi-layer materials and articles**

1. In a multi-material multi-layer material or article, the composition of each plastic layer shall comply with this Regulation.

2. By derogation from paragraph 1, in a multi-material multi-layer material or article a plastic layer which is not in direct contact with food and is separated from the food by a functional barrier, may be manufactured with substances not listed in the Union list or the provisional list.

3. The substances not listed in the Union list or provisional list referred to in paragraph 2 shall not belong to either of the following categories:

(a) substances classified as ‘mutagenic’, ‘carcinogenic’ or ‘toxic to reproduction’ in accordance with the criteria set out in sections 3.5, 3.6. and 3.7 of Annex I to Regulation (EC) No 1272/2008;

(b) substances in nanoform.

4. By derogation from paragraph 1, Articles 11 and 12 of this Regulation do not apply to plastic layers in multi-material multi-layer materials and articles.

5. The plastic layers in a multi-material multi-layer material or article shall always comply with the restrictions for vinyl chloride monomer laid down in Annex I to this Regulation.

6. In a multi-material multi-layer material or article, specific and overall migration limits for plastic layers and for the final material or article may be established by national law.

CHAPTER IV

DECLARATION OF COMPLIANCE AND DOCUMENTATION*Article 15***Declaration of compliance**

1. At the marketing stages other than at the retail stage, a written declaration in accordance with Article 16 of Regulation (EC) No 1935/2004 shall be available for plastic materials and articles, products from intermediate stages of their manufacturing as well as for the substances intended for the manufacturing of those materials and articles.

▼B

2. The written declaration referred to in paragraph 1 shall be issued by the business operator and shall contain the information laid down in Annex IV.

3. The written declaration shall permit an easy identification of the materials, articles or products from intermediate stages of manufacture or substances for which it is issued. It shall be renewed when substantial changes in the composition or production occur that bring about changes in the migration from the materials or articles or when new scientific data becomes available.

*Article 16***Supporting documents**

1. Appropriate documentation to demonstrate that the materials and articles, products from intermediate stages of their manufacturing as well as the substances intended for the manufacturing of those materials and articles comply with the requirements of this Regulation shall be made available by the business operator to the national competent authorities on request.

2. That documentation shall contain the conditions and results of testing, calculations, including modelling, other analysis, and evidence on the safety or reasoning demonstrating compliance. Rules for experimental demonstration of compliance are set out in Chapter V.

CHAPTER V

COMPLIANCE*Article 17***Expression of migration test results**

1. To check the compliance, the specific migration values shall be expressed in mg/kg applying the real surface to volume ratio in actual or foreseen use.

2. By derogation from paragraph 1 for:

(a) containers and other articles, containing or intended to contain, less than 500 millilitres or grams or more than 10 litres,

(b) materials and articles for which, due to their form it is impracticable to estimate the relationship between the surface area of such materials or articles and the quantity of food in contact therewith,

(c) sheets and films that are not yet in contact with food,

(d) sheets and films containing less than 500 millilitres or grams or more than 10 litres,

▼B

the value of migration shall be expressed in mg/kg applying a surface to volume ratio of 6 dm² per kg of food.

This paragraph does not apply to plastic materials and articles intended to be brought into contact with or already in contact with food for infants and young children, as defined by Directives 2006/141/EC and 2006/125/EC.

3. By derogation from paragraph 1, for caps, gaskets, stoppers and similar sealing articles the specific migration value shall be expressed in:

▼M7

(a) mg/kg using the actual content of the container for which the closure is intended applying the total contact surface of sealing article and sealed container if the intended use of the article is known, while taking into account the provisions of paragraph 2;

▼B

(b) mg/article if the intended use of the article is unknown.

4. For caps, gaskets, stoppers and similar sealing articles the overall migration value shall be expressed in:

(a) mg/dm² applying the total contact surface of sealing article and sealed container if the intended use of the article is known;

(b) mg/article if the intended use of the article is unknown.

*Article 18***Rules for assessing compliance with migration limits**

1. For materials and articles already in contact with food verification of compliance with specific migration limits shall be carried out in accordance with the rules set out in Chapter 1 of Annex V.

2. For materials and articles not yet in contact with food verification of compliance with specific migration limits shall be carried out in food or in food simulants set out in Annex III in accordance with the rules set out in Chapter 2, Section 2.1 of Annex V.

3. For materials and articles not yet in contact with food screening of compliance with the specific migration limit can be performed applying screening approaches in accordance with the rules set out in Chapter 2, Section 2.2 of Annex V. If a material or article fails to comply with the migration limits in the screening approach a conclusion of non-compliance has to be confirmed by verification of compliance in accordance with paragraph 2.

▼M7

4. For materials and articles not yet in contact with food verification of compliance with the overall migration limit shall be carried out in food simulants as set out in Annex III in accordance with the rules set out in Chapter 3 of Annex V.

▼B

5. For materials and articles not yet in contact with food screening of compliance with the overall migration limit can be performed applying screening approaches in accordance with the rules set out in Chapter 3, Section 3.4 of Annex V. If a material or article fails to comply with the migration limit in the screening approach a conclusion of non-compliance has to be confirmed by verification of compliance in accordance with paragraph 4.

6. The results of specific migration testing obtained in food shall prevail over the results obtained in food simulant. The results of specific migration testing obtained in food simulant shall prevail over the results obtained by screening approaches.

▼M7

7. Before comparing specific and overall migration test results with the migration limits the correction factors set out in point 3 of Annex III and Chapter 4 of Annex V shall be applied in accordance with the rules set out therein.

▼B*Article 19***Assessment of substances not included in the Union list**

Compliance with Article 3 of Regulation (EC) No 1935/2004 of substances referred to in Articles 6(1), 6(2), 6(4), 6(5) and 14(2) of this Regulation which are not covered by an inclusion in Annex I to this Regulation shall be assessed in accordance with internationally recognised scientific principles on risk assessment.

CHAPTER VI

FINAL PROVISIONS*Article 20***Amendments of EU acts**

The Annex to Council Directive 85/572/EEC ⁽¹⁾ is replaced by the following:

‘The food simulants to be used for testing migration of constituents of plastic materials and articles intended to come into contact with a single food or specific groups of foods are set out in point 3 of Annex III to Commission Regulation (EU) No 10/2011.’

⁽¹⁾ OJ L 372, 31.12.1985, p. 14.



Article 21

Repeal of EU acts

Directives 80/766/EEC, 81/432/EEC, and 2002/72/EC are hereby repealed with effect from 1 May 2011.

References to the repealed Directives shall be construed as references to this Regulation and shall be read in accordance with the correlation tables in Annex VI.

Article 22

Transitional provisions

1. Until 31 December 2012 the supporting documents referred to in Article 16 shall be based on the basic rules for overall and specific migration testing set out in the Annex to Directive 82/711/EEC.

2. As from 1 January 2013 the supporting documents referred to in Article 16 for materials, articles and substances placed on the market until 31 December 2015, may be based on:

- (a) the rules for migration testing set out in Article 18 of this Regulation; or
- (b) the basic rules for overall and specific migration testing set out in the Annex to Directive 82/711/EEC.

3. As from 1 January 2016, the supporting documents referred to in Article 16 shall be based on the rules for migration testing set out in Article 18, without prejudice to paragraph 2 of this Article.

4. Until 31 December 2015 additives used in glass fibre sizing for glass fibre reinforced plastics which are not listed in Annex I have to comply with the risk assessment provisions set out in Article 19.

5. Materials and articles that have been lawfully placed on the market before 1 May 2011 may be placed on the market until 31 December 2012.

Article 23

Entry into force and application

This Regulation shall enter into force on the 20th day following its publication in the *Official Journal of the European Union*.

It shall apply from 1 May 2011.

The provision of Article 5 as regards the use of additives, others than plasticisers, shall apply for plastic layers or plastic coatings in caps and closures referred to in Article 2(1)(d), as from 31 December 2015.

▼B

The provision of Article 5 as regards the use of additives used in glass fibre sizing for glass fibre reinforced plastics, shall apply from 31 December 2015.

The provisions of Articles 18(2), 18(4) and 20 shall apply from 31 December 2012.

This Regulation shall be binding in its entirety and directly applicable in the Member States in accordance with the Treaties.

▼B*ANNEX I***Substances****1. Union list of authorised monomers, other starting substances, macromolecules obtained from microbial fermentation, additives and polymer production aids**

Table 1 contains the following information:

Column 1 (FCM substance No): the unique identification number of the substance

Column 2 (Ref. No): the EEC packaging material reference number

Column 3 (CAS No): the Chemical Abstracts Service (CAS) registry number

Column 4 (Substance Name): the chemical name

Column 5 (Use as additive or polymer production aid (PPA) (yes/no)): an indication if the substance is authorised to be used as additive or polymer production aid (yes) or if the substance is not authorised to be used as additive or polymer production aid (no). If the substance is only authorised as PPA it is indicated (yes) and in the specifications the use is restricted to PPA.

Column 6 (Use as monomer or other starting substance or macromolecule obtained from microbial fermentation (yes/no)): an indication if the substance is authorised to be used as monomer or other starting substance or macromolecule obtained from microbial fermentation (yes) or if the substance is not authorised to be used as monomer or other starting substance or macromolecule obtained from microbial fermentation (no). If the substance is authorised as macromolecule obtained from microbial fermentation it is indicated (yes) and in the specifications it is indicated that the substance is a macromolecule obtained from microbial fermentation.

Column 7 (FRF applicable (yes/no)): an indication if for the substance the migration results can be corrected by the Fat Consumption Reduction Factor (FRF) (yes) or if they cannot be corrected by the FRF (no).

▼M7

Column 8 (SML [mg/kg]): the specific migration limit applicable for the substance. It is expressed in mg substance per kg food. It is marked as ND ('not-detectable') if the substance is one in respect of which no migration is permitted, to be determined in accordance with Article 11(4).

▼B

Column 9 (SML(T) [mg/kg] (group restriction No)): contains the identification number of the group of substances for which the group restriction in Column 1 in Table 2 of this Annex applies.

Column 10 (Restrictions and specifications): contains other restrictions than the specific migration limit specifically mentioned and it contains specifications related to the substance. In case detailed specifications are set out a reference to Table 4 is included.

Column 11 (Notes on verification of compliance): contains the Notes number which refers to the detailed rules applicable for verification of compliance for this substance included in Column 1 in Table 3 of this Annex.

If a substance appearing on the list as an individual compound is also covered by a generic term, the restrictions applying to this substance shall be those indicated for the individual compound.

▼M7

Table 1

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
FCM substance No	Ref. No	CAS No	Substance name	Use as additive or polymer production aid (yes/no)	Use as monomer or other starting substance or macromolecule obtained from microbial fermentation (yes/no)	FRF applicable (yes/no)	SML [mg/kg]	SML(T) [mg/kg] (Group restriction No)	Restrictions and specifications	Notes on verification of compliance
1	12310	0266309-43-7	albumin	no	yes	no				
2	12340	—	albumin, coagulated by formaldehyde	no	yes	no				
3	12375	—	alcohols, aliphatic, monohydric, saturated, linear, primary (C ₄ -C ₂₂)	no	yes	no				
4	22332	—	mixture of (40 % w/w) 2,2,4-trimethylhexane-1,6-diisocyanate and (60 % w/w) 2,4,4-trimethylhexane-1,6-diisocyanate	no	yes	no		(17)	1 mg/kg in final product expressed as isocyanate moiety.	(10)
5	25360	—	trialkyl(C ₅ -C ₁₅)acetic acid, 2,3-epoxypropyl ester	no	yes	no	ND		1 mg/kg in final product expressed as epoxygroup. Molecular weight is 43 Da.	
6	25380	—	trialkyl acetic acid (C ₇ -C ₁₇), vinyl esters	no	yes	no	0,05			(1)
7	30370	—	acetylacetic acid, salts	yes	no	no				
8	30401	—	acetylated mono- and diglycerides of fatty acids	yes	no	no		(32)		

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
9	30610	—	acids, C ₂ -C ₂₄ , aliphatic, linear, monocarboxylic from natural oils and fats, and their mono-, di- and triglycerol esters (branched fatty acids at naturally occurring levels are included)	yes	no	no				
10	30612	—	acids, C ₂ -C ₂₄ , aliphatic, linear, monocarboxylic, synthetic and their mono-, di- and triglycerol esters	yes	no	no				
11	30960	—	acids, aliphatic, monocarboxylic (C ₆ -C ₂₂), esters with polyglycerol	yes	no	no				
12	31328	—	acids, fatty, from animal or vegetable food fats and oils	yes	no	no				
13	33120	—	alcohols, aliphatic, monohydric, saturated, linear, primary (C ₄ -C ₂₄)	yes	no	no				
14	33801	—	n-alkyl(C ₁₀ -C ₁₃)benzenesulphonic acid	yes	no	no	30			
15	34130	—	alkyl, linear with even number of carbon atoms (C ₁₂ -C ₂₀) dimethylamines	yes	no	yes	30			
16	34230	—	alkyl(C ₈ -C ₂₂)sulphonic acids	yes	no	no	6			
17	34281	—	alkyl(C ₈ -C ₂₂)sulphuric acids, linear, primary with an even number of carbon atoms	yes	no	no				

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
18	34475	—	aluminium calcium hydroxide phosphite, hydrate	yes	no	no				
19	39090	—	N,N-bis(2-hydroxyethyl)alkyl (C ₈ -C ₁₈)amine	yes	no	no		(7)		
20	39120	—	N,N-bis(2-hydroxyethyl)alkyl (C ₈ -C ₁₈)amine hydrochlorides	yes	no	no		(7)	SML(T) expressed excluding HCl	
21	42500	—	carbonic acid, salts	yes	no	no				
22	43200	—	castor oil, mono- and diglycerides	yes	no	no				
23	43515	—	chlorides of choline esters of coconut oil fatty acids	yes	no	no	0,9			(1)
24	45280	—	cotton fibers	yes	no	no				
25	45440	—	cresols, butylated, styrenated	yes	no	no	12			
26	46700	—	5,7-di-tert-butyl-3-(3,4- and 2,3-dimethylphenyl)-3H-benzofuran-2-one containing: a) 5,7-di-tert-butyl-3-(3,4-dimethylphenyl)-3H-benzofuran-2-one (80 to 100 % w/w) and b) 5,7-di-tert-butyl-3-(2,3-dimethylphenyl)-3H-benzofuran-2-one (0 to 20 % w/w)	yes	no	no	5			
27	48960	—	9,10-dihydroxy stearic acid and its oligomers	yes	no	no	5			
28	50160	—	di-n-octyltin bis(n-alkyl(C ₁₀ -C ₁₆)mercaptoacetate)	yes	no	no		(10)		

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
29	50360	—	di-n-octyltin bis(ethyl maleate)	yes	no	no		(10)		
30	50560	—	di-n-octyltin 1,4-butanediol bis(mercaptoacetate)	yes	no	no		(10)		
31	50800	—	di-n-octyltin dimaleate, esterified	yes	no	no		(10)		
32	50880	—	di-n-octyltin dimaleate, polymers (n = 2-4)	yes	no	no		(10)		
33	51120	—	di-n-octyltin thiobenzoate 2-ethylhexyl mercaptoacetate	yes	no	no		(10)		
34	54270	—	ethylhydroxymethylcellulose	yes	no	no				
35	54280	—	ethylhydroxypropylcellulose	yes	no	no				
36	54450	—	fats and oils, from animal or vegetable food sources	yes	no	no				
37	54480	—	fats and oils, hydrogenated, from animal or vegetable food sources	yes	no	no				
38	55520	—	glass fibers	yes	no	no				
39	55600	—	glass microballs	yes	no	no				
40	56360	—	glycerol, esters with acetic acid	yes	no	no				

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
41	56486	—	glycerol, esters with acids, aliphatic, saturated, linear, with an even number of carbon atoms (C ₁₄ -C ₁₈) and with acids, aliphatic, unsaturated, linear, with an even number of carbon atoms (C ₁₆ -C ₁₈)	yes	no	no				
42	56487	—	glycerol, esters with butyric acid	yes	no	no				
43	56490	—	glycerol, esters with erucic acid	yes	no	no				
44	56495	—	glycerol, esters with 12-hydroxystearic acid	yes	no	no				
45	56500	—	glycerol, esters with lauric acid	yes	no	no				
46	56510	—	glycerol, esters with linoleic acid	yes	no	no				
47	56520	—	glycerol, esters with myristic acid	yes	no	no				
48	56535	—	glycerol, esters with nonanoic acid	yes	no	no				
49	56540	—	glycerol, esters with oleic acid	yes	no	no				
50	56550	—	glycerol, esters with palmitic acid	yes	no	no				

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
51	56570	—	glycerol, esters with propionic acid	yes	no	no				
52	56580	—	glycerol, esters with ricinoleic acid	yes	no	no				
53	56585	—	glycerol, esters with stearic acid	yes	no	no				
54	57040	—	glycerol monooleate, ester with ascorbic acid	yes	no	no				
55	57120	—	glycerol monooleate, ester with citric acid	yes	no	no				
56	57200	—	glycerol monopalmitate, ester with ascorbic acid	yes	no	no				
57	57280	—	glycerol monopalmitate, ester with citric acid	yes	no	no				
58	57600	—	glycerol monostearate, ester with ascorbic acid	yes	no	no				
59	57680	—	glycerol monostearate, ester with citric acid	yes	no	no				
60	58300	—	glycine, salts	yes	no	no				
62	64500	—	lysine, salts	yes	no	no				
63	65440	—	manganese pyrophosphite	yes	no	no				
64	66695	—	methylhydroxymethylcellulose	yes	no	no				

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
65	67155	—	mixture of 4-(2-benzoxazolyl)-4'-(5-methyl-2-benzoxazolyl)stilbene, 4,4'-bis(2-benzoxazolyl) stilbene and 4,4'-bis(5-methyl-2-benzoxazolyl)stilbene	yes	no	no			Not more than 0,05 % (w/w) (quantity of substance used/ quantity of the formulation). Mixture obtained from the manufacturing process in the typical ratio of (58-62 %):(23-27 %):(13-17 %).	
66	67600	—	mono-n-octyltin tris(alkyl (C ₁₀ -C ₁₆) mercaptoacetate)	yes	no	no		(11)		
67	67840	—	montanic acids and/or their esters with ethyleneglycol and/or with 1,3-butanediol and/or with glycerol	yes	no	no				
68	73160	—	phosphoric acid, mono- and di-n-alkyl (C ₁₆ and C ₁₈) esters	yes	no	yes	0,05			
69	74400	—	phosphorous acid, tris(nonyl-and/ or dinonylphenyl) ester	yes	no	yes	30			
70	76463	—	polyacrylic acid, salts	yes	no	no		(22)		
71	76730	—	polydimethylsiloxane, γ -hydroxy-propylated	yes	no	no	6			
72	76815	—	polyester of adipic acid with glycerol or pentaerythritol, esters with even numbered, unbranched C ₁₂ -C ₂₂ fatty acids	yes	no	no		(32)	The fraction with molecular weight below 1 000 Da ► M7 shall ◀ not exceed 5 % (w/w)	

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
73	76866	—	polyesters of 1,2-propanediol and/or 1,3- and/or 1,4-butanediol and/or polypropyleneglycol with adipic acid, which may be end-capped with acetic acid or fatty acids C ₁₂ -C ₁₈ or n-octanol and/or n-decanol	yes	no	yes		(31) (32)		
74	77440	—	polyethyleneglycol diricinoleate	yes	no	yes	42			
75	77702	—	polyethyleneglycol esters of aliph. monocarb. acids (C ₆ -C ₂₂) and their ammonium and sodium sulphates	yes	no	no				
76	77732	—	polyethylene glycol (EO = 1-30, typically 5) ether of butyl 2-cyano 3-(4-hydroxy-3-methoxyphenyl) acrylate	yes	no	no	0,05		Only for use in PET	
77	77733	—	polyethyleneglycol (EO = 1-30, typically 5) ether of butyl-2-cyano-3-(4-hydroxyphenyl) acrylate	yes	no	no	0,05		Only for use in PET	
78	77897	—	polyethyleneglycol (EO = 1-50) monoalkylether (linear and branched, C ₈ -C ₂₀) sulphate, salts	yes	no	no	5			
79	80640	—	polyoxyalkyl (C ₂ -C ₄) dimethyl-polysiloxane	yes	no	no				

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
80	81760	—	powders, flakes and fibres of brass, bronze, copper, stainless steel, tin, iron and alloys of copper, tin and iron	yes	no	no				
81	83320	—	propylhydroxyethylcellulose	yes	no	no				
82	83325	—	propylhydroxymethylcellulose	yes	no	no				
83	83330	—	propylhydroxypropylcellulose	yes	no	no				
84	85601	—	silicates, natural (with the exception of asbestos)	yes	no	no				
85	85610	—	silicates, natural, silanated (with the exception of asbestos)	yes	no	no				
86	86000	—	silicic acid, silylated	yes	no	no				
▼ <u>M7</u>										
87	86285		Silicon dioxide, silanated	yes	no	no			For synthetic amorphous silicon dioxide, silanated: primary particles of 1–100 nm which are aggregated to a size of 0,1–1 µm and may form agglomerates within the size distribution of 0,3 µm to the mm size.	
▼ <u>B</u>										
88	86880	—	sodium monoalkyl dialkylphenoxybenzenedisulphonate	yes	no	no	9			
89	89440	—	stearic acid, esters with ethylene-glycol	yes	no	no		(2)		
90	92195	—	taurine, salts	yes	no	no				

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
91	92320	—	tetradecyl-polyethyleneglycol(EO = 3-8) ether of glycolic acid	yes	no	yes	15			
92	93970	—	tricyclodecanedimethanol bis(hexahydrophthalate)	yes	no	no	0,05			
93	95858	—	waxes, paraffinic, refined, derived from petroleum based or synthetic hydrocarbon feedstocks, low viscosity	yes	no	no	0,05		Not to be used for articles in contact with fatty foods for which ►M7 simulant D1 and/or D2 ◀ is laid down. Average molecular weight not less than 350 Da. Viscosity at 100 °C not less than 2,5 cSt ($2,5 \times 10^{-6} \text{ m}^2/\text{s}$). Content of hydrocarbons with Carbon number less than 25, not more than 40 % (w/w).	
94	95859	—	waxes, refined, derived from petroleum based or synthetic hydrocarbon feedstocks, high viscosity	yes	no	no			Average molecular weight not less than 500 Da. Viscosity at 100 °C not less than 11 cSt ($11 \times 10^{-6} \text{ m}^2/\text{s}$). Content of mineral hydrocarbons with Carbon number less than 25, not more than 5 % (w/w).	
95	95883	—	white mineral oils, paraffinic, derived from petroleum based hydrocarbon feedstocks	yes	no	no			Average molecular weight not less than 480 Da. Viscosity at 100 °C not less than 8,5 cSt ($8,5 \times 10^{-6} \text{ m}^2/\text{s}$). Content of mineral hydrocarbons with Carbon number less than 25, not more than 5 % (w/w).	
96	95920	—	wood flour and fibers, untreated	yes	no	no				

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
97	72081/10	—	petroleum hydrocarbon resins (hydrogenated)	yes	no	no			<p>Petroleum hydrocarbon resins, hydrogenated are produced by the catalytic or thermalpolymerisation of dienes and olefins of the aliphatic, alicyclic and/or monobenzenoidarylalkene types from distillates of cracked petroleum stocks with a boiling range not greater than 220 °C, as well as the pure monomers found in these distillation streams, subsequently followed by distillation, hydrogenation and additional processing.</p> <p>Properties:</p> <ul style="list-style-type: none"> — Viscosity at 120 °C: > 3 Pa.s, — Softening point: > 95 °C as determined by ASTM Method E 28-67, — Bromine number: < 40 (ASTM D1159), — The colour of a 50 % solution in toluene < 11 on the Gardner scale, — Residual aromatic monomer ≤ 50 ppm, 	
98	17260	0000050-00-0	formaldehyde	yes	yes	no		(15)		
	54880									
99	19460	0000050-21-5	lactic acid	yes	yes	no				
	62960									

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
100	24490	0000050-70-4	sorbitol	yes	yes	no				
	88320									
101	36000	0000050-81-7	ascorbic acid	yes	no	no				
102	17530	0000050-99-7	glucose	no	yes	no				
103	18100	0000056-81-5	glycerol	yes	yes	no				
	55920									
104	58960	0000057-09-0	hexadecyltrimethylammonium bromide	yes	no	no	6			
105	22780	0000057-10-3	palmitic acid	yes	yes	no				
	70400									
106	24550	0000057-11-4	stearic acid	yes	yes	no				
	89040									
107	25960	0000057-13-6	urea	no	yes	no				
108	24880	0000057-50-1	sucrose	no	yes	no				
109	23740	0000057-55-6	1,2-propanediol	yes	yes	no				
	81840									
110	93520	0000059-02-9 0010191-41-0	α -tocopherol	yes	no	no				
111	53600	0000060-00-4	ethylenediaminetetraacetic acid	yes	no	no				
112	64015	0000060-33-3	linoleic acid	yes	no	no				

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
113	16780	0000064-17-5	ethanol	yes	yes	no				
	52800									
114	55040	0000064-18-6	formic acid	yes	no	no				
115	10090	0000064-19-7	acetic acid	yes	yes	no				
	30000									
116	13090	0000065-85-0	benzoic acid	yes	yes	no				
	37600									
117	21550	0000067-56-1	methanol	no	yes	no				
118	23830	0000067-63-0	2-propanol	yes	yes	no				
	81882									
119	30295	0000067-64-1	acetone	yes	no	no				
120	49540	0000067-68-5	dimethyl sulphoxide	yes	no	no				
121	24270	0000069-72-7	salicylic acid	yes	yes	no				
	84640									
122	23800	0000071-23-8	1-propanol	no	yes	no				
123	13840	0000071-36-3	1-butanol	no	yes	no				
124	22870	0000071-41-0	1-pentanol	no	yes	no				
125	16950	0000074-85-1	ethylene	no	yes	no				

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
126	10210	0000074-86-2	acetylene	no	yes	no				
127	26050	0000075-01-4	vinyl chloride	no	yes	no	ND		1 mg/kg in final product	
128	10060	0000075-07-0	acetaldehyde	no	yes	no		(1)		
129	17020	0000075-21-8	ethylene oxide	no	yes	no	ND		1 mg/kg in final product	(10)
130	26110	0000075-35-4	vinylidene chloride	no	yes	no	ND			(1)
131	48460	0000075-37-6	1,1-difluoroethane	yes	no	no				
132	26140	0000075-38-7	vinylidene fluoride	no	yes	no	5			
133	14380	0000075-44-5	carbonyl chloride	no	yes	no	ND		1 mg/kg in final product	(10)
	23155									
134	43680	0000075-45-6	chlorodifluoromethane	yes	no	no	6		Content of chlorofluoromethane less than 1 mg/kg of the substance	
135	24010	0000075-56-9	propylene oxide	no	yes	no	ND		1 mg/kg in final product	
136	41680	0000076-22-2	camphor	yes	no	no				(3)
137	66580	0000077-62-3	2,2'-methylenebis(4-methyl-6-(1-methylcyclohexyl)phenol)	yes	no	yes		(5)		
138	93760	0000077-90-7	tri-n-butyl acetyl citrate	yes	no	no		(32)		
139	14680	0000077-92-9	citric acid	yes	yes	no				
	44160									
140	44640	0000077-93-0	citric acid, triethyl ester	yes	no	no		(32)		

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
141	13380	0000077-99-6	1,1,1-trimethylolpropane	yes	yes	no	6			
	25600									
	94960									
142	26305	0000078-08-0	vinyltriethoxysilane	no	yes	no	0,05		Only to be used as a surface treatment agent	► <u>M8</u> ——— ◀
143	62450	0000078-78-4	isopentane	yes	no	no				
144	19243	0000078-79-5	2-methyl-1,3-butadiene	no	yes	no	ND		1 mg/kg in final product	
	21640									
145	10630	0000079-06-1	acrylamide	no	yes	no	ND			
146	23890	0000079-09-4	propionic acid	yes	yes	no				
	82000									
147	10690	0000079-10-7	acrylic acid	no	yes	no		(22)		
148	14650	0000079-38-9	chlorotrifluoroethylene	no	yes	no	ND			(1)
149	19990	0000079-39-0	methacrylamide	no	yes	no	ND			
150	20020	0000079-41-4	methacrylic acid	no	yes	no		(23)		
▼ <u>M10</u>	13480	0000080-05-7	2,2-bis(4-hydroxyphenyl)propane	no	yes	no	0,05		Not to be used for the manufacture of polycarbonate infant ⁽⁶⁾ feeding bottles ⁽⁷⁾ . Not to be used for the manufacture of polycarbonate drinking cups or bottles which, due to their spill proof characteristics, are intended for infants ⁽⁹⁾ and young children ⁽¹⁰⁾ .	
	13607									
▼ <u>B</u>	152	0000080-07-9	4,4'-dichlorodiphenyl sulphone	no	yes	no	0,05			
	153	0000080-08-0	4,4'-diaminodiphenyl sulphone	no	yes	no	5			

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
154	13617	0000080-09-1	4,4'-dihydroxydiphenyl sulphone	no	yes	no	0,05			
	16090									
155	23470	0000080-56-8	α -pinene	no	yes	no				
156	21130	0000080-62-6	methacrylic acid, methyl ester	no	yes	no		(23)		
157	74880	0000084-74-2	phthalic acid, dibutyl ester	yes	no	no	0,3	(32)	Only to be used as: (a) plasticiser in repeated use materials and articles contacting non-fatty foods; (b) technical support agent in polyolefins in concentrations up to 0,05 % in the final product.	(7)
158	23380	0000085-44-9	phthalic anhydride	yes	yes	no				
	76320									
159	74560	0000085-68-7	phthalic acid, benzyl butyl ester	yes	no	no	30	(32)	Only to be used as: (a) plasticiser in repeated use materials and articles; (b) plasticiser in single-use materials and articles contacting non-fatty foods except for infant formulae and follow-on formulae as defined by Directive 2006/141/EC or processed cereal-based foods and baby foods for infants and young children as defined by Directive 2006/125/EC;	(7)

▼ B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
									(c) technical support agent in concentrations up to 0,1 % in the final product.	

▼ M6

160	84800	0000087-18-3	salicylic acid, 4-tert-butylphenyl ester	yes	no	yes	12			
161	92160	000087-69-4	L-(+)-tartaric acid	yes	no	no				

▼ B

162	65520	0000087-78-5	mannitol	yes	no	no				
163	66400	0000088-24-4	2,2'-methylene bis(4-ethyl-6-tert-butylphenol)	yes	no	yes		(13)		
164	34895	0000088-68-6	2-aminobenzamide	yes	no	no	0,05		Only for use in PET for water and beverages	
165	23200	0000088-99-3	o-phthalic acid	yes	yes	no				
	74480									
166	24057	0000089-32-7	pyromellitic anhydride	no	yes	no	0,05			
167	25240	0000091-08-7	2,6-toluene diisocyanate	no	yes	no		(17)	1 mg/kg in final product expressed as isocyanate moiety	(10)
168	13075	0000091-76-9	2,4-diamino-6-phenyl-1,3,5-triazine	no	yes	no	5			▶ <u>M8</u> ——— ◀
	15310									
169	16240	0000091-97-4	3,3'-dimethyl-4,4'-diisocyanato-biphenyl	no	yes	no		(17)	1 mg/kg in final product expressed as isocyanate moiety	(10)
170	16000	0000092-88-6	4,4'-dihydroxybiphenyl	no	yes	no	6			
171	38080	0000093-58-3	benzoic acid, methyl ester	yes	no	no				
172	37840	0000093-89-0	benzoic acid, ethyl ester	yes	no	no				

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
173	60240	0000094-13-3	4-hydroxybenzoic acid, propyl ester	yes	no	no				
174	14740	0000095-48-7	<i>o</i> -cresol	no	yes	no				
175	20050	0000096-05-9	methacrylic acid, allyl ester	no	yes	no	0,05			
176	11710	0000096-33-3	acrylic acid, methyl ester	no	yes	no		(22)		
177	16955	0000096-49-1	ethylene carbonate	no	yes	no	30		SML expressed as ethyleneglycol. Residual content of 5 mg ethylene carbonate per kg of hydrogel with max 10 g of hydrogel in contact with 1 kg of food.	
178	92800	0000096-69-5	4,4'-thiobis(6-tert-butyl-3-methylphenol)	yes	no	yes	0,48			
179	48800	0000097-23-4	2,2'-dihydroxy--5,5'-dichlorodiphenylmethane	yes	no	yes	12			
180	17160	0000097-53-0	eugenol	no	yes	no		(33)		
181	20890	0000097-63-2	methacrylic acid, ethyl ester	no	yes	no		(23)		
182	19270	0000097-65-4	itaconic acid	no	yes	no				
183	21010	0000097-86-9	methacrylic acid, isobutyl ester	no	yes	no		(23)		
184	20110	0000097-88-1	methacrylic acid, butyl ester	no	yes	no		(23)		
185	20440	0000097-90-5	methacrylic acid, diester with ethyleneglycol	no	yes	no	0,05			
186	14020	0000098-54-4	4-tert-butylphenol	no	yes	no	0,05			
187	22210	0000098-83-9	α -methylstyrene	no	yes	no	0,05			

▼M3▼B

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
188	19180	0000099-63-8	isophthalic acid dichloride	no	yes	no		(27)		
189	60200	0000099-76-3	4-hydroxybenzoic acid, methyl ester	yes	no	no				
190	18880	0000099-96-7	<i>p</i> -hydroxybenzoic acid	no	yes	no				
191	24940	0000100-20-9	terephthalic acid dichloride	no	yes	no		(28)		
192	23187	—	phthalic acid	no	yes	no		(28)		
193	24610	0000100-42-5	styrene	no	yes	no				
194	13150	0000100-51-6	benzyl alcohol	no	yes	no				
195	37360	0000100-52-7	benzaldehyde	yes	no	no				(3)
196	18670	0000100-97-0	hexamethylenetetramine	yes	yes	no		(15)		
	59280									
197	20260	0000101-43-9	methacrylic acid, cyclohexyl ester	no	yes	no	0,05			
198	16630	0000101-68-8	diphenylmethane-4,4'-diisocyanate	no	yes	no		(17)	1 mg/kg in final product expressed as isocyanate moiety	(10)
199	24073	0000101-90-6	resorcinol diglycidyl ether	no	yes	no	ND		Not to be used for articles in contact with fatty foods for which ►M7 simulant D1 and/or D2 ◀ is laid down. For indirect food contact only, behind a PET layer.	(8)
200	51680	0000102-08-9	N,N'-diphenylthiourea	yes	no	yes	3			
201	16540	0000102-09-0	diphenyl carbonate	no	yes	no	0,05			
202	23070	0000102-39-6	(1,3-phenylenedioxy)diacetic acid	no	yes	no	0,05			►M8 — ◀

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
203	13323	0000102-40-9	1,3-bis(2-hydroxyethoxy)benzene	no	yes	no	0,05			
204	25180	0000102-60-3	N,N,N',N'-tetrakis(2-hydroxypropyl)ethylenediamine	yes	yes	no				
	92640									
205	25385	0000102-70-5	triallylamine	no	yes	no			40 mg/kg hydrogel at a ratio of 1 kg food to a maximum of 1,5 grams of hydrogel. Only to be used in hydrogels intended for non-direct food contact use.	
206	11500	0000103-11-7	acrylic acid, 2-ethylhexyl ester	no	yes	no	0,05			
207	31920	0000103-23-1	adipic acid, bis(2-ethylhexyl) ester	yes	no	yes	18	(32)		(2)
208	18898	0000103-90-2	N-(4-hydroxyphenyl) acetamide	no	yes	no	0,05			
209	17050	0000104-76-7	2-ethyl-1-hexanol	no	yes	no	30			
210	13390	0000105-08-8	1,4-bis(hydroxymethyl)cyclohexane	no	yes	no				
	14880									
211	23920	0000105-38-4	propionic acid, vinyl ester	no	yes	no		(1)		
212	14200	0000105-60-2	caprolactam	yes	yes	no			(4)	
	41840									
213	82400	0000105-62-4	1,2-propyleneglycol dioleate	yes	no	no				
214	61840	0000106-14-9	12-hydroxystearic acid	yes	no	no				

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
215	14170	0000106-31-0	butyric anhydride	no	yes	no				
216	14770	0000106-44-5	<i>p</i> -cresol	no	yes	no				
217	15565	0000106-46-7	1,4-dichlorobenzene	no	yes	no	12			
218	11590	0000106-63-8	acrylic acid, isobutyl ester	no	yes	no		(22)		
219	14570	0000106-89-8	epichlorohydrin	no	yes	no	ND		1 mg/kg in final product	(10)
	16750									
220	20590	0000106-91-2	methacrylic acid, 2,3-epoxypropyl ester	no	yes	no	0,02			(10)
221	40570	0000106-97-8	butane	yes	no	no				
222	13870	0000106-98-9	1-butene	no	yes	no				
223	13630	0000106-99-0	butadiene	no	yes	no	ND		1 mg/kg in final product	
224	13900	0000107-01-7	2-butene	no	yes	no				
225	12100	0000107-13-1	acrylonitrile	no	yes	no	ND			
226	15272	0000107-15-3	ethylenediamine	no	yes	no	12			
	16960									
227	16990	0000107-21-1	ethyleneglycol	yes	yes	no		(2)		
	53650									
228	13690	0000107-88-0	1,3-butanediol	no	yes	no				
229	14140	0000107-92-6	butyric acid	no	yes	no				

▼ B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)	
230	16150	0000108-01-0	dimethylaminoethanol	no	yes	no	18				
231	10120	0000108-05-4	acetic acid, vinyl ester	no	yes	no	12				
232	10150	0000108-24-7	acetic anhydride	yes	yes	no					
	30280										
233	24850	0000108-30-5	succinic anhydride	no	yes	no					
234	19960	0000108-31-6	maleic anhydride	no	yes	no		(3)			
235	14710	0000108-39-4	<i>m</i> -cresol	no	yes	no					
236	23050	0000108-45-2	1,3-phenylenediamine	no	yes	no	ND				
237	15910	0000108-46-3	1,3-dihydroxybenzene	no	yes	no	2,4				
	24072										
238	18070	0000108-55-4	glutaric anhydride	no	yes	no					
▼ <u>M2</u>	239	0000108-78-1	2,4,6-triamino-1,3,5-triazine	yes	yes	no	2,5				
											19975
											25420
	93720										
▼ <u>B</u>	240	45760	0000108-91-8	cyclohexylamine	yes	no	no				
▼ <u>M6</u>	241	22960	0000108-95-2	phenol	no	yes	no	3			
▼ <u>B</u>	242	85360	0000109-43-3	sebacic acid, dibutyl ester	yes	no	no		(32)		
	243	19060	0000109-53-5	isobutyl vinyl ether	no	yes	no	0,05		(10)	
	244	71720	0000109-66-0	pentane	yes	no	no				

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
245	22900	0000109-67-1	1-pentene	no	yes	no	5			
246	25150	0000109-99-9	tetrahydrofuran	no	yes	no	0,6			
247	24820	0000110-15-6	succinic acid	yes	yes	no				
	90960									
248	19540	0000110-16-7	maleic acid	yes	yes	no		(3)		
	64800									
249	17290	0000110-17-8	fumaric acid	yes	yes	no				
	55120									
250	53520	0000110-30-5	N,N'-ethylenebisstearamide	yes	no	no				
251	53360	0000110-31-6	N,N'-ethylenebisoleamide	yes	no	no				
252	87200	0000110-44-1	sorbic acid	yes	no	no				
253	15250	0000110-60-1	1,4-diaminobutane	no	yes	no				
254	13720	0000110-63-4	1,4-butanediol	yes	yes	no		(30)		
	40580									
255	25900	0000110-88-3	trioxane	no	yes	no	5			
256	18010	0000110-94-1	glutaric acid	yes	yes	no				
	55680									
257	13550	0000110-98-5	dipropylene glycol	yes	yes	no				
	16660	0025265-71-8								
	51760									

▼M3

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
258	70480	0000111-06-8	palmitic acid, butyl ester	yes	no	no				
259	58720	0000111-14-8	heptanoic acid	yes	no	no				
260	24280	0000111-20-6	sebacic acid	no	yes	no				
261	15790	0000111-40-0	diethylenetriamine	no	yes	no	5			
262	35284	0000111-41-1	N-(2-aminoethyl)ethanolamine	yes	no	no	0,05		Not to be used for articles in contact with fatty foods for which ►M7 simulant D1 and/or D2 ◀ is laid down. For indirect food contact only, behind a PET layer.	
263	13326	0000111-46-6	diethyleneglycol	yes	yes	no		(2)		
	15760									
	47680									
264	22660	0000111-66-0	1-octene	no	yes	no	15			
265	22600	0000111-87-5	1-octanol	no	yes	no				
266	25510	0000112-27-6	triethyleneglycol	yes	yes	no				
	94320									
267	15100	0000112-30-1	1-decanol	no	yes	no				
268	16704	0000112-41-4	1-dodecene	no	yes	no	0,05			
269	25090	0000112-60-7	tetraethyleneglycol	yes	yes	no				
	92350									

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
270	22763	0000112-80-1	oleic acid	yes	yes	no				
	69040									
271	52720	0000112-84-5	erucamide	yes	no	no				
272	37040	0000112-85-6	behenic acid	yes	no	no				
273	52730	0000112-86-7	erucic acid	yes	no	no				
274	22570	0000112-96-9	octadecyl isocyanate	no	yes	no		(17)	1 mg/kg in final product expressed as isocyanate moiety	(10)
275	23980	0000115-07-1	propylene	no	yes	no				
276	19000	0000115-11-7	isobutene	no	yes	no				
277	18280	0000115-27-5	hexachloroendomethylenetetrahydrophthalic anhydride	no	yes	no	ND			
278	18250	0000115-28-6	hexachloroendomethylenetetrahydrophthalic acid	no	yes	no	ND			
279	22840	0000115-77-5	pentaerythritol	yes	yes	no				
	71600									
280	73720	0000115-96-8	phosphoric acid, trichloroethyl ester	yes	no	no	ND			
281	25120	0000116-14-3	tetrafluoroethylene	no	yes	no	0,05			
282	18430	0000116-15-4	hexafluoropropylene	no	yes	no	ND			

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
283	74640	0000117-81-7	phthalic acid, bis(2-ethylhexyl) ester	yes	no	no	1,5	(32)	Only to be used as: (a) plasticiser in repeated use materials and articles contacting non-fatty foods; (b) technical support agent in concentrations up to 0,1 % in the final product.	(7)
284	84880	0000119-36-8	salicylic acid, methyl ester	yes	no	no	30			
285	66480	0000119-47-1	2,2'-methylene bis(4-methyl-6-tert-butylphenol)	yes	no	yes		(13)		
286	38240	0000119-61-9	benzophenone	yes	no	yes	0,6			
287	60160	0000120-47-8	4-hydroxybenzoic acid, ethyl ester	yes	no	no				
288	24970	0000120-61-6	terephthalic acid, dimethyl ester	no	yes	no				
289	15880	0000120-80-9	1,2-dihydroxybenzene	no	yes	no	6			
	24051									
290	55360	0000121-79-9	gallic acid, propyl ester	yes	no	no		(20)		
291	19150	0000121-91-5	isophthalic acid	no	yes	no		(27)		
292	94560	0000122-20-3	triisopropanolamine	yes	no	no	5			
293	23175	0000122-52-1	phosphorous acid, triethyl ester	no	yes	no	ND		1 mg/kg in final product	(1)
294	93120	0000123-28-4	thiodipropionic acid, didodecyl ester	yes	no	yes		(14)		

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
295	15940	0000123-31-9	1,4-dihydroxybenzene	yes	yes	no	0,6			
	18867									
	48620									
296	23860	0000123-38-6	propionaldehyde	no	yes	no				
297	23950	0000123-62-6	propionic anhydride	no	yes	no				
298	14110	0000123-72-8	butyraldehyde	no	yes	no				
299	63840	0000123-76-2	levulinic acid	yes	no	no				
300	30045	0000123-86-4	acetic acid, butyl ester	yes	no	no				
301	89120	0000123-95-5	stearic acid, butyl ester	yes	no	no				
302	12820	0000123-99-9	azelaic acid	no	yes	no				
303	12130	0000124-04-9	adipic acid	yes	yes	no				
	31730									
304	14320	0000124-07-2	caprylic acid	yes	yes	no				
	41960									
305	15274	0000124-09-4	hexamethylenediamine	no	yes	no	2,4			
	18460									
306	88960	0000124-26-5	stearamide	yes	no	no				
307	42160	0000124-38-9	carbon dioxide	yes	no	no				
308	91200	0000126-13-6	sucrose acetate isobutyrate	yes	no	no				

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
309	91360	0000126-14-7	sucrose octaacetate	yes	no	no				
310	16390	0000126-30-7	2,2-dimethyl-1,3-propanediol	no	yes	no	0,05			
	22437									
311	16480	0000126-58-9	dipentaerythritol	yes	yes	no				
	51200									
312	21490	0000126-98-7	methacrylonitrile	no	yes	no	ND			
313	16650	0000127-63-9	diphenyl sulphone	yes	yes	no	3			
	51570									
314	23500	0000127-91-3	β-pinene	no	yes	no				
315	46640	0000128-37-0	2,6-di-tert-butyl-p-cresol	yes	no	no	3			
316	23230	0000131-17-9	phthalic acid, diallyl ester	no	yes	no	ND			
317	48880	0000131-53-3	2,2'-dihydroxy-4-methoxybenzophenone	yes	no	yes		(8)		
318	48640	0000131-56-6	2,4-dihydroxybenzophenone	yes	no	no		(8)		
319	61360	0000131-57-7	2-hydroxy-4-methoxybenzophenone	yes	no	yes		(8)		
320	37680	0000136-60-7	benzoic acid, butyl ester	yes	no	no				
321	36080	0000137-66-6	ascorbyl palmitate	yes	no	no				
322	63040	0000138-22-7	lactic acid, butyl ester	yes	no	no				
323	11470	0000140-88-5	acrylic acid, ethyl ester	no	yes	no		(22)		

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
324	83700	0000141-22-0	ricinoleic acid	yes	no	yes	42			
325	10780	0000141-32-2	acrylic acid, n-butyl ester	no	yes	no		(22)		
326	12763	0000141-43-5	2-aminoethanol	yes	yes	no	0,05		Not to be used for articles in contact with fatty foods for which ►M7 simulant D1 and/or D2 ◀ is laid down. For indirect food contact only, behind a PET layer.	
	35170									
327	30140	0000141-78-6	acetic acid, ethyl ester	yes	no	no				
328	65040	0000141-82-2	malonic acid	yes	no	no				
329	59360	0000142-62-1	hexanoic acid	yes	no	no				
330	19470	0000143-07-7	lauric acid	yes	yes	no				
	63280									
331	22480	0000143-08-8	1-nonanol	no	yes	no				
332	69760	0000143-28-2	oleyl alcohol	yes	no	no				
333	22775	0000144-62-7	oxalic acid	yes	yes	no	6			
	69920									
334	17005	0000151-56-4	ethyleneimine	no	yes	no	ND			
335	68960	0000301-02-0	oleamide	yes	no	no				
336	15095	0000334-48-5	n-decanoic acid	yes	yes	no				
	45940									
337	15820	0000345-92-6	4,4'-difluorobenzophenone	no	yes	no	0,05			

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
338	71020	0000373-49-9	palmitoleic acid	yes	no	no				
339	86160	0000409-21-2	silicon carbide	yes	no	no				

▼M4

340	47440	0000461-58-5	dicyanodiamide	yes	no	no	60			
-----	-------	--------------	----------------	-----	----	----	----	--	--	--

▼B

341	13180	0000498-66-8	bicyclo[2.2.1]hept-2-ene	no	yes	no	0,05			
	22550									
342	14260	0000502-44-3	caprolactone	no	yes	no		(29)		
343	23770	0000504-63-2	1,3-propanediol	no	yes	no	0,05			

▼M6

344	13810	0000505-65-7	1,4-butanediol formal	no	yes	no	0,05	15 30		(21)
	21821									

▼B

345	35840	0000506-30-9	arachidic acid	yes	no	no				
346	10030	0000514-10-3	abietic acid	no	yes	no				
347	13050	0000528-44-9	trimellitic acid	no	yes	no		(21)		
	25540									
348	22350	0000544-63-8	myristic acid	yes	yes	no				
	67891									
349	25550	0000552-30-7	trimellitic anhydride	no	yes	no		(21)		
350	63920	0000557-59-5	lignoceric acid	yes	no	no				

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
351	21730	0000563-45-1	3-methyl-1-butene	no	yes	no	ND		Only to be used in polypropylene	(1)
352	16360	0000576-26-1	2,6-dimethylphenol	no	yes	no	0,05			
353	42480	0000584-09-8	carbonic acid, rubidium salt	yes	no	no	12			
354	25210	0000584-84-9	2,4-toluene diisocyanate	no	yes	no		(17)	1 mg/kg in final product expressed as isocyanate moiety	(10)
355	20170	0000585-07-9	methacrylic acid, tert-butyl ester	no	yes	no		(23)		
356	18820	0000592-41-6	1-hexene	no	yes	no	3			
357	13932	0000598-32-3	3-buten-2-ol	no	yes	no	ND		Only to be used as a co-monomer for the preparation of polymeric additive	(1)
358	14841	0000599-64-4	4-cumylphenol	no	yes	no	0,05			
359	15970	0000611-99-4	4,4'-dihydroxybenzophenone	yes	yes	no		(8)		
	48720									
360	57920	0000620-67-7	glycerol triheptanoate	yes	no	no				
361	18700	0000629-11-8	1,6-hexanediol	no	yes	no	0,05			
362	14350	0000630-08-0	carbon monoxide	no	yes	no				
363	16450	0000646-06-0	1,3-dioxolane	no	yes	no	5			

▼ B▼ M6

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
364	15404	0000652-67-5	1,4:3,6-dianhydrosorbitol	no	yes	no	5		Only to be used as: (a) a co-monomer in poly (ethylene-co-isosorbide terephthalate); (b) a co-monomer at levels of up to 40 mole % of the diol component in combination with ethylene glycol and/or 1,4-bis(hydroxymethyl)cyclohexane, for the production of polyesters. Polyesters made using dianhydrosorbitol together with 1,4-bis(hydroxymethyl)cyclohexane shall not be used in contact with foods containing more than 15 % alcohol.	
365	11680	0000689-12-3	acrylic acid, isopropyl ester	no	yes	no		(22)		
366	22150	0000691-37-2	4-methyl-1-pentene	no	yes	no	0,05			
367	16697	0000693-23-2	n-dodecanedioic acid	no	yes	no				
368	93280	0000693-36-7	thiodipropionic acid, dioctadecyl ester	yes	no	yes		(14)		
369	12761	0000693-57-2	12-aminododecanoic acid	no	yes	no	0,05			
370	21460	0000760-93-0	methacrylic anhydride	no	yes	no		(23)		
371	11510 11830	0000818-61-1	acrylic acid, monoester with ethyleneglycol	no	yes	no		(22)		
372	18640	0000822-06-0	hexamethylene diisocyanate	no	yes	no		(17)	1 mg/kg in final product expressed as isocyanate moiety	(10)
373	22390	0000840-65-3	2,6-naphthalenedicarboxylic acid, dimethyl ester	no	yes	no	0,05			
374	21190	0000868-77-9	methacrylic acid, monoester with ethyleneglycol	no	yes	no		(23)		
375	15130	0000872-05-9	1-decene	no	yes	no	0,05			

▼ B

▼ **B**▼ **M2**▼ **B**

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
376	66905	0000872-50-4	N-methylpyrrolidone	yes	no	no	60			
377	12786	0000919-30-2	3-aminopropyltriethoxysilane	no	yes	no	0,05		Residual extractable content of 3-aminopropyltriethoxysilane to be less than 3 mg/kg filler when used for the reactive surface treatment of inorganic fillers. SML = 0,05 mg/kg when used for the surface treatment of materials and articles.	
378	21970	0000923-02-4	N-methylolmethacrylamide	no	yes	no	0,05			
379	21940	0000924-42-5	N-methylolacrylamide	no	yes	no	ND			
380	11980	0000925-60-0	acrylic acid, propyl ester	no	yes	no		(22)		
381	15030	0000931-88-4	cyclooctene	no	yes	no	0,05		Only to be used in polymers contacting foods for which simulant A is laid down	
382	19490	0000947-04-6	lauro lactam	no	yes	no	5			
383	72160	0000948-65-2	2-phenylindole	yes	no	yes	15			
384	40000	0000991-84-4	2,4-bis(octylmercapto)-6-(4-hydroxy-3,5-di-tert-butylanilino)-1,3,5-triazine	yes	no	yes	30			
385	11530	0000999-61-1	acrylic acid, 2-hydroxypropyl ester	no	yes	no	0,05		SML expressed as the sum of acrylic acid, 2-hydroxypropyl ester and acrylic acid, 2-hydroxyisopropyl ester. It may contain up to 25 % (m/m) of acrylic acid, 2-hydroxyisopropyl ester (CAS No 0002918-23-2).	(1)
386	55280	0001034-01-1	gallic acid, octyl ester	yes	no	no		(20)		
387	26155	0001072-63-5	1-vinylimidazole	no	yes	no	0,05			► M8 ◀
388	25080	0001120-36-1	1-tetradecene	no	yes	no	0,05			

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
389	22360	0001141-38-4	2,6-naphthalenedicarboxylic acid	no	yes	no	5			
390	55200	0001166-52-5	gallic acid, dodecyl ester	yes	no	no		(20)		

▼M7

391	22932	0001187-93-5	perfluoromethyl perfluorovinyl ether	no	yes	no	0,05		Only to be used in: — anti-stick coatings; — fluoro- and perfluoropolymers intended for repeated use applications where the contact ratio is 1 dm ² surface in contact with at least 150 kg food.	
-----	-------	--------------	--------------------------------------	----	-----	----	------	--	--	--

▼B

392	72800	0001241-94-7	phosphoric acid, diphenyl 2-ethylhexyl ester	yes	no	yes	2,4			
393	37280	0001302-78-9	bentonite	yes	no	no				
394	41280	0001305-62-0	calcium hydroxide	yes	no	no				
395	41520	0001305-78-8	calcium oxide	yes	no	no				
396	64640	0001309-42-8	magnesium hydroxide	yes	no	no				
397	64720	0001309-48-4	magnesium oxide	yes	no	no				
398	35760	0001309-64-4	antimony trioxide	yes	no	no	0,04		SML expressed as antimony	(6)
399	81600	0001310-58-3	potassium hydroxide	yes	no	no				
400	86720	0001310-73-2	sodium hydroxide	yes	no	no				
401	24475	0001313-82-2	sodium sulphide	no	yes	no				
402	96240	0001314-13-2	zinc oxide	yes	no	no				
403	96320	0001314-98-3	zinc sulphide	yes	no	no				
404	67200	0001317-33-5	molybdenum disulphide	yes	no	no				
405	16690	0001321-74-0	divinylbenzene	no	yes	no	ND		SML expressed as the sum of divinylbenzene and ethylvinylbenzene. It may contain up to 45 % (m/m) of ethylvinylbenzene.	(1)
406	83300	0001323-39-3	1,2-propyleneglycol monostearate	yes	no	no				

▼ B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
407	87040	0001330-43-4	sodium tetraborate	yes	no	no		(16)		
408	82960	0001330-80-9	1,2-propyleneglycol monooleate	yes	no	no				
409	62240	0001332-37-2	iron oxide	yes	no	no				

▼ M6

410	62720	0001332-58-7	kaolin	yes	no	no			<p>Particles can be thinner than 100 nm only if incorporated at a quantity of less than 12 % w/w in an ethylene vinyl alcohol copolymer (EVOH) inner layer of a multi-layer structure, in which the layer in direct contact with the food provides a functional barrier preventing migration of particles into the food.</p>	
-----	-------	--------------	--------	-----	----	----	--	--	--	--

▼ B

411	42080	0001333-86-4	carbon black	yes	no	no			<p>Primary particles of 10 – 300 nm which are aggregated to a size of 100 – 1 200 nm which may form agglomerates within the size distribution of 300 nm – mm. Toluene extractables: maximum 0,1 %, determined according to ISO method 6209. UV absorption of cyclohexane extract at 386 nm: < 0,02 AU for a 1 cm cell or < 0,1 AU for a 5 cm cell, determined according to a generally recognised method of analysis. Benzo(a)pyrene content: max 0,25 mg/kg carbon black. Maximum use level of carbon black in the polymer: 2,5 % w/w.</p>	
-----	-------	--------------	--------------	-----	----	----	--	--	---	--

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
412	45200	0001335-23-5	copper iodide	yes	no	no		(6)		
413	35600	0001336-21-6	ammonium hydroxide	yes	no	no				
414	87600	0001338-39-2	sorbitan monolaurate	yes	no	no				
415	87840	0001338-41-6	sorbitan monostearate	yes	no	no				
416	87680	0001338-43-8	sorbitan monooleate	yes	no	no				
417	85680	0001343-98-2	silicic acid	yes	no	no				
418	34720	0001344-28-1	aluminium oxide	yes	no	no				
419	92150	0001401-55-4	tannic acids	yes	no	no			According to the JECFA specifications	
420	19210	0001459-93-4	isophthalic acid, dimethyl ester	no	yes	no	0,05			
▼ <u>M4</u>										
421	13000	0001477-55-0	1,3-benzenedimethanamine	no	yes	no		(34)		
▼ <u>B</u>										
422	38515	0001533-45-5	4,4'-bis(2-benzoxazolyl)stilbene	yes	no	yes	0,05			(2)
423	22937	0001623-05-8	perfluoropropylperfluorovinyl ether	no	yes	no	0,05			
424	15070	0001647-16-1	1,9-decadiene	no	yes	no	0,05			

▼ **B**

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
425	10840	0001663-39-4	acrylic acid, tert-butyl ester	no	yes	no		(22)		
426	13510	0001675-54-3	2,2-bis(4-hydroxyphenyl)propane bis(2,3-epoxypropyl) ether	no	yes	no			In compliance with Commission Regulation (EC) No 1895/2005 ⁽¹⁾	
	13610									
427	18896	0001679-51-2	4-(hydroxymethyl)-1-cyclohexene	no	yes	no	0,05			
428	95200	0001709-70-2	1,3,5-trimethyl-2,4,6-tris(3,5-di-tert-butyl-4-hydroxybenzyl)benzene	yes	no	no				
429	13210	0001761-71-3	bis(4-aminocyclohexyl)methane	no	yes	no	0,05			
430	95600	0001843-03-4	1,1,3-tris(2-methyl-4-hydroxy-5-tert-butylphenyl) butane	yes	no	yes	5			
431	61600	0001843-05-6	2-hydroxy-4-n-octyloxybenzophenone	yes	no	yes		(8)		
432	12280	0002035-75-8	adipic anhydride	no	yes	no				
433	68320	0002082-79-3	octadecyl 3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate	yes	no	yes	6			
434	20410	0002082-81-7	methacrylic acid, diester with 1,4-butanediol	no	yes	no	0,05			
435	14230	0002123-24-2	caprolactam, sodium salt	no	yes	no		(4)		
436	19480	0002146-71-6	lauric acid, vinyl ester	no	yes	no				
437	11245	0002156-97-0	acrylic acid, dodecyl ester	no	yes	no	0,05			(2)
▼ M2										
438	13303	0002162-74-5	bis(2,6-diisopropylphenyl) carbodiimide	no	yes	no	0,05		Expressed as the sum of bis(2,6-diisopropylphenyl)carbodiimide and its hydrolysis product 2,6-diisopropylaniline	

▼ B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
439	21280	0002177-70-0	methacrylic acid, phenyl ester	no	yes	no		(23)		
440	21340	0002210-28-8	methacrylic acid, propyl ester	no	yes	no		(23)		
441	38160	0002315-68-6	benzoic acid, propyl ester	yes	no	no				
442	13780	0002425-79-8	1,4-butanediol bis(2,3-epoxypropyl)ether	no	yes	no	ND		Residual content = 1 mg/kg in final product expressed as epoxy-group. Molecular weight is 43 Da.	(10)
443	12788	0002432-99-7	11-aminoundecanoic acid	no	yes	no	5			
444	61440	0002440-22-4	2-(2'-hydroxy-5'-methylphenyl)benzotriazole	yes	no	no		(12)		
445	83440	0002466-09-3	pyrophosphoric acid	yes	no	no				
446	10750	0002495-35-4	acrylic acid, benzyl ester	no	yes	no		(22)		
447	20080	0002495-37-6	methacrylic acid, benzyl ester	no	yes	no		(23)		
448	11890	0002499-59-4	acrylic acid, n-octyl ester	no	yes	no		(22)		
▼ <u>M3</u>										
449	49840	0002500-88-1	dioctadecyl disulphide	yes	no	yes	0,05			
▼ <u>B</u>										
450	24430	0002561-88-8	sebacic anhydride	no	yes	no				
451	66755	0002682-20-4	2-methyl-4-isothiazolin-3-one	yes	no	no	0,5		Only to be used in aqueous polymer dispersions and emulsions	
▼ <u>M2</u>										
452	38885	0002725-22-6	2,4-bis(2,4-dimethylphenyl)-6-(2-hydroxy-4-n-octyloxyphenyl)-1,3,5-triazine	yes	no	no	5			
▼ <u>B</u>										
453	26320	0002768-02-7	vinyltrimethoxysilane	no	yes	no	0,05			(10)

▼ **B**

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
454	12670	0002855-13-2	1-amino-3-aminomethyl-3,5,5-trimethylcyclohexane	no	yes	no	6			
455	20530	0002867-47-2	methacrylic acid, 2-(dimethyl-amino)-ethyl ester	no	yes	no	ND			
456	10810	0002998-08-5	acrylic acid, sec-butyl ester	no	yes	no		(22)		
457	20140	0002998-18-7	methacrylic acid, sec-butyl ester	no	yes	no		(23)		
458	36960	0003061-75-4	behenamide	yes	no	no				
459	46870	0003135-18-0	3,5-di-tert-butyl-4-hydroxybenzyl-phosphonic acid, dioctadecyl ester	yes	no	no				
460	14950	0003173-53-3	cyclohexyl isocyanate	no	yes	no		(17)	1 mg/kg in final product expressed as isocyanate moiety	(10)
461	22420	0003173-72-6	1,5-naphthalene diisocyanate	no	yes	no		(17)	1 mg/kg in final product expressed as isocyanate moiety	(10)
462	26170	0003195-78-6	N-vinyl-N-methylacetamide	no	yes	no	0,02			► M8 ◀
463	25840	0003290-92-4	1,1,1-trimethylolpropane trimethacrylate	no	yes	no	0,05			
464	61280	0003293-97-8	2-hydroxy-4-n-hexyloxybenzophenone	yes	no	yes		(8)		
465	68040	0003333-62-8	7-[2H-naphtho-(1,2-D)triazol-2-yl]-3-phenylcoumarin	yes	no	no				
466	50640	0003648-18-8	di-n-octyltin dilaurate	yes	no	no		(10)		
▼ M12	467	3724-65-0	crotonic acid	yes	yes	no		(35)		
	14800									
	45600									
▼ B	468	0003825-26-1	perfluorooctanoic acid, ammonium salt	yes	no	no			Only to be used in repeated use articles, sintered at high temperatures	

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
469	60480	0003864-99-1	2-(2'-hydroxy-3,5'-di-tert-butylphenyl)-5-chlorobenzotriazole	yes	no	yes		(12)		
470	60400	0003896-11-5	2-(2'-hydroxy-3'-tert-butyl-5'-methylphenyl)-5-chlorobenzotriazole	yes	no	yes		(12)		
471	24888	0003965-55-7	5-sulphoisophthalic acid, monosodium salt, dimethyl ester	no	yes	no	0,05			
472	66560	0004066-02-8	2,2'-methylenebis(4-methyl-6-cyclohexylphenol)	yes	no	yes		(5)		
473	12265	0004074-90-2	adipic acid, divinyl ester	no	yes	no	ND		5 mg/kg in final product. Only to be used as co-monomer.	(1)
474	43600	0004080-31-3	1-(3-chloroallyl)-3,5,7-triaza-1-azoniaadamantane chloride	yes	no	no	0,3			
475	19110	0004098-71-9	1-isocyanato-3-isocyanatomethyl-3,5,5-trimethylcyclohexane	no	yes	no		(17)	1 mg/kg in final product expressed as isocyanate moiety	(10)
476	16570	0004128-73-8	diphenylether-4,4'-diisocyanate	no	yes	no		(17)	1 mg/kg in final product expressed as isocyanate moiety	(10)
477	46720	0004130-42-1	2,6-di-tert-butyl-4-ethylphenol	yes	no	yes	4,8			(1)
478	60180	0004191-73-5	4-hydroxybenzoic acid, isopropyl ester	yes	no	no				
479	12970	0004196-95-6	azelaic anhydride	no	yes	no				
480	46790	0004221-80-1	3,5-di-tert-butyl-4-hydroxybenzoic acid, 2,4-di-tert-butylphenyl ester	yes	no	no				
481	13060	0004422-95-1	1,3,5-benzenetricarboxylic acid trichloride	no	yes	no	0,05		SML expressed as 1,3,5-benzenetricarboxylic acid	► M8 ◀

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
482	21100	0004655-34-9	methacrylic acid, isopropyl ester	no	yes	no		(23)		
483	68860	0004724-48-5	n-octylphosphonic acid	yes	no	no	0,05			
484	13395	0004767-03-7	2,2-bis(hydroxymethyl)propionic acid	no	yes	no	0,05			(1)
485	13560	0005124-30-1	dicyclohexylmethane-4,4'-diisocyanate	no	yes	no		(17)	1 mg/kg in final product expressed as isocyanate moiety	(10)
	15700									
486	54005	0005136-44-7	ethylene-N-palmitamide-N'-stearamide	yes	no	no				
487	45640	0005232-99-5	2-cyano-3,3-diphenylacrylic acid, ethyl ester	yes	no	no	0,05			
488	53440	0005518-18-3	N,N'-ethylenebispalmitamide	yes	no	no				
489	41040	0005743-36-2	calcium butyrate	yes	no	no				
490	16600	0005873-54-1	diphenylmethane-2,4'-diisocyanate	no	yes	no		(17)	1 mg/kg in final product expressed as isocyanate moiety	(10)
491	82720	0006182-11-2	1,2-propyleneglycol distearate	yes	no	no				
492	45650	0006197-30-4	2-cyano-3,3-diphenylacrylic acid, 2-ethylhexyl ester	yes	no	no	0,05			
493	39200	0006200-40-4	bis(2-hydroxyethyl)-2-hydroxypropyl-3-(dodecyloxy)methylammonium chloride	yes	no	no	1,8			
494	62140	0006303-21-5	hypophosphorous acid	yes	no	no				
495	35160	0006642-31-5	6-amino-1,3-dimethyluracil	yes	no	no	5			

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
496	71680	0006683-19-8	pentaerythritol tetrakis[3-(3,5-di-tert-butyl-4-hydroxyphenyl)-propionate]	yes	no	no				
497	95020	0006846-50-0	2,2,4-trimethyl-1,3-pentanediol diisobutyrate	yes	no	no	5		Only to be used in single-use gloves	
498	16210	0006864-37-5	3,3'-dimethyl-4,4'-diaminodicyclohexylmethane	no	yes	no	0,05		Only to be used in polyamides	(5)
499	19965	0006915-15-7	malic acid	yes	yes	no			In case of use as a monomer only to be used as a co-monomer in aliphatic polyesters up to maximum level of 1 % on a molar basis	
	65020									
500	38560	0007128-64-5	2,5-bis(5-tert-butyl-2-benzoxazolyl)thiophene	yes	no	yes	0,6			
501	34480	—	aluminium fibers, flakes and powders	yes	no	no				
502	22778	0007456-68-0	4,4'-oxybis(benzenesulphonyl azide)	no	yes	no	0,05			► M8 ◀
503	46080	0007585-39-9	β-dextrin	yes	no	no				
504	86240	0007631-86-9	silicon dioxide	yes	no	no			For synthetic amorphous silicon dioxide: primary particles of 1 – 100 nm which are aggregated to a size of 0,1 – 1 μm which may form agglomerates within the size distribution of 0,3 μm to the mm size.	
505	86480	0007631-90-5	sodium bisulphite	yes	no	no		(19)		

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
506	86920	0007632-00-0	sodium nitrite	yes	no	no	0,6			
507	59990	0007647-01-0	hydrochloric acid	yes	no	no				
508	86560	0007647-15-6	sodium bromide	yes	no	no				
509	23170	0007664-38-2	phosphoric acid	yes	yes	no				
	72640									
510	12789	0007664-41-7	ammonia	yes	yes	no				
	35320									
511	91920	0007664-93-9	sulphuric acid	yes	no	no				
512	81680	0007681-11-0	potassium iodide	yes	no	no		(6)		
513	86800	0007681-82-5	sodium iodide	yes	no	no		(6)		
514	91840	0007704-34-9	sulphur	yes	no	no				
515	26360	0007732-18-5	water	yes	yes	no			In compliance with Directive 98/83/EC (2)	
	95855									
516	86960	0007757-83-7	sodium sulphite	yes	no	no		(19)		
517	81520	0007758-02-3	potassium bromide	yes	no	no				
518	35845	0007771-44-0	arachidonic acid	yes	no	no				
519	87120	0007772-98-7	sodium thiosulphate	yes	no	no		(19)		
520	65120	0007773-01-5	manganese chloride	yes	no	no				
521	58320	0007782-42-5	graphite	yes	no	no				

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
522	14530	0007782-50-5	chlorine	no	yes	no				
523	45195	0007787-70-4	copper bromide	yes	no	no				
524	24520	0008001-22-7	soybean oil	no	yes	no				
525	62640	0008001-39-6	japan wax	yes	no	no				
526	43440	0008001-75-0	ceresin	yes	no	no				
527	14411	0008001-79-4	castor oil	yes	yes	no				
	42880									
528	63760	0008002-43-5	lecithin	yes	no	no				
529	67850	0008002-53-7	montan wax	yes	no	no				
530	41760	0008006-44-8	candelilla wax	yes	no	no				
531	36880	0008012-89-3	beeswax	yes	no	no				
532	88640	0008013-07-8	soybean oil, epoxidised	yes	no	no	60 30(*)	(32)	(*) In the case of PVC gaskets used to seal glass jars containing infant formulae and follow-on formulae as defined by Directive 2006/141/EC or processed cereal-based foods and baby foods for infants and young children as defined by Directive 2006/125/EC, the SML is lowered to 30 mg/kg. Oxirane < 8 %, iodine number < 6.	

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
533	42720	0008015-86-9	carnauba wax	yes	no	no				
534	80720	0008017-16-1	polyphosphoric acids	yes	no	no				
535	24100	0008050-09-7	rosin	yes	yes	no				
	24130									
	24190									
	83840									
536	84320	0008050-15-5	rosin, hydrogenated, ester with methanol	yes	no	no				
537	84080	0008050-26-8	rosin, ester with pentaerythritol	yes	no	no				
538	84000	0008050-31-5	rosin, ester with glycerol	yes	no	no				
539	24160	0008052-10-6	rosin tall oil	no	yes	no				
540	63940	0008062-15-5	lignosulphonic acid	yes	no	no	0,24		Only to be used as dispersant for plastics dispersions	
541	58480	0009000-01-5	gum arabic	yes	no	no				
542	42640	0009000-11-7	carboxymethylcellulose	yes	no	no				
543	45920	0009000-16-2	dammar	yes	no	no				
544	58400	0009000-30-0	guar gum	yes	no	no				
545	93680	0009000-65-1	tragacanth gum	yes	no	no				
546	71440	0009000-69-5	pectin	yes	no	no				

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
547	55440	0009000-70-8	gelatin	yes	no	no				
548	42800	0009000-71-9	casein	yes	no	no				
549	80000	0009002-88-4	polyethylene wax	yes	no	no				
550	81060	0009003-07-0	polypropylene wax	yes	no	no				
551	79920	0009003-11-6 0106392-12-5	poly(ethylene propylene) glycol	yes	no	no				
552	81500	0009003-39-8	polyvinylpyrrolidone	yes	no	no			The substance shall meet the purity criteria as laid down in Commission Directive 2008/84/EC ⁽³⁾	
553	14500	0009004-34-6	cellulose	yes	yes	no				
	43280									
554	43300	0009004-36-8	cellulose acetate butyrate	yes	no	no				
555	53280	0009004-57-3	ethylcellulose	yes	no	no				
556	54260	0009004-58-4	ethylhydroxyethylcellulose	yes	no	no				
557	66640	0009004-59-5	methylethylcellulose	yes	no	no				
558	60560	0009004-62-0	hydroxyethylcellulose	yes	no	no				
559	61680	0009004-64-2	hydroxypropylcellulose	yes	no	no				
560	66700	0009004-65-3	methylhydroxypropylcellulose	yes	no	no				
561	66240	0009004-67-5	methylcellulose	yes	no	no				
562	22450	0009004-70-0	nitrocellulose	no	yes	no				

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
563	78320	0009004-97-1	polyethyleneglycol monoricinoleate	yes	no	yes	42			
564	24540	0009005-25-8	starch, edible	yes	yes	no				
	88800									
565	61120	0009005-27-0	hydroxyethyl starch	yes	no	no				
566	33350	0009005-32-7	alginic acid	yes	no	no				
567	82080	0009005-37-2	1,2-propyleneglycol alginate	yes	no	no				
568	79040	0009005-64-5	polyethyleneglycol sorbitan monolaurate	yes	no	no				
569	79120	0009005-65-6	polyethyleneglycol sorbitan monooleate	yes	no	no				
570	79200	0009005-66-7	polyethyleneglycol sorbitan monopalmitate	yes	no	no				
571	79280	0009005-67-8	polyethyleneglycol sorbitan monostearate	yes	no	no				
572	79360	0009005-70-3	polyethyleneglycol sorbitan trioleate	yes	no	no				
573	79440	0009005-71-4	polyethyleneglycol sorbitan tristearate	yes	no	no				
574	24250	0009006-04-6	rubber, natural	yes	yes	no				
	84560									

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
575	76721	0063148-62-9	polydimethylsiloxane (Mw > 6 800 Da)	yes	no	no			Viscosity at 25 °C not less than 100 cSt ($100 \times 10^{-6} \text{ m}^2/\text{s}$)	
576	60880	0009032-42-2	hydroxyethylmethylcellulose	yes	no	no				
577	62280	0009044-17-1	isobutylene-butene copolymer	yes	no	no				
578	79600	0009046-01-9	polyethyleneglycol tridecyl ether phosphate	yes	no	no	5		For materials and articles intended for contact with aqueous foods only. Polyethyleneglycol (EO ≤ 11) tridecyl ether phosphate (mono- and dialkyl ester) with a maximum 10 % content of polyethyleneglycol (EO ≤ 11) tridecylether.	
579	61800	0009049-76-7	hydroxypropyl starch	yes	no	no				
580	46070	0010016-20-3	α-dextrin	yes	no	no				
581	36800	0010022-31-8	barium nitrate	yes	no	no				
582	50240	0010039-33-5	di-n-octyltin bis(2-ethylhexyl maleate)	yes	no	no		(10)		
583	40400	0010043-11-5	boron nitride	yes	no	no		(16)		
584	13620	0010043-35-3	boric acid	yes	yes	no		(16)		
	40320									
585	41120	0010043-52-4	calcium chloride	yes	no	no				
586	65280	0010043-84-2	manganese hypophosphite	yes	no	no				

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
587	68400	0010094-45-8	octadecylceramide	yes	no	yes	5			
588	64320	0010377-51-2	lithium iodide	yes	no	no		(6)		
589	52645	0010436-08-5	cis-11-eicosenamide	yes	no	no				
590	21370	0010595-80-9	methacrylic acid, 2-sulphoethyl ester	no	yes	no	ND			(1)
591	36160	0010605-09-1	ascorbyl stearate	yes	no	no				
592	34690	0011097-59-9	aluminium magnesium carbonate hydroxide	yes	no	no				
593	44960	0011104-61-3	cobalt oxide	yes	no	no				
594	65360	0011129-60-5	manganese oxide	yes	no	no				
595	19510	0011132-73-3	lignocellulose	no	yes	no				
596	95935	0011138-66-2	xanthan gum	yes	no	no				
597	67120	0012001-26-2	mica	yes	no	no				
598	41600	0012004-14-7 0037293-22-4	calcium sulphoaluminate	yes	no	no				
599	36840	0012007-55-5	barium tetraborate	yes	no	no		(16)		
600	60030	0012072-90-1	hydromagnesite	yes	no	no				
601	35440	0012124-97-9	ammonium bromide	yes	no	no				
602	70240	0012198-93-5	ozokerite	yes	no	no				
603	83460	0012269-78-2	pyrophyllite	yes	no	no				
604	60080	0012304-65-3	hydrotalcite	yes	no	no				

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
605	11005	0012542-30-2	acrylic acid, dicyclopentenyl ester	no	yes	no	0,05			(1)
606	65200	0012626-88-9	manganese hydroxide	yes	no	no				
607	62245	0012751-22-3	iron phosphide	yes	no	no			Only to be used in PET polymers and copolymers	
608	40800	0013003-12-8	4,4'-butylidene-bis(6-tert-butyl-3-methylphenyl-ditridecyl phosphite)	yes	no	yes	6			
609	83455	0013445-56-2	pyrophosphorous acid	yes	no	no				
610	93440	0013463-67-7	titanium dioxide	yes	no	no				
611	35120	0013560-49-1	3-aminocrotonic acid, diester with thiobis (2-hydroxyethyl) ether	yes	no	no				
612	16694	0013811-50-2	N,N'-divinyl-2-imidazolidinone	no	yes	no	0,05			(10)
613	95905	0013983-17-0	wollastonite	yes	no	no				
614	45560	0014464-46-1	crystalite	yes	no	no				
615	92080	0014807-96-6	talc	yes	no	no				
616	83470	0014808-60-7	quartz	yes	no	no				
617	10660	0015214-89-8	2-acrylamido-2-methylpropanesulphonic acid	no	yes	no	0,05			
618	51040	0015535-79-2	di-n-octyltin mercaptoacetate	yes	no	no		(10)		
619	50320	0015571-58-1	di-n-octyltin bis(2-ethylhexyl mercaptoacetate)	yes	no	no		(10)		

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
620	50720	0015571-60-5	di-n-octyltin dimaleate	yes	no	no		(10)		
621	17110	0016219-75-3	5-ethylidenebicyclo[2,2,1]hept-2-ene	no	yes	no	0,05			(9)
622	69840	0016260-09-6	oleylpalmitamide	yes	no	yes	5			
623	52640	0016389-88-1	dolomite	yes	no	no				
624	18897	0016712-64-4	6-hydroxy-2-naphthalenecarboxylic acid	no	yes	no	0,05			
625	36720	0017194-00-2	barium hydroxide	yes	no	no				
626	57800	0018641-57-1	glycerol tribehenate	yes	no	no				
627	59760	0019569-21-2	huntite	yes	no	no				
628	96190	0020427-58-1	zinc hydroxide	yes	no	no				
629	34560	0021645-51-2	aluminium hydroxide	yes	no	no				
630	82240	0022788-19-8	1,2-propyleneglycol dilaurate	yes	no	no				
631	59120	0023128-74-7	1,6-hexamethylene-bis(3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionamide)	yes	no	yes	45			
632	52880	0023676-09-7	4-ethoxybenzoic acid, ethyl ester	yes	no	no	3,6			
633	53200	0023949-66-8	2-ethoxy-2'-ethyloxanilide	yes	no	yes	30			

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
634	25910	0024800-44-0	tripropylene glycol	no	yes	no				
635	40720	0025013-16-5	tert-butyl-4-hydroxyanisole	yes	no	no	30			
636	31500	0025134-51-4	acrylic acid, acrylic acid, 2-ethylhexyl ester, copolymer	yes	no	no	0,05	(22)	SML expressed as acrylic acid, 2-ethylhexyl ester	
637	71635	0025151-96-6	pentaerythritol dioleate	yes	no	no	0,05		Not to be used for articles in contact with fatty foods for which ► <u>M7</u> simulant D1 and/or D2 ◀ is laid down	
638	23590	0025322-68-3	polyethyleneglycol	yes	yes	no				
	76960									
639	23651	0025322-69-4	polypropylene glycol	yes	yes	no				
	80800									
640	54930	0025359-91-5	formaldehyde-1-naphthol, copolymer	yes	no	no	0,05			
▼ <u>M7</u>	641	22331	0025513-64-8	mixture of (35-45 % w/w) 1,6-diamino-2,2,4-trimethylhexane and (55-65 % w/w) 1,6-diamino-2,4,4-trimethylhexane	no	yes	no	0,05		
▼ <u>B</u>	642	64990	0025736-61-2	maleic anhydride-styrene, copolymer, sodium salt	yes	no	no			The fraction with molecular weight below 1 000 Da ► <u>M7</u> shall ◀ not exceed 0,05 % (w/w)
	643	87760	0026266-57-9	sorbitan monopalmitate	yes	no	no			
	644	88080	0026266-58-0	sorbitan trioleate	yes	no	no			
	645	67760	0026401-86-5	mono-n-octyltin tris(isooctyl mercaptoacetate)	yes	no	no		(11)	
	646	50480	0026401-97-8	di-n-octyltin bis(isooctyl mercaptoacetate)	yes	no	no		(10)	

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
647	56720	0026402-23-3	glycerol monohecanoate	yes	no	no				
648	56880	0026402-26-6	glycerol monohecanoate	yes	no	no				
649	47210	0026427-07-6	dibutylthiostannoic acid polymer	yes	no	no			Molecular unit = (C ₈ H ₁₈ S ₃ Sn ₂) _n (n = 1,5-2)	
650	49600	0026636-01-1	dimethyltin bis(isooctyl mercaptoacetate)	yes	no	no		(9)		
651	88240	0026658-19-5	sorbitan tristearate	yes	no	no				
652	38820	0026741-53-7	bis(2,4-di-tert-butylphenyl) pentaerythritol diphosphate	yes	no	yes	0,6			
653	25270	0026747-90-0	2,4-toluene diisocyanate dimer	no	yes	no		(17)	1 mg/kg in final product expressed as isocyanate moiety	(10)
654	88600	0026836-47-5	sorbitol monostearate	yes	no	no				
655	25450	0026896-48-0	tricyclodecanedimethanol	no	yes	no	0,05			
656	24760	0026914-43-2	styrenesulphonic acid	no	yes	no	0,05			
657	67680	0027107-89-7	mono-n-octyltin tris(2-ethylhexyl mercaptoacetate)	yes	no	no		(11)		
658	52000	0027176-87-0	dodecylbenzenesulphonic acid	yes	no	no	30			
659	82800	0027194-74-7	1,2-propyleneglycol monolaurate	yes	no	no				
660	47540	0027458-90-8	di-tert-dodecyl disulphide	yes	no	yes	0,05			

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
661	95360	0027676-62-6	1,3,5-tris(3,5-di-tert-butyl-4-hydroxybenzyl)-1,3,5-triazine-2,4,6(1H,3H,5H)-trione	yes	no	yes	5			
662	25927	0027955-94-8	1,1,1-tris(4-hydroxyphenyl)ethane	no	yes	no	0,005		Only to be used in polycarbonates	►M8 — ◀
663	64150	0028290-79-1	linolenic acid	yes	no	no				
664	95000	0028931-67-1	trimethylolpropane trimethacrylate-methyl methacrylate copolymer	yes	no	no				
665	83120	0029013-28-3	1,2-propyleneglycol monopalmitate	yes	no	no				
666	87280	0029116-98-1	sorbitan dioleate	yes	no	no				
667	55190	0029204-02-2	gadoleic acid	yes	no	no				
668	80240	0029894-35-7	polyglycerol ricinoleate	yes	no	no				
669	56610	0030233-64-8	glycerol monobehenate	yes	no	no				
670	56800	0030899-62-8	glycerol monolaurate diacetate	yes	no	no		(32)		
671	74240	0031570-04-4	phosphorous acid, tris(2,4-di-tert-butylphenyl)ester	yes	no	no				
672	76845	0031831-53-5	polyester of 1,4-butanediol with caprolactone	yes	no	no		(29) (30)	The fraction with molecular weight below 1 000 Da ►M7 shall ◀ not exceed 0,5 % (w/w)	
673	53670	0032509-66-3	ethylene glycol bis[3,3-bis(3-tert-butyl-4-hydroxyphenyl)butyrate]	yes	no	yes	6			

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
674	46480	0032647-67-9	dibenzylidene sorbitol	yes	no	no				
675	38800	0032687-78-8	N,N'-bis(3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionyl)hydrazide	yes	no	yes	15			
676	50400	0033568-99-9	di-n-octyltin bis(isooctyl maleate)	yes	no	no		(10)		
677	82560	0033587-20-1	1,2-propyleneglycol dipalmitate	yes	no	no				
678	59200	0035074-77-2	1,6-hexamethylene-bis(3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate)	yes	no	yes	6			
679	39060	0035958-30-6	1,1-bis(2-hydroxy-3,5-di-tert-butylphenyl)ethane	yes	no	yes	5			
680	94400	0036443-68-2	triethyleneglycol bis[3-(3-tert-butyl-4-hydroxy-5-methylphenyl)propionate]	yes	no	no	9			
681	18310	0036653-82-4	1-hexadecanol	no	yes	no				
682	53270	0037205-99-5	ethylcarboxymethylcellulose	yes	no	no				
683	66200	0037206-01-2	methylcarboxymethylcellulose	yes	no	no				
684	68125	0037244-96-5	nepheline syenite	yes	no	no				
685	85950	0037296-97-2	silicic acid, magnesium-sodium-fluoride salt	yes	no	no	0,15		SML expressed as fluoride. Only to be used in layers of multi-layer materials not coming into direct contact with food.	

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
686	61390	0037353-59-6	hydroxymethylcellulose	yes	no	no				
687	13530	0038103-06-9	2,2-bis(4-hydroxyphenyl)propane bis(phthalic anhydride)	no	yes	no	0,05			
	13614									
688	92560	0038613-77-3	tetrakis(2,4-di-tert-butyl-phenyl)-4,4'-biphenylene diphosphonite	yes	no	yes	18			
689	95280	0040601-76-1	1,3,5-tris(4-tert-butyl-3-hydroxy-2,6-dimethylbenzyl)-1,3,5-triazine-2,4,6(1H,3H,5H)-trione	yes	no	yes	6			
690	92880	0041484-35-9	thiodiethanol bis(3-(3,5-di-tert-butyl-4-hydroxy phenyl) propionate)	yes	no	yes	2,4			
691	13600	0047465-97-4	3,3-bis(3-methyl-4-hydroxyphenyl)2-indolinone	no	yes	no	1,8			
692	52320	0052047-59-3	2-(4-dodecylphenyl)indole	yes	no	yes	0,06			
693	88160	0054140-20-4	sorbitan tripalmitate	yes	no	no				
694	21400	0054276-35-6	methacrylic acid, sulphopropyl ester	no	yes	no	0,05			(1)
695	67520	0054849-38-6	monomethyltin tris(isooctyl mercaptoacetate)	yes	no	no		(9)		
696	92205	0057569-40-1	terephthalic acid, diester with 2,2'-methylenebis(4-methyl-6-tert-butylphenol)	yes	no	no				
697	67515	0057583-34-3	monomethyltin tris(ethylhexyl mercaptoacetate)	yes	no	no		(9)		
698	49595	0057583-35-4	dimethyltin bis(ethylhexyl mercaptoacetate)	yes	no	no		(9)		

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
699	90720	0058446-52-9	stearoylbenzoylmethane	yes	no	no				
700	31520	0061167-58-6	acrylic acid, 2-tert-butyl-6-(3-tert-butyl-2-hydroxy-5-methylbenzyl)-4-methylphenyl ester	yes	no	yes	6			
701	40160	0061269-61-2	N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine-1,2-dibromoethane, copolymer	yes	no	no	2,4			
702	87920	0061752-68-9	sorbitan tetrastearate	yes	no	no				
703	17170	0061788-47-4	fatty acids, coco	no	yes	no				
704	77600	0061788-85-0	polyethyleneglycol ester of hydrogenated castor oil	yes	no	no				
705	10599/90A 10599/91	0061788-89-4	acids, fatty, unsaturated (C ₁₈), dimers, non hydrogenated, distilled and non-distilled	no	yes	no		(18)		(1)
706	17230	0061790-12-3	fatty acids, tall oil	no	yes	no				
707	46375	0061790-53-2	diatomaceous earth	yes	no	no				
708	77520	0061791-12-6	polyethyleneglycol ester of castor oil	yes	no	no	42			
709	87520	0062568-11-0	sorbitan monobehenate	yes	no	no				
710	38700	0063397-60-4	bis(2-carbobutoxyethyl)tin-bis(isooctyl mercaptoacetate)	yes	no	yes	18			

▼ B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
711	42000	0063438-80-2	(2-carbobutoxyethyl)tin-tris(isooctyl mercaptoacetate)	yes	no	yes	30			
712	42960	0064147-40-6	castor oil, dehydrated	yes	no	no				

▼ M6

713	43480	0064365-11-3	charcoal, activated	yes	no	no			Only for use in PET at maximum 10 mg/kg of polymer. Same purity requirements as for Vegetable Carbon (E 153) set out by Commission Regulation (EU) No 231/2012 ⁽⁴⁾ with exception of ash content which can be up to 10 % (w/w).	
		0007440-44-0								

▼ B

714	84400	0064365-17-9	rosin, hydrogenated, ester with pentaerythritol	yes	no	no				
715	46880	0065140-91-2	3,5-di-tert-butyl-4-hydroxybenzyl-phosphonic acid, monoethyl ester, calcium salt	yes	no	no	6			
716	60800	0065447-77-0	1-(2-hydroxyethyl)-4-hydroxy-2,2,6,6-tetramethyl piperidine-succinic acid, dimethyl ester, copolymer	yes	no	no	30			
717	84210	0065997-06-0	rosin, hydrogenated	yes	no	no				
718	84240	0065997-13-9	rosin, hydrogenated, ester with glycerol	yes	no	no				
719	65920	0066822-60-4	N-methacryloyloxyethyl-N,N-dimethyl-N-carboxymethyl-ammonium chloride, sodium salt -octadecyl methacrylate-ethyl methacrylate-cyclohexyl methacrylate-N-vinyl-2-pyrrolidone, copolymers	yes	no	no				

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
720	67360	0067649-65-4	mono-n-dodecyltin tris(isooctyl mercaptoacetate)	yes	no	no		(25)		
721	46800	0067845-93-6	3,5-di-tert-butyl-4-hydroxybenzoic acid, hexadecyl ester	yes	no	no				
722	17200	0068308-53-2	fatty acids, soya	no	yes	no				
723	88880	0068412-29-3	starch, hydrolysed	yes	no	no				
724	24903	0068425-17-2	syrups, hydrolysed starch, hydrogenated	no	yes	no			In compliance with the purity criteria for maltitol syrup E 965(ii) as laid down in Commission Directive 2008/60/EC ⁽⁵⁾	
▼ <u>M6</u>										
▼ <u>B</u>										
726	83599	0068442-12-6	reaction products of oleic acid, 2-mercaptoethyl ester, with dichlorodimethyltin, sodium sulphide and trichloromethyltin	yes	no	yes		(9)		
727	43360	0068442-85-3	cellulose, regenerated	yes	no	no				

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
728	75100	0068515-48-0 0028553-12-0	phthalic acid, diesters with primary, saturated C ₈ -C ₁₀ branched alcohols, more than 60 % C ₉	yes	no	no		(26) (32)	Only to be used as: (a) plasticiser in repeated use materials and articles; (b) plasticiser in single-use materials and articles contacting non-fatty foods except for infant formulae and follow-on formulae as defined by Directive 2006/141/EC or processed cereal-based foods and baby foods for infants and young children as defined by Directive 2006/125/EC; (c) technical support agent in concentrations up to 0,1 % in the final product.	(7)
729	75105	0068515-49-1 0026761-40-0	phthalic acid, diesters with primary, saturated C ₉ -C ₁₁ alcohols more than 90 % C ₁₀	yes	no	no		(26) (32)	Only to be used as: (a) plasticiser in repeated use materials and articles; (b) plasticiser in single-use materials and articles contacting non-fatty foods except for infant formulae and follow-on formulae as defined by Directive 2006/141/EC or processed cereal-based foods and baby foods for infants and young children as defined by Directive 2006/125/EC; (c) technical support agent in concentrations up to 0,1 % in the final product.	(7)

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
730	66930	0068554-70-1	methylsilsesquioxane	yes	no	no			Residual monomer in methylsil-sesquioxane: < 1 mg methyl-trimethoxysilane/kg of methylsil-sesquioxane	
731	18220	0068564-88-5	N-heptylaminoundecanoic acid	no	yes	no	0,05			(2)
732	45450	0068610-51-5	<i>p</i> -cresol-dicyclopentadiene-isobutylene, copolymer	yes	no	yes	5			
733	10599/92A 10599/93	0068783-41-5	acids, fatty, unsaturated (C ₁₈), dimers, hydrogenated, distilled and non-distilled	no	yes	no		(18)		(1)
734	46380	0068855-54-9	diatomaceous earth, soda ash flux-calcined	yes	no	no				
735	40120	0068951-50-8	bis(polyethyleneglycol)hydroxy-methylphosphonate	yes	no	no	0,6			
736	50960	0069226-44-4	di-n-octyltin ethyleneglycol bis(mercaptoacetate)	yes	no	no		(10)		
737	77370	0070142-34-6	polyethyleneglycol-30 dipolyhydroxystearate	yes	no	no				
738	60320	0070321-86-7	2-[2-hydroxy-3,5-bis(1,1-dimethylbenzyl)phenyl]benzo-triazole	yes	no	yes	1,5			
739	70000	0070331-94-1	2,2'-oxamidobis[ethyl-3-(3,5-di-tert-butyl-4-hydroxyphenyl)-propionate]	yes	no	no				

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
740	81200	0071878-19-8	poly[6-[(1,1,3,3-tetramethylbutyl)amino]-1,3,5-triazine-2,4-diyl]-[(2,2,6,6-tetramethyl-4-piperidyl)-imino]hexamethylene[(2,2,6,6-tetramethyl-4-piperidyl) imino]	yes	no	yes	3			
741	24070	0073138-82-6	resin acids and rosin acids	yes	yes	no				
	83610									
742	92700	0078301-43-6	2,2,4,4-tetramethyl-20-(2,3-epoxypropyl)-7-oxa-3,20-diazadispiro[5.1.1.1.2]-heneicosan-21-one, polymer	yes	no	yes	5			
743	38950	0079072-96-1	bis(4-ethylbenzylidene)sorbitol	yes	no	no				
▼ <u>M12</u>										
744	18888	080181-31-3	3-hydroxybutanoic acid-3-hydroxypentanoic acid, copolymer	no	yes	no		(35)	The substance is used as product obtained by bacterial fermentation. In compliance with the specifications mentioned in the Table 4 of Annex I.	
▼ <u>B</u>										
745	68145	0080410-33-9	2,2',2'-nitriolo(triethyl tris(3,3',5,5'-tetra-tert-butyl-1,1'-bi-phenyl-2,2'-diyl)phosphite)	yes	no	yes	5		SML expressed as sum of phosphite and phosphate	
746	38810	0080693-00-1	bis(2,6-di-tert-butyl-4-methylphenyl)pentaerythritol diphosphite	yes	no	yes	5		SML expressed as sum of phosphite and phosphate	
747	47600	0084030-61-5	di-n-dodecyltin bis(isooctyl mercaptoacetate)	yes	no	yes		(25)		

▼ **B**

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
748	12765	0084434-12-8	N-(2-aminoethyl)- β -alanine, sodium salt	no	yes	no	0,05			
749	66360	0085209-91-2	2,2'-methylene bis(4,6-di-tert-butylphenyl) sodium phosphate	yes	no	yes	5			
750	66350	0085209-93-4	2,2'-methylenebis(4,6-di-tert-butylphenyl) lithium phosphate	yes	no	no	5			
751	81515	0087189-25-1	poly(zinc glycerolate)	yes	no	no				

▼ **M7**

752	39890	0087826-41-3 0069158-41-4 0054686-97-4 0081541-12-0	bis(methylbenzylidene)sorbitol	yes	no	no				
-----	-------	--	--------------------------------	-----	----	----	--	--	--	--

▼ **B**

753	62800	0092704-41-1	kaolin, calcined	yes	no	no				
754	56020	0099880-64-5	glycerol dibehenate	yes	no	no				
755	21765	0106246-33-7	4,4'-methylenebis(3-chloro-2,6-diethylaniline)	no	yes	no	0,05			(1)
756	40020	0110553-27-0	2,4-bis(octylthiomethyl)-6-methylphenol	yes	no	yes		(24)		
757	95725	0110638-71-6	vermiculite, reaction product with citric acid, lithium salt	yes	no	no				
758	38940	0110675-26-8	2,4-bis(dodecylthiomethyl)-6-methylphenol	yes	no	yes		(24)		
759	54300	0118337-09-0	2,2'-ethylidenebis(4,6-di-tert-butylphenyl) fluorophosphonite	yes	no	yes	6			

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
760	83595	0119345-01-6	reaction product of di-tert-butylphosphonite with biphenyl, obtained by condensation of 2,4-di-tert-butylphenol with Friedel Craft reaction product of phosphorous trichloride and biphenyl	yes	no	no	18		<p>Composition:</p> <ul style="list-style-type: none"> — 4,4'-biphenylene-bis[0,0-bis(2,4-di-tert-butylphenyl)phosphonite] (CAS No 0038613-77-3) (36-46 % w/w (*)), — 4,3'-biphenylene-bis[0,0-bis(2,4-di-tert-butylphenyl)phosphonite] (CAS No 0118421-00-4) (17-23 % w/w (*)), — 3,3'-biphenylene-bis[0,0-bis(2,4-di-tert-butylphenyl)phosphonite] (CAS No 0118421-01-5) (1-5 % w/w (*)), — 4-biphenylene-0,0-bis(2,4-di-tert-butylphenyl)phosphonite (CAS No 0091362-37-7) (11-19 % w/w (*)), — tris(2,4-di-tert-butylphenyl)phosphite (CAS No 0031570-04-4) (9-18 % w/w (*)), — 4,4'-biphenylene-0,0-bis(2,4-di-tert-butylphenyl)phosphonate-0,0-bis(2,4-di-tert-butylphenyl)phosphonite (CAS No 0112949-97-0) (< 5 % w/w (*)) <p>(*) Quantity of substance used/quantity of formulation</p> <p>Other specifications:</p> <ul style="list-style-type: none"> — Phosphor content of min. 5,4 % to max. 5,9 %, — Acid value of max. 10 mg KOH per gram, — Melt range of 85– 110 °C, 	

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
761	92930	0120218-34-0	thiodiethanolbis(5-methoxycarbonyl-2,6-dimethyl-1,4-dihydropyridine-3-carboxylate)	yes	no	no	6			
762	31530	0123968-25-2	acrylic acid, 2,4-di-tert-pentyl-6-(1-(3,5-di-tert-pentyl-2-hydroxyphenyl)ethyl)phenyl ester	yes	no	yes	5			
763	39925	0129228-21-3	3,3-bis(methoxymethyl)-2,5-dimethylhexane	yes	no	yes	0,05			
764	13317	0132459-54-2	N,N'-bis[4-(ethoxycarbonyl)phenyl]-1,4,5,8-naphthalenetetracarboxydiimide	no	yes	no	0,05		Purity > 98,1 % (w/w). Only to be used as co-monomer (max 4 %) for polyesters (PET, PBT).	
765	49485	0134701-20-5	2,4-dimethyl-6-(1-methylpentadecyl)phenol	yes	no	yes	1			
766	38879	0135861-56-2	bis(3,4-dimethylbenzylidene)sorbitol	yes	no	no				
767	38510	0136504-96-6	1,2-bis(3-aminopropyl)ethylenediamine, polymer with N-butyl-2,2,6,6-tetramethyl-4-piperidamine and 2,4,6-trichloro-1,3,5-triazine	yes	no	no	5			
768	34850	0143925-92-2	amines, bis(hydrogenated tallow alkyl) oxidised	yes	no	no			Not to be used for articles in contact with fatty foods for which ►M7 simulant D1 and/or D2 ◀ is laid down. Only to be used in: (a) polyolefins at 0,1 % (w/w) concentration and in (b) PET at 0,25 % (w/w) concentration.	(1)
769	74010	0145650-60-8	phosphorous acid, bis(2,4-di-tert-butyl-6-methylphenyl) ethyl ester	yes	no	yes	5		SML expressed as sum of phosphite and phosphate	
770	51700	0147315-50-2	2-(4,6-diphenyl-1,3,5-triazin-2-yl)-5-(hexyloxy)phenol	yes	no	no	0,05			

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
771	34650	0151841-65-5	aluminium hydroxybis [2,2'-methylenebis (4,6-di-tert-butylphenyl) phosphate]	yes	no	no	5			
772	47500	0153250-52-3	N,N'-dicyclohexyl-2,6-naphthalene dicarboxamide	yes	no	no	5			
773	38840	0154862-43-8	bis(2,4-dicumylphenyl)pentaerythritol-diphosphate	yes	no	yes	5		SML expressed as sum of the substance itself, its oxidised form bis(2,4-dicumylphenyl)pentaerythritol-phosphate and its hydrolysis product (2,4-dicumylphenol)	
774	95270	0161717-32-4	2,4,6-tris(tert-butyl)phenyl-2-butyl-2-ethyl-1,3-propanediol phosphite	yes	no	yes	2		SML expressed as sum of phosphite, phosphate and the hydrolysis product = TTBP	
775	45705	0166412-78-8	1,2-cyclohexanedicarboxylic acid, diisononyl ester	yes	no	no		(32)		
776	76723	0167883-16-1	polydimethylsiloxane, 3-aminopropyl terminated, polymer with dicyclohexylmethane-4,4'-diisocyanate	yes	no	no			The fraction with molecular weight below 1 000 Da ►M7 shall ◀ not exceed 1,5 % (w/w)	
777	31542	0174254-23-0	acrylic acid, methyl ester, telomer with 1-dodecanethiol, C ₁₆ -C ₁₈ alkyl esters	yes	no	no			0,5 % in final product	(1)
778	71670	0178671-58-4	pentaerythritol tetrakis (2-cyano-3,3-diphenylacrylate)	yes	no	yes	0,05			
779	39815	0182121-12-6	9,9-bis(methoxymethyl)fluorene	yes	no	yes	0,05			►M8 ◀

▼M7

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
780	81220	0192268-64-7	poly-[[6-[N-(2,2,6,6-tetramethyl-4-piperidiny)-n-butylamino]-1,3,5-triazine-2,4-diyl][(2,2,6,6-tetramethyl-4-piperidiny)imino]-1,6-hexanediy][(2,2,6,6-tetramethyl-4-piperidiny)imino]]-α-[N,N,N',N'-tetrabutyl-N''-(2,2,6,6-tetramethyl-4-piperidiny)-N''-[6-(2,2,6,6-tetramethyl-4-piperidiny-lamino)-hexyl]-[1,3,5-triazine-2,4,6-triamine]-ω-N,N,N',N'-tetrabutyl-1,3,5-triazine-2,4-diamine]	yes	no	no	5			
781	95265	0227099-60-7	1,3,5-tris(4-benzoylphenyl) benzene	yes	no	no	0,05			
782	76725	0661476-41-1	polydimethylsiloxane, 3-aminopropyl terminated, polymer with 1-isocyanato-3-isocyanatomethyl-3,5,5-trimethylcyclohexane	yes	no	no			The fraction with molecular weight below 1 000 Da ► M7 shall ◀ not exceed 1 % (w/w)	
783	55910	0736150-63-3	glycerides, castor-oil mono-, hydrogenated, acetates	yes	no	no		(32)		
▼ <u>M6</u>										
784	95420	0745070-61-5	1,3,5-tris (2,2-di-methylpropanamido) benzene	yes	no	no	5			
▼ <u>B</u>										
785	24910	0000100-21-0	terephthalic acid	no	yes	no		(28)		
786	14627	0000117-21-5	3-chlorophthalic anhydride	no	yes	no	0,05		SML expressed as 3-chlorophthalic acid	
787	14628	0000118-45-6	4-chlorophthalic anhydride	no	yes	no	0,05		SML expressed as 4-chlorophthalic acid	
788	21498	0002530-85-0	[3-(methacryloxy)propyl]trimethoxysilane	no	yes	no	0,05		Only to be used as a surface treatment agent of inorganic fillers	(1) (11)

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
789	60027	—	hydrogenated homopolymers and/or copolymers made of 1-hexene and/or 1-octene and/or 1-decene and/or 1-dodecene and/or 1-tetradecene (Mw: 440–12 000)	yes	no	no			Average molecular weight not less than 440 Da. Viscosity at 100 °C not less than 3,8 cSt ($3,8 \times 10^{-6} \text{ m}^2/\text{s}$).	(2)
790	80480	0090751-07-8 0082451-48-7	poly(6-morpholino-1,3,5-triazine-2,4-diyl)-[(2,2,6,6-tetramethyl-4-piperidyl)imino] hexa-methylene-[(2,2,6,6-tetramethyl-4-piperidyl)imino]	yes	no	no	5		Average molecular weight not less than 2 400 Da. Residual content of morpholine $\leq 30 \text{ mg/kg}$, of N,N'-bis(2,2,6,6-tetramethylpiperidin-4-yl)hexane-1,6-diamine $< 15 000 \text{ mg/kg}$, and of 2,4-dichloro-6-morpholino-1,3,5-triazine $\leq 20 \text{ mg/kg}$.	(16)
791	92470	0106990-43-6	N,N',N'',N'''-tetrakis(4,6-bis(N-butyl-(N-methyl-2,2,6,6-tetramethylpiperidin-4-yl)amino)triazin-2-yl)-4,7-diazadecane-1,10-diamine	yes	no	no	0,05			
792	92475	0203255-81-6	3,3',5,5'-tetrakis(tert-butyl)-2,2'-dihydroxybiphenyl, cyclic ester with [3-(3-tert-butyl-4-hydroxy-5-methylphenyl)propyl]oxyphosphonous acid	yes	no	yes	5		SML expressed as the sum of phosphite and phosphate form of the substance and the hydrolysis products	
793	94000	0000102-71-6	triethanolamine	yes	no	no	0,05		SML expressed as the sum of triethanolamine and the hydrochloride adduct expressed as triethanolamine	
794	18117	0000079-14-1	glycolic acid	no	yes	no			Only to be used for manufacture of polyglycolic acid (PGA) for (i) indirect food contact behind polyesters such as polyethylene terephthalate (PET) or polylactic acid (PLA); and (ii) direct food contact of a blend of PGA up to 3 % w/w in PET or PLA.	

▼M2

▼ **B**

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
795	40155	0124172-53-8	N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)-N,N'-diformylhexamethylenediamine	yes	no	no	0,05			(2) (12)
796	72141	0018600-59-4	2,2'-(1,4-phenylene)bis[4H-3,1-benzoxazin-4-one]	yes	no	yes	0,05		SML including the sum of its hydrolysis products	
▼ M2										
797	76807	0073018-26-5	polyester of adipic acid with 1,3-butanediol, 1,2-propanediol and 2-ethyl-1-hexanol	yes	no	yes		(31) (32)		
▼ B										
798	92200	0006422-86-2	terephthalic acid, bis(2-ethylhexyl)ester	yes	no	no	60	(32)		
▼ M6										
799	77708		polyethyleneglycol (EO = 1-50) ethers of linear and branched primary (C ₈ -C ₂₂) alcohols	yes	no	no	1,8		In compliance with the maximum ethylene oxide content as laid down in the purity criteria for food additives in Commission Regulation (EU) No 231/2012.	
▼ B										
800	94425	0000867-13-0	triethyl phosphonoacetate	yes	no	no			Only for use in PET	
801	30607	—	acids, C ₂ -C ₂₄ , aliphatic, linear, monocarboxylic, from natural oils and fats, lithium salt	yes	no	no				
802	33105	0146340-15-0	alcohols, C ₁₂ -C ₁₄ secondary, β-(2-hydroxyethoxy), ethoxylated	yes	no	no	5			(12)
803	33535	0152261-33-1	α-alkenes(C ₂₀ -C ₂₄) copolymer with maleic anhydride, reaction product with 4-amino-2,2,6,6-tetramethylpiperidine	yes	no	no			Not to be used for articles in contact with fatty foods for which ► M7 simulant D1 and/or D2 ◀ is laid down. Not to be used in contact with alcoholic foods.	(13)

▼**B**

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
804	80510	1010121-89-7	poly(3-nonyl-1,1-dioxo-1-thio-propane-1,3-diyl)-block-poly(x-oleyl-7-hydroxy-1,5-diimi-nooctane-1,8-diyl), process mixture with x = 1 and/or 5, neutralised with dodecylbenzene-sulfonic acid	yes	no	no			Only to be used as polymer production aid in polyethylene (PE), polypropylene (PP) and polystyrene (PS)	
805	93450	—	titanium dioxide, coated with a copolymer of n-octyltrichlorosilane and [aminotris(methylenephosphonic acid), penta sodium salt]	yes	no	no			The content of the surface treatment copolymer of the coated titanium dioxide is less than 1 % w/w	
806	14876	0001076-97-7	1,4-cyclohexanedicarboxylic acid	no	yes	no	5		Only to be used for manufacture of polyesters	
▼ M3										
807	93485	—	titanium nitride, nanoparticles	yes	no	no			No migration of titanium nitride nanoparticles. Only to be used in polyethylene terephthalate (PET) up to 20 mg/kg. In the PET, the agglomerates have a diameter of 100-500 nm consisting of primary titanium nitride nanoparticles; primary particles have a diameter of approximately 20 nm.	
▼ B										
808	38550	0882073-43-0	bis(4-propylbenzylidene)propylsorbitol	yes	no	no	5		SML including the sum of its hydrolysis products	
809	49080	0852282-89-4	N-(2,6-diisopropylphenyl)-6-[4-(1,1,3,3-tetramethylbutyl)phenoxy]-1H-benzo[de]isoquinolin-1,3(2H)-dione	yes	no	yes	0,05		Only for use in PET	(6) (14) (15)
810	68119		neopentyl glycol, diesters and monoesters with benzoic acid and 2-ethylhexanoic acid	yes	no	no	5	(32)	Not to be used for articles in contact with fatty foods for which ► M7 simulant D1 and/or D2 ◀ is laid down.	

▼ B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
811	80077	0068441-17-8	polyethylene waxes, oxidised	yes	no	no	60			

▼ M2

812	80350	0124578-12-7	poly(12-hydroxystearic acid)-polyethyleneimine copolymer	yes	no	no			Only to be used in plastics up to 0,1 % w/w. Prepared by the reaction of poly(12-hydroxystearic acid) with polyethyleneimine.	
-----	-------	--------------	--	-----	----	----	--	--	--	--

▼ B

813	91530	—	sulphosuccinic acid alkyl (C ₄ -C ₂₀) or cyclohexyl diesters, salts	yes	no	no	5			
814	91815	—	sulphosuccinic acid monoalkyl (C ₁₀ -C ₁₆) polyethyleneglycol esters, salts	yes	no	no	2			
815	94985	—	trimethylolpropane, mixed triesters and diesters with benzoic acid and 2-ethylhexanoic acid	yes	no	no	5	(32)	Not to be used for articles in contact with fatty foods for which ► <u>M7</u> simulant D1 and/or D2 ◀ is laid down	
816	45704	—	cis-1,2-cyclohexanedicarboxylic acid, salts	yes	no	no	5			
817	38507	—	cis-endo-bicyclo[2.2.1]heptane-2,3-dicarboxylic acid, salts	yes	no	no	5		Not to be used with polyethylene in contact with acidic foods. Purity ≥ 96 %.	
818	21530	—	methallylsulphonic acid, salts	no	yes	no	5			
819	68110	—	neodecanoic acid, salts	yes	no	no	0,05		Not to be used in polymers contacting fatty foods. Not to be used for articles in contact with fatty foods for which ► <u>M7</u> simulant D1 and/or D2 ◀ is laid down. SML expressed as neodecanoic acid.	

▼ B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
820	76420	—	pimelic acid, salts	yes	no	no				
821	90810	—	stearoyl-2-lactylic acid, salts	yes	no	no				

▼ M11

822	71938		Perchloric acid, salts	yes	no	no	0,002			(4)
-----	-------	--	------------------------	-----	----	----	-------	--	--	-----

▼ B

823	24889	—	5-Sulphoisophthalic acid, salts	no	yes	no	5			
-----	-------	---	---------------------------------	----	-----	----	---	--	--	--

854	71943	0329238-24-6	perfluoro acetic acid, α -substituted with the copolymer of perfluoro-1,2-propylene glycol and perfluoro-1,1-ethylene glycol, terminated with chlorohexafluoropropoxy groups	yes	no	no			Only to be used in concentrations up to 0,5 % w/w in the polymerisation of fluoropolymers that are processed at temperatures at or above 340 °C and are intended for use in repeated use articles	
-----	-------	--------------	---	-----	----	----	--	--	---	--

▼ M2

855	40560		(butadiene, styrene, methyl methacrylate) copolymer cross-linked with 1,3-butanediol dimethacrylate	yes	no	no			Only to be used in rigid poly(vinyl chloride) (PVC) at a maximum level of 12 % at room temperature or below.	
-----	-------	--	---	-----	----	----	--	--	--	--

▼ M9

856	40563	25101-28-4	(butadiene, styrene, methyl methacrylate, butyl acrylate) copolymer cross-linked with divinylbenzene or 1,3-butanediol dimethacrylate	yes	no	no			Only to be used in: — rigid poly(vinyl chloride) (PVC) at a maximum level of 12 % at room temperature or below; or — at up to 40 % w/w in blends of styrene acrylonitrile copolymer (SAN)/ poly(methyl methacrylate) (PMMA) repeat-use articles at room temperature or below, and when either in contact only with aqueous, acidic and/ or low alcoholic (< 20 %) foodstuffs for less than 1 day,	
-----	-------	------------	---	-----	----	----	--	--	---	--

▼ M9

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
									or when in contact only with dry foodstuffs for any duration of time.	
▼ <u>M2</u>	857	66765	0037953-21-2	(methyl methacrylate, butyl acrylate, styrene, glycidyl methacrylate) copolymer	yes	no	no		Only to be used in rigid poly(vinyl chloride) (PVC) at a maximum level of 2 % at room temperature or below.	
▼ <u>M3</u> ▼ <u>C1</u>	858	38565	0090498-90-1	3,9-bis[2-(3-(3-tert-butyl-4-hydroxy-5-methylphenyl)propionyloxy)-1,1-dimethylethyl]-2,4,8,10-tetraoxaspiro[5,5]undecane	yes	no	yes	0,05	SML expressed as the sum of the substance and its oxidation product 3-[(3-(3-tert-butyl-4-hydroxy-5-methylphenyl)prop-2-enoyloxy)-1,1-dimethylethyl]-9-[(3-(3-tert-butyl-4-hydroxy-5-methylphenyl)propionyloxy)-1,1-dimethylethyl]-2,4,8,10-tetraoxaspiro[5,5]-undecane in equilibrium with its para quinone methid tautomer.	(2)
▼ <u>M6</u>	859			(butadiene, ethyl acrylate, methyl methacrylate, styrene) copolymer crosslinked with divinylbenzene, in nanoform	yes	no	no		Only to be used as particles in non-plasticised PVC up to 10 % w/w in contact with all food types at room temperature or below including long-term storage. When used together with the substance with FCM No 998 and/or the substance with FCM No 1043, the restriction of 10 % w/w applies to the sum of those substances. The diameter of particles shall be > 20 nm, and for at least 95 % by number it shall be > 40 nm.	

▼B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
860	71980	0051798-33-5	perfluoro[2-(poly(n-propoxy))propanoic acid]	yes	no	no			Only to be used in the polymerisation of fluoropolymers that are processed at temperatures at or above 265 °C and are intended for use in repeated use articles	
861	71990	0013252-13-6	perfluoro[2-(n-propoxy)propanoic acid]	yes	no	no			Only to be used in the polymerisation of fluoropolymers that are processed at temperatures at or above 265 °C and are intended for use in repeated use articles	
▼ <u>M2</u>										
862	15180	0018085-02-4	3,4-diacetoxy-1-butene	no	yes	no	0,05		SML including the hydrolysis product 3,4-dihydroxy-1-butene Only to be used as a co-monomer for ethylvinylalcohol (EVOH) and polyvinylalcohol (PVOH) copolymers.	(17) (19)
863	15260	0000646-25-3	1,10-decanediamine	no	yes	no	0,05		Only to be used as a co-monomer for manufacturing polyamide articles for repeated use in contact with aqueous, acidic and dairy foodstuffs at room temperature or for short term contact up to 150 °C.	
▼ <u>B</u>										
864	46330	0000056-06-4	2,4-diamino-6-hydroxypyrimidine	yes	no	no	5		Only to be used in rigid poly(vinyl chloride) (PVC) in contact with non-acidic and non-alcoholic aqueous food	

▼ B

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)	
▼ <u>M3</u>	865	40619	0025322-99-0	(butyl acrylate, methyl methacrylate, butyl methacrylate) copolymer	yes	no	no			Only to be used in: (a) rigid poly(vinyl chloride) (PVC) at a maximum level of 1 % w/w; (b) polylactic acid (PLA) at a maximum level of 5 % w/w.	
▼ <u>B</u>	866	40620	—	(butyl acrylate, methyl methacrylate) copolymer, cross-linked with allyl methacrylate	yes	no	no			Only to be used in rigid poly(vinyl chloride) (PVC) at a maximum level of 7 %	
	867	40815	0040471-03-2	(butyl methacrylate, ethyl acrylate, methyl methacrylate) copolymer	yes	no	no			Only to be used in rigid poly(vinyl chloride) (PVC) at a maximum level of 2 %	
▼ <u>M3</u>	868	53245	0009010-88-2	(ethyl acrylate, methyl methacrylate) copolymer	yes	no	no			Only to be used in: (a) rigid poly(vinyl chloride) (PVC) at a maximum level of 2 % w/w; (b) polylactic acid (PLA) at a maximum level of 5 % w/w; (c) polyethylene terephthalate (PET) at a maximum level of 5 % w/w.	
▼ <u>B</u>	869	66763	0027136-15-8	(butyl acrylate, methyl methacrylate, styrene) copolymer	yes	no	no			Only to be used in rigid poly(vinyl chloride) (PVC) at a maximum level of 3 %	
	870	95500	0160535-46-6	N,N',N''-tris(2-methylcyclohexyl)-1,2,3-propane-tricarboxamide	yes	no	no	5			

▼ **B**▼ **M7**▼ **M4**▼ **M2**▼ **M3**▼ **B**

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
871		0287916-86-3	dodecanoic acid, 12-amino-, polymer with ethene, 2,5-furandione, α -hydro- ω -hydroxypoly (oxy-1,2-ethanediyl) and 1-propene	yes	no	no			Only to be used in polyolefins at levels of up to 20 weight %. These polyolefins shall only be used in contact with foods for which Table 2 of Annex III assigns food simulant E, at ambient temperature or below, and when migration of the total oligomeric fraction of less than 1 000 Da does not exceed 50 μ g/kg food.	(23)
872		0006607-41-6	2-phenyl-3,3-bis(4-hydroxyphenyl)phthalimidine	no	yes	no	0,05		To be used only as a co-monomer in polycarbonate copolymers	(20)
873	93460		titanium dioxide reacted with octyltriethoxysilane	yes	no	no			Reaction product of titanium dioxide with up to 2 % w/w surface treatment substance octyltriethoxysilane, processed at high temperatures.	
874	16265	0156065-00-8	α -dimethyl-3-(4'-hydroxy-3'-methoxyphenyl)propylsilyloxy, ω -3-dimethyl-3-(4'-hydroxy-3'-methoxyphenyl)propylsilyl polydimethylsiloxane	no	yes	no	0,05	(33)	Only to be used as comonomer in siloxane modified polycarbonate. The oligomeric mixture shall be characterised by the formula $C_{24}H_{38}Si_2O_5(SiOC_2H_6)_n$ ($50 > n \geq 26$).	
875	80345	0058128-22-6	poly(12-hydroxystearic acid) stearate	yes	no	yes	5			

▼ **B**

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
878	31335	—	acids, fatty (C ₈ -C ₂₂) from animal or vegetable fats and oils, esters with branched alcohols, aliphatic, monohydric, saturated, primary (C ₃ -C ₂₂)	yes	no	no				
879	31336	—	acids, fatty (C ₈ -C ₂₂) from animal or vegetable fats and oils, esters with alcohols, linear, aliphatic, monohydric, saturated, primary (C ₁ -C ₂₂)	yes	no	no				

▼ **M6**

880	31348		acids, fatty (C ₈ -C ₂₂), esters with pentaerythritol'	yes	no	no				
881	25187	0003010-96-6	2,2,4,4-tetramethylcyclobutane-1,3-diol	no	yes	no	5		Only for: (a) repeated use articles for long term storage at room temperature or below and hotfill; (b) single use materials and articles as a co-monomer at a maximum use level of 35 mole % of the diol component of polyesters, and if such materials and articles are for long term storage at room temperature or below of food types which have an alcohol content of up to 10 % and for which Table 2 of Annex III does not assign simulant D2. Hot fill conditions are allowed for such single use materials and articles.	

▼**B**

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
882	25872	0002416-94-6	2,3,6-trimethylphenol	no	yes	no	0,05			
883	22074	0004457-71-0	3-methyl-1,5-pentanediol	no	yes	no	0,05		Only to be used in materials in contact with food at a surface to mass ratio up to 0,5 dm ² /kg	
884	34240	0091082-17-6	alkyl(C ₁₀ -C ₂₁)sulphonic acid, esters with phenol	yes	no	no	0,05		Not to be used for articles in contact with fatty foods for which ► M7 simulant D1 and/or D2 ◀ is laid down.	
885	45676	0263244-54-8	cyclic oligomers of (butylene terephthalate)	yes	no	no			Only to be used in poly(ethylene terephthalate) (PET), poly(butylene terephthalate) (PBT), polycarbonate (PC), polystyrene (PS) and rigid poly(vinyl chloride) (PVC) plastics in concentrations up to 1 % w/w, in contact with aqueous, acidic and alcoholic foods, for long term storage at room temperature.	
▼ M2										
894	93360	0016545-54-3	thiodipropionic acid, ditetradecyl ester	yes	no	no		(14)		
895	47060	0171090-93-0	3-(3,5-di-tert-butyl-4-hydroxyphenyl)propanoic acid, esters with C13-C15 branched and linear alcohols	yes	no	no	0,05		Only to be used in polyolefins in contact with foods other than fatty/high-alcoholic and dairy products.	

▼ M2

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
896	71958	0958445-44-8	3H-perfluoro-3-[(3-methoxypropoxy)propanoic acid], ammonium salt	yes	no	no			Only to be used in the polymerisation of fluoropolymers when: <ul style="list-style-type: none"> — processed at temperatures higher than 280 °C for at least 10 minutes, — processed at temperatures higher than 190 °C up to 30 % w/w for use in blends with polyoxymethylene polymers and intended for repeated use articles. 	

▼ M3

902		0000128-44-9	1,2-benzisothiazol-3(2H)-one 1,1-dioxide, sodium salt	yes	no	no			The substance shall comply with the specific purity criteria as set out in Commission Regulation (EU) No 231/2012 ⁽⁸⁾ .	
-----	--	--------------	---	-----	----	----	--	--	--	--

▼ M6

903		37486-69-4	2H-perfluoro-[(5,8,11,14-tetramethyl)-tetraethyleneglycol ethyl propyl ether]	yes	no	no			Only to be used as a polymer production aid in the polymerisation of fluoropolymers intended for: <ul style="list-style-type: none"> (a) repeated and single use materials and articles when sintered or processed (non-sintered) at temperatures at or above 360 °C for at least 10 minutes or at higher temperatures for equivalent shorter times; (b) repeated use materials and articles when processed (non-sintered) at temperatures from 300 °C and up to 360 °C for at least 10 minutes. 	
-----	--	------------	---	-----	----	----	--	--	--	--

▼ M2

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
923	39150	0000120-40-1	N,N-bis(2-hydroxyethyl)dodecanamide	yes	no	no	5		The residual amount of diethanolamine in plastics, as an impurity and decomposition product of the substance, ► <u>M7</u> shall ◀ not result in a migration of diethanolamine higher than 0,3 mg/kg food.	(18)
924	94987		trimethylolpropane, mixed triesters and diesters with n-octanoic and n-decanoic acids	yes	no	no	0,05		Only for use in PET in contact with all types of foods other than fatty, high-alcoholic and dairy products.	
926	71955	0908020-52-0	perfluoro[(2-ethoxyethoxy)acetic acid], ammonium salt	yes	no	no			Only to be used in the polymerisation of fluoropolymers that are processed at temperatures higher than 300 °C for at least 10 minutes.	
▼ <u>M6</u>										
969		24937-78-8	ethylene-vinyl acetate copolymer wax	yes	no	no			Only to be used as a polymeric additive up to 2 % w/w in polyolefins. The migration of low molecular weight oligomeric fraction below 1 000 Da shall not exceed 5 mg/kg food.	
▼ <u>M2</u>										
971	25885	0002459-10-1	trimethyl trimellitate	no	yes	no			Only to be used as a co-monomer up to 0,35 % w/w to produce modified polyesters intended to be used in contact with aqueous and dry foodstuffs containing no free fat at the surface.	(17)

▼ **M2**

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
972	45197	0012158-74-6	copper hydroxide phosphate	yes	no	no				
973	22931	0019430-93-4	(perfluorobutyl)ethylene	no	yes	no			Only to be used as a co-monomer up to 0,1 % w/w in the polymerisation of fluoropolymers, sintered at high temperatures.	

▼ **M11**

974	74050	939402-02-5	phosphorous acid, mixed 2,4-bis(1,1- dimethylpropyl)phenyl and 4-(1,1- dimethylpropyl)phenyl triesters	yes	no	yes	10		SML expressed as the sum of the phosphite and phosphate forms of the substance, 4-tert-amylphenol and 2,4-di-tert-amylphenol. The migration of 2,4-di-tert-amylphenol shall not exceed 1 mg/kg food.	
-----	-------	-------------	--	-----	----	-----	----	--	--	--

▼ **M3**

979	79987	—	(polyethylene terephthalate, hydroxylated polybutadiene, pyromellitic anhydride) copolymer	yes	no	no			Only to be used in polyethylene terephthalate (PET) at a maximum level of 5 % w/w.	
-----	-------	---	--	-----	----	----	--	--	--	--

▼ **M4**

988		3634-83-1	1,3-bis(isocyanatomethyl)benzene	no	yes	no		(34)	SML(T) applies to the migration of its hydrolysis product, 1,3-benzenedimethanamine To be used only as co-monomer in the manufacture of a middle layer coating on a poly(ethylene terephthalate) polymer film in a multilayer film	
-----	--	-----------	----------------------------------	----	-----	----	--	------	---	--

▼ **B**▼ **M6**▼ **M8**

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
998			(butadiene, ethyl acrylate, methyl methacrylate, styrene) copolymer not cross-linked, in nanoform	yes	no	no			Only to be used as particles in non-plasticised PVC up to 10 % w/w in contact with all food types at room temperature or below including long-term storage. When used together with the substance with FCM No 859 and/ or the substance with FCM No 1043, the restriction of 10 % w/w applies to the sum of those substances. The diameter of particles shall be > 20 nm, and for at least 95 % by number it shall be > 40 nm.	
1007		976-56-7	diethyl[[3,5-bis(1,1-dimethyl-ethyl)-4-hydroxyphenyl]methyl]phosphonate	no	yes	no			Only to be used up to 0,2 % w/w based on the final polymer weight in the polymerisation process to manufacture poly(ethylene terephthalate) (PET).	
1016			(methacrylic acid, ethyl acrylate, n-butyl acrylate, methyl methacrylate and butadiene) copolymer in nanoform	yes	no	no			Only to be used up to: (a) 10 % w/w in non-plasticised PVC; (b) 15 % w/w in non-plasticised PLA. The final material shall be used at room temperature or below.	

▼ M6

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
1017		25618-55-7	polyglycerol	yes	no	no			To be processed under conditions preventing the decomposition of the substance and up to a maximum temperature of 275 °C.	

▼ M8

1030			montmorillonite clay modified by dimethyldialkyl(C16-C18)ammonium chloride	yes	no	no			<p>Only to be used up to 12 % (w/w) in polyolefins in contact with dry foods to which simulant E is assigned in table 2 of Annex III at room temperature or below.</p> <p>The sum of the specific migration of 1-chlorohexadecane and 1-chlorooctadecane shall not exceed 0,05 mg/kg food.</p> <p>Can contain platelets in the nanoform that are only in one dimension thinner than 100 nm. Such platelets shall be oriented parallel to the polymer surface and shall be fully embedded in the polymer.</p>	
------	--	--	--	-----	----	----	--	--	--	--

▼ M7

1031		3238-40-2	furan-2,5-dicarboxylic acid	no	yes	no	5		Only to be used as a monomer in the production of polyethylene furanoate. The migration of the oligomeric fraction of less than 1 000 Da shall not exceed 50 µg/kg food (expressed as furan-2,5-dicarboxylic acid).	(22) (23)
------	--	-----------	-----------------------------	----	-----	----	---	--	---	--------------

▼ M7

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
1034		3710-30-3	1,7-octadiene	no	yes	no	0,05		Only to be used as a crosslinking co-monomer in the manufacture of polyolefins for contact with any type of foods for long term storage at room temperature, including when packaged under hot-fill conditions.	

▼ M6

1043			(butadiene, ethyl acrylate, methyl methacrylate, styrene) copolymer crosslinked with 1,3-butanediol dimethacrylate, in nanoform	yes	no	no			Only to be used as particles in non-plasticised PVC up to 10 % w/w in contact with all food types at room temperature or below including long-term storage. When used together with the substance with FCM No 859 and/or the substance with FCM No 998, the restriction of 10 % w/w applies to the sum of those substances. The diameter of particles shall be > 20 nm, and for at least 95 % by number it shall be > 40 nm.	
------	--	--	---	-----	----	----	--	--	--	--

▼ M7

1045		1190931-27-1	perfluoro{acetic acid, 2-[(5-methoxy-1,3-dioxolan-4-yl)oxy]}, ammonium salt	yes	no	no			Only to be used as a polymer production aid during the manufacture of fluoropolymers under high temperature conditions of at least 370 °C.	
1046			zinc oxide, nanoparticles, coated with [3-(methacryloxy)propyl] trimethoxysilane (FCM No 788)	yes	no	no			Only to be used in unplasticised polymers. The restrictions and specifications specified for FCM substance No 788 shall be respected.	

▼ **M7**

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
1048		624-03-3	ethylene glycol dipalmitate	yes	no	no		(2)	Only to be used when produced from a fatty acid precursor that is obtained from edible fats or oils.	
1050			zinc oxide, nanoparticles, uncoated	yes	no	no			Only to be used in unplasticised polymers.	
1051		42774-15-2	N,N'-bis(2,2,6,6-tetramethyl-4-piperidinyloxy) isophthalamide	yes	no	no	5			
1052		1455-42-1	2,4,8,10-tetraoxaspiro[5,5]undecane-3,9-diethanol,β3,β3,β9,β9-tetramethyl- ('SPG')	no	yes	no	5		Only to be used as a monomer in the production of polyesters. The migration of oligomers of less than 1 000 Da shall not exceed 50 µg/kg food (expressed as SPG).	(22) (23)
1053			fatty acids, C16–18 saturated, esters with dipentaerythritol	yes	no	no			Only to be used when produced from a fatty acid precursor that is obtained from edible fats or oils	
▼ M8										
1055		7695-91-2 58-95-7	α-tocopherol acetate	yes	no	no			Only to be used as antioxidant in polyolefins.	(24)
▼ M12										
1059		147398-31-0	poly((R)-3-hydroxybutyrate-co-(R)-3-hydroxyhexanoate)	no	yes	no		(35)	Only to be used alone or blended with other polymers in contact with foods for which food simulant E is assigned in Table 2 of Annex III.	

▼ **M8**

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
1060			ground sunflower seed hulls	yes	no	no			Only to be used at room temperature or below in contact with foods for which Table 2 of Annex III assigns food simulant E. The seed hulls shall be obtained from sunflower seeds that are fit for human consumption. The processing temperature of the plastic containing the additive shall not exceed 240 °C.	
▼ M9		80512-44-3	2,4,4'-trifluorobenzophenone	no	yes	no			Only to be used as a co-monomer in the manufacture of polyether ether ketone plastics up to 0,3 % w/w of the final material.	
▼ M8			mixture composed of 97 % tetraethyl orthosilicate (TEOS) with CAS No 78-10-4 and 3 % hexamethyldisilazane (HMDS) with CAS No 999-97-3	no	yes	no			Only to be used for the production of recycled PET and at up to 0,12 % (w/w).	
▼ M9		1547-26-8	2,3,3,4,4,5,5-heptafluoro-1-pentene	no	yes	no			Only to be used together with tetrafluoroethylene and/or ethylene co-monomers to manufacture fluorocopolymers for application as polymer processing aid at up to 0,2 % w/w of the food contact	

▼ M9

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
									material, and when the low-molecular mass fraction below 1 500 Da in the fluorocopolymer does not exceed 30 mg/kg.	
1064		39318-18-8	tungsten oxide	yes	no	no	0,05		Stoichiometry: WO _n , n = 2,72-2,90	(25)
1065		85711-28-0	mixture of methyl-branched and linear C ₁₄ -C ₁₈ alkanamides, derived from fatty acids	yes	no	no	5		Only to be used in the manufacture of articles made of polyolefins, and which do not come into contact with foods for which food simulant D2 is assigned in Table 2 of Annex III.	(26)
▼ <u>M12</u>										
1066		23985-75-3	1,2,3,4-tetrahydronaphthalene-2,6-dicarboxylic acid, dimethyl ester	no	yes	no	0,05		Only to be used as a co-monomer in the manufacture of a polyester non-food contact layer in a plastic multilayer material, which is to be used only in contact with foods for which food simulants A, B, C and/or D1 are assigned in Table 2 of Annex III. The specific migration limit in column 8 refers to the sum of the substance and of its dimers (cyclic and open chain).	

▼ M12

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
1067		616-38-6	dimethyl carbonate	no	yes	no			<p>Only to be used:</p> <p>a) with 1,6-hexanediol in the manufacture of polycarbonate pre-polymers that are used at up to 30 % to manufacture thermoplastic polyurethanes with 4,4'-methylenediphenyldiisocyanate and diols, such as polypropylene glycol and 1,4-butanediol. The resulting material shall only be applied in repeated use articles intended to come into short-term contact (≤ 30 min at room temperature) with food for which simulants A and/or B are assigned in Table 2 of Annex III; or</p> <p>b) for the production of other polycarbonates and/or under other conditions provided that the migration of dimethyl carbonate does not exceed 0,05 mg/kg food and that the migration of all polycarbonate oligomers with a molecular weight below 1 000 Da together does not exceed 0,05 mg/kg food.</p>	(27)
1068		2530-83-8	[3-(2,3-epoxypropoxy)propyl]trimethoxy silane	no	yes	no			<p>Only to be used as a component of a sizing agent to treat glass fibres to be embedded in glass-fibre-reinforced low diffusivity plastics (polyethylene terephthalate (PET), polycarbonate (PC),</p>	

▼ **M12**

(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)
									polybutylene terephthalate (PBT), thermoset polyesters and epoxy bisphenol vinyl ester) in contact with all foodstuffs. In treated glass fibres, residues of the substance must not be detectable at 0,01 mg/kg for the substance and 0,06 mg/kg for each of the reaction products (hydrolysed monomers and epoxy-containing cyclic dimer, trimer and tetramer).	
1069		75-28-5	isobutane	yes	no	no			Only to be used as a blowing agent.	

▼ **B**

(¹) OJ L 302, 19.11.2005, p. 28.

(²) OJ L 330, 5.12.1998, p. 32.

(³) OJ L 253, 20.9.2008, p. 1.

► **M6** (⁴) Commission Regulation (EU) No 231/2012 of 9 March 2012 laying down specifications of food additives listed in Annexes II and III to Regulation (EC) No 1333/2008 of the European Parliament and of the Council (OJ L 83, 22.3.2012, p. 1). ◀

(⁵) OJ L 158, 18.6.2008, p. 17.

► **M1** (⁶) Infant as defined in Article 2(2)(a) of Regulation (EU) No 609/2013 of the European Parliament and of the Council of 12 June 2013 on food intended for infants and young children, food for special medical purposes, and total diet replacement for weight control and repealing Council Directive 92/52/EEC, Commission Directives 96/8/EC, 1999/21/EC, 2006/125/EC and 2006/141/EC, Directive 2009/39/EC of the European Parliament and of the Council and Commission Regulations (EC) No 41/2009 and (EC) No 953/2009 (OJ L 181, 29.6.2013, p. 35).

(⁷) This restriction is applicable from 1 May 2011 as regards the manufacture and from 1 June 2011 as regards the placing on the market and importation into the Union. ◀

► **M3** (⁸) OJ L 83, 22.3.2012, p. 1. ◀

► **M10** (⁹) Infant as defined in Article 2(2)(a) of Regulation (EU) No 609/2013.

(¹⁰) Young children as defined in Article 2(2)(b) of Regulation (EU) No 609/2013. ◀

▼B**2. Group restriction of substances**

Table 2 on Group restrictions contains the following information:

Column 1 (Group restriction No): contains the identification number of the group of substances for which the group restriction applies. It is the number referred to in Column 9 in Table 1 of this Annex.

Column 2 (FCM substance No): contains the unique identification numbers of the substances for which the group restriction applies. It is the number referred to in Column 1 in Table 1 of this Annex.

Column 3 (SML (T) [mg/kg]): contains the total specific migration limit for the sum of substances applicable to this group. It is expressed in mg substance per kg food. It is indicated ND if the substance shall not migrate in detectable quantities.

Column 4 (Group restriction specification): contains an indication of the substance whose molecular weight forms the basis for expression of the result.

Table 2

(1)	(2)	(3)	(4)
Group Restriction No	FCM substance No	SML (T) [mg/kg]	Group restriction specification
1	128 211	6	expressed as acetaldehyde
2	89 227 263 1048	30	expressed as ethyleneglycol
3	234 248	30	expressed as maleic acid
4	212 435	15	expressed as caprolactam
5	137 472	3	expressed as the sum of the substances
6	412 512 513 588	1	expressed as iodine
7	19 20	1,2	expressed as tertiary amine
8	317 318 319 359 431 464	6	expressed as the sum of the substances
9	650 695 697 698 726	0,18	expressed as tin

▼M7**▼B**

▼B

(1)	(2)	(3)	(4)
10	28 29 30 31 32 33 466 582 618 619 620 646 676 736	0,006	expressed as tin
11	66 645 657	1,2	expressed as tin
12	444 469 470	30	expressed as the sum of the substances
13	163 285	1,5	expressed as the sum of the substances
▼<u>M2</u>			
14	294 368 894	5	expressed as the sum of the substances and their oxidation products
▼<u>M6</u>			
15	98 196 344	15	expressed as formaldehyde
▼<u>B</u>			
16	407 583 584 599	6	expressed as boron Without prejudice to the provisions of Directive 98/83/EC
17	4 167 169 198 274 354 372 460 461 475 476 485 490 653	ND	expressed as isocyanate moiety

▼B

(1)	(2)	(3)	(4)
18	705 733	0,05	expressed as the sum of the substances
19	505 516 519	10	expressed as SO ₂
20	290 386 390	30	expressed as the sum of the substances
21	347 349	5	expressed as trimellitic acid
22	70 147 176 218 323 325 365 371 380 425 446 448 456 636	6	expressed as acrylic acid
23	150 156 181 183 184 355 370 374 439 440 447 457 482	6	expressed as methacrylic acid
24	756 758	5	expressed as the sum of the substances
25	720 747	0,05	sum of mono-n-dodecyltin tris(isooctylmercaptoacetate), di-n-dodecyltin bis(isooctyl mercaptoacetate), mono-dodecyltin trichloride and di-dodecyltin dichloride) expressed as the sum of mono- and di-dodecyltin chloride
26	728 729	9	expressed as the sum of the substances
27	188 291	5	expressed as isophthalic acid

▼B

(1)	(2)	(3)	(4)
28	191 192 785	7,5	expressed as terephthalic acid
29	342 672	0,05	expressed as the sum of 6-hydroxyhexanoic acid and caprolactone

▼M6

30	254 344 672	5	expressed as 1,4-butanediol
----	-------------------	---	-----------------------------

▼B

31	73 797	30	expressed as the sum of the substances
32	8 72 73 138 140 157 159 207 242 283 532 670 728 729 775 783 797 798 810 815	60	expressed as the sum of the substances

▼M3

33	180 874	ND	expressed as eugenol
----	------------	----	----------------------

▼M4

34	421 988	0,05	Expressed as 1,3-benzenedimethanamine
----	------------	------	---------------------------------------

▼M12

35	467 744 1059	0,05	expressed as crotonic acid
----	--------------------	------	----------------------------

▼B**3. Notes on verification of compliance**

Table 3 on notes on verification of compliance contains the following information:

Column 1 (Note No): contains the identification number of the Note. It is the number referred to in Column 11 in Table 1 of this Annex.

Column 2 (Notes on verification of compliance): contains rules that shall be respected when testing for compliance of the substance with specific migration limits or other restrictions or it contains remarks on situations where there is a risk of non-compliance.

▼ B

Table 3

(1)	(2)
Note No	Notes on verification of compliance
(1)	Verification of compliance by residual content per food contact surface area (QMA) pending the availability of an analytical method.
(2)	There is a risk that the SML or OML could be exceeded in fatty food simulants.
(3)	There is a risk that the migration of the substance deteriorates the organoleptic characteristics of the food in contact and then, that the final product does not comply with Article 3(1) c of the Framework Regulation (EC) No 1935/2004.
▼ M3	
(4)	Compliance testing when there is a fat contact ► M7 shall ◀ be performed using saturated fatty food simulants as simulant D2.
▼ B	
(5)	Compliance testing when there is a fat contact ► M7 shall ◀ be performed using isooctane as substitute of simulant D2 (unstable).
(6)	Migration limit might be exceeded at very high temperature.
(7)	If testing in food is performed, Annex V 1.4 shall be taken into account.
(8)	Verification of compliance by residual content per food contact surface area (QMA); QMA = 0,005 mg/6 dm ² .
(9)	Verification of compliance by residual content per food contact surface area (QMA) pending the availability of analytical method for migration testing. The ratio surface to quantity of food shall be lower than 2dm ² /kg.
(10)	Verification of compliance by residual content per food contact surface area (QMA) in case of reaction with food or simulant.
(11)	Only a method of analysis for the determination of the residual monomer in the treated filler is available.
(12)	There is a risk that the SML could be exceeded from polyolefins.
(13)	Only a method for determination of the content in polymer and a method for determination of the starting substances in food simulants are available.
(14)	There is a risk that the SML could be exceeded from plastics containing more than 0,5 % w/w of the substance.

▼ B

(1)	(2)
(15)	There is a risk that the SML could be exceeded in contact with foods with high alcoholic content.
(16)	There is a risk that the SML could be exceeded from low-density polyethylene (LDPE) containing more than 0,3 % w/w of the substance when in contact with fatty foods
(17)	Only a method for determination of the residual content of the substance in the polymer is available

▼ M2

(18)	There is a risk that the SML could be exceeded from low-density polyethylene (LDPE)
(19)	There is a risk that the OML could be exceeded in direct contact with aqueous foods from ethylvinylalcohol (EVOH) and polyvinylalcohol (PVOH) copolymers

▼ M4

(20)	The substance contains aniline as an impurity; verification of compliance with the restriction set for primary aromatic amines in Annex II (2) is necessary
------	---

▼ M6

(21)	In case of reaction with foods or simulants verification of compliance shall include verification that the migration limits of the hydrolysis products, formaldehyde and 1,4-butanediol, are not exceeded.
------	--

▼ M7

(22)	When used in contact with non-alcoholic foods for which Table 2 of Annex III assigns food simulant D1, food simulant C shall be used for verification of compliance instead of food simulant D1.
(23)	When a final material or article containing this substance is placed on the market, a well described method to determine whether the oligomer migration complies with the restrictions specified in column 10 of Table 1 shall form part of the supporting documentation referred to in Article 16. This method shall be suitable for use by a competent authority to verify compliance. If an adequate method is publicly available, reference shall be made to that method. If the method requires a calibration sample, a sufficient sample shall be supplied to the competent authority on its request.

▼ M8

(24)	The substance or its hydrolysis products are authorised food additives and compliance with Article 11(3) shall be verified.
------	---

▼ B

(1)	(2)
▼ <u>M9</u>	
(25)	When used as reheat agent in polyethylene terephthalate (PET) verification of compliance with the specific migration limit is not required; in all other cases compliance with the specific migration limit shall be verified in accordance with Article 18; the specific migration limit is expressed as mg tungsten/kg food.
(26)	Migration of stearamide, listed in Table 1 under FCM substance No 306 to which no specific migration limit applies, shall be excluded from verification of the compliance of the migration of the mixture with the specific migration limit laid down for the mixture.
▼ <u>M12</u>	
(27)	When a final material or article containing this substance and produced under conditions other than those described in point (a) column 10 of Table 1 is placed on the market, a well described method to determine whether the oligomer migration complies with the restrictions specified in point (b) column 10 of Table 1 shall form part of the supporting documentation referred to in Article 16. This method shall be suitable for use by a competent authority to verify compliance. If an adequate method is publicly available, reference shall be made to that method. If the method requires a calibration sample, a sufficient sample shall be supplied to the competent authority on its request.

▼ B

4. Detailed specification on substances

Table 4 on detailed specifications on substances contains the following information

Column 1 (FCM substance No): contains the unique identification number of the substances referred to in Column 1 in Table 1 of Annex I to which the specification applies.

Column 2 (Detailed specification on the substance): contains the specification on the substance.

Table 4

(1)	(2)	
FCM substance No	Detailed specification on the substance	
744	Definition	The copolymers are produced by the controlled fermentation of <i>Alcaligenes eutrophus</i> using mixtures of glucose and propanoic acid as carbon sources. The organism used has not been genetically engineered and has been derived from a single wildtype organism <i>Alcaligenes eutrophus</i> strain H16 NCIMB 10442. Master stocks of the organism are stored as freeze-dried ampoules. A submaster/working stock is prepared from the master stock and stored in liquid nitrogen and used to prepare inocula for the fermenter. Fermenter samples will be examined daily both microscopically and for any changes in colonial morphology on a variety of agars at different temperatures. The copolymers are isolated from heat treatment bacteria by controlled digestion of the other cellular components, washing and drying. These copolymers are normally offered as formulated, melt formed granules containing additives such as nucleating agents, plasticisers, fillers, stabilisers and pigments which all conform to the general and individual specifications
	Chemical name	Poly(3-D-hydroxybutanoate-co-3-D-hydroxypentanoate)
	CAS number	0080181-31-3
	Structural formula	$ \begin{array}{cccc} & & \text{CH}_3 & \\ & & & \\ \text{CH}_3 & \text{O} & \text{CH}_2 & \text{O} \\ & & & \\ (-\text{O}-\text{CH}-\text{CH}_2-\text{C}-)_m & - & (\text{O}-\text{CH}-\text{CH}_2-\text{C}-)_n & \\ \end{array} $ <p>where $n/(m + n)$ greater than 0 and less or equal to 0,25</p>

▼ **B**

(1)	(2)	
	Average molecular weight	Not less than 150 000 Daltons (measured by gel permeation chromatography)
	Assay	Not less than 98 % poly(3-D-hydroxybutanoate-co-3-D-hydroxy-pentanoate) analysed after hydrolysis as a mixture of 3-D-hydroxybutanoic and 3-D-hydroxypentanoic acids
	Description	White to off-white powder after isolation
	Characteristics	
	Identification tests:	
	Solubility	Soluble in chlorinated hydrocarbons such as chloroform or dichloromethane but practically insoluble in ethanol, aliphatic alkanes and water
	► M12 Restriction	Specific migration limit for crotonic acid is 0,05 mg/kg food ◀
	Purity	Prior to granulation the raw material copolymer powder must contain:
	— nitrogen,	Not more than 2 500 mg/kg of plastic
	— zinc,	Not more than 100 mg/kg of plastic
	— copper,	Not more than 5 mg/kg of plastic
	— lead,	Not more than 2 mg/kg of plastic
	— arsenic,	Not more than 1 mg/kg of plastic
	— chromium,	Not more than 1 mg/kg of plastic

▼ B*ANNEX II***Restrictions on materials and articles****▼ M7**

1. Plastic materials and articles shall not release the following substances in quantities exceeding the specific migration limits below:
 - Aluminium = 1 mg/kg food or food simulant
 - Barium = 1 mg/kg food or food simulant
 - Cobalt = 0,05 mg/kg food or food simulant
 - Copper = 5 mg/kg food or food simulant
 - Iron = 48 mg/kg food or food simulant
 - Lithium = 0,6 mg/kg food or food simulant
 - Manganese = 0,6 mg/kg food or food simulant
 - Zinc = 5 mg/kg food or food simulant.
2. Primary aromatic amines which are not listed in Table 1 of Annex I shall not migrate or shall not otherwise be released from plastic materials and articles into food or food simulant in accordance with Article 11(4). The detection limit referred to in the second subparagraph of Article 11(4) applies to the sum of primary aromatic amines released.

▼B*ANNEX III***Food simulants****1. Food simulants**

For demonstration of compliance for plastic materials and articles not yet in contact with food the food simulants listed in Table 1 below are assigned.

▼M7*Table 1***List of food simulants**

Food simulant	Abbreviation
Ethanol 10 % (v/v)	Food simulant A
Acetic acid 3 % (w/v)	Food simulant B
Ethanol 20 % (v/v)	Food simulant C
Ethanol 50 % (v/v)	Food simulant D1
Any vegetable oil containing less than 1 % unsaponifiable matter	Food simulant D2
poly(2,6-diphenyl-p-phenylene oxide), particle size 60-80 mesh, pore size 200 nm	Food simulant E

▼B**2. General assignment of food simulants to foods**

Food simulants A, B and C are assigned for foods that have a hydrophilic character and are able to extract hydrophilic substances. Food simulant B shall be used for those foods which have a pH below 4.5. Food simulant C shall be used for alcoholic foods with an alcohol content of up to 20 % and those foods which contain a relevant amount of organic ingredients that render the food more lipophilic.

Food simulants D1 and D2 are assigned for foods that have a lipophilic character and are able to extract lipophilic substances. Food simulant D1 shall be used for alcoholic foods with an alcohol content of above 20 % and for oil in water emulsions. Food simulant D2 shall be used for foods which contain free fats at the surface.

Food simulant E is assigned for testing specific migration into dry foods.

▼M7**3. Specific assignment of food simulants to foods for migration testing of materials and articles not yet in contact with food**

For testing migration from materials and articles not yet in contact with food the food simulants that corresponds to a certain food category shall be chosen according to Table 2 below.

For testing migration from materials and articles intended to come into contact with foods not listed in Table 2 below, or a combination of foods, the general food simulant assignments in point 2 shall be used for specific migration testing, and for overall migration testing the food simulant assignments in point 4 shall be applicable.

▼M7

Table 2 contains the following information:

- Column 1 (Reference number): contains the reference number of the food category
- Column 2 (Description of food): contains a description of the foods covered by the food category
- Column 3 (Food simulants): contains sub-columns for each of the food simulants

The food simulant for which a cross is contained in the respective sub-column of column 3 shall be used when testing migration of materials and articles not yet in contact with food.

For food categories where in sub-column D2 or E the cross is followed by an oblique stroke and a figure, the migration test result shall be corrected by dividing the result by this figure. The corrected test result shall then be compared to the migration limit to establish compliance. The test results for substances that shall not migrate in detectable quantities shall not be corrected in this way.

For food category 01.04 food simulant D2 shall be replaced by 95 % ethanol.

For food categories where in sub-column B the cross is followed by (*) the testing in food simulant B can be omitted if the food has a pH of more than 4,5.

For food categories where in sub-column D2 the cross is followed by (**) the testing in food simulant D2 can be omitted if it can be demonstrated that there is no 'fatty contact' with the plastic food contact material.

▼B

Table 2

food category specific assignment of food simulants

(1) Reference number	(2) Description of food	(3) Food simulants					
		A	B	C	D1	D2	E
01	Beverages						
01.01	Non-alcoholic beverages or alcoholic beverages of an alcoholic strength lower than or equal to 6 % vol.: A. Clear drinks: Water, ciders, clear fruit or vegetable juices of normal strength or concentrated, fruit nectars, lemonades, syrups, bitters, infusions, coffee, tea, beers, soft drinks, energy drinks and the like, flavoured water, liquid coffee extract		X(*)	X			

▼B

(1)	(2)	(3)					
Reference number	Description of food	Food simulants					
		A	B	C	D1	D2	E
	B. cloudy drinks: juices and nectars and soft drinks containing fruit pulp, musts containing fruit pulp, liquid chocolate		X(*)		X		
01.02	Alcoholic beverages of an alcoholic strength of between 6 %vol and 20 %.			X			
01.03	Alcoholic beverages of an alcoholic strength above 20 % and all cream liquors				X		
01.04	Miscellaneous: undenaturated ethyl alcohol		X(*)			Substitute 95 % ethanol	
02	Cereals, cereal products, pastry, biscuits, cakes and other bakers' wares						
02.01	Starches						X
02.02	Cereals, unprocessed, puffed, in flakes (including popcorn, corn flakes and the like)						X
02.03	Cereal flour and meal						X
02.04	Dry pasta e.g. macaroni, spaghetti and similar products and fresh pasta						X
02.05	Pastry, biscuits, cakes, bread, and other bakers' wares, dry:						
	A. With fatty substances on the surface					X/3	
	B. Other						X
02.06	Pastry, cakes, bread, dough and other bakers' wares, fresh:						
	A. With fatty substances on the surface					X/3	
	B. Other						X
03	Chocolate, sugar and products thereof Confectionery products						
03.01	Chocolate, chocolate-coated products, substitutes and products coated with substitutes					X/3	

▼ B

(1) Reference number	(2) Description of food	(3) Food simulants					
		A	B	C	D1	D2	E
		03.02	Confectionery products: A. In solid form: I. With fatty substances on the surface II. Other B. In paste form: I. With fatty substances on the surface II. Moist				
03.03	Sugar and sugar products A. In solid form: crystal or powder B. Molasses, sugar syrups, honey and the like					X/2	X
04	Fruit, vegetables and products thereof						
▼ <u>M7</u>							
04.01	Fruit, fresh or chilled: A. unpeeled and uncut B. peeled and/or cut						X/10
		X	X (*)				
▼ <u>B</u>							
04.02	Processed fruit: A. Dried or dehydrated fruits, whole, sliced, flour or powder B. Fruit in the form of purée, preserves, pastes or in its own juice or in sugar syrup (jams, compote, and similar products) C. Fruit preserved in a liquid medium: I. In an oily medium II. In an alcoholic medium						X
			X(*)	X			
						X	
					X		
04.03	Nuts (peanuts, chestnuts, almonds, hazelnuts, walnuts, pine kernels and others): A. Shelled, dried, flaked or powdered						X

▼ B

(1) Reference number	(2) Description of food	(3) Food simulants					
		A	B	C	D1	D2	E
	B. Shelled and roasted						X
	C. In paste or cream form	X				X	
	▼ <u>M7</u>						
04.04	Vegetables, fresh or chilled:						
	A. unpeeled and uncut						X/10
	B. peeled and/or cut	X	X (*)				
04.05	Processed vegetables:						X
	A. Dried or dehydrated vegetables whole, sliced or in the form of flour or powder.						
	B. (<i>obsolete</i>)						
	C. Vegetables in the form of purée, preserves, pastes or in its own juice (including pickled and in brine).		X (*)	X			
	D. Preserved vegetables:						
	I. In an oily medium	X				X	
	II. In an alcoholic medium				X		
	▼ <u>B</u>						
05	Fats and oils						
05.01	Animals and vegetable fats and oils, whether natural or treated (including cocoa butter, lard, resolidified butter)					X	
05.02	Margarine, butter and other fats and oils made from water emulsions in oil					X/2	
06	Animal products and eggs						
06.01	Fish:						
	A. Fresh, chilled, processed, salted or smoked including fish eggs	X				X/3(**)	
	B. Preserved fish:						
	I. In an oily medium	X				X	
	II. In an aqueous medium		X(*)	X			
06.02	Crustaceans and molluscs (including oysters, mussels, snails)						

▼B

(1) Reference number	(2) Description of food	(3) Food simulants					
		A	B	C	D1	D2	E
	A. Fresh within the shell						
	B. Shell removed, processed, preserved or cooked with the shell						
	I. In an oily medium	X				X	
	II. In an aqueous medium		X(*)	X			
06.03	Meat of all zoological species (including poultry and game):						
	A. Fresh, chilled, salted, smoked	X				X/4(**)	
	B. Processed meat products (such as ham, salami, bacon, sausages, and other) or in the form of paste, creams	X				X/4(**)	
	C. Marinated meat products in an oily medium	X				X	
06.04	Preserved meat:						
	A. In an fatty or oily medium	X				X/3	
	B. In an aqueous medium		X(*)		X		
06.05	Whole eggs, egg yolk, egg white						
	A. Powdered or dried or frozen						X
	B. Liquid and cooked				X		
07	Milk products						
07.01	Milk						
	A. Milk and milk based drinks whole, partly dried and skimmed or partly skimmed				X		
	B. Milk powder including infant formula (based on whole milk powder)						X
07.02	Fermented milk such as yoghurt, buttermilk and similar products		X(*)		X		
07.03	Cream and sour cream		X(*)		X		

▼ B

(1) Reference number	(2) Description of food	(3) Food simulants					
		A	B	C	D1	D2	E
		07.04	Cheeses:				
	A. Whole, with not edible rind						X
	B. Natural cheese without rind or with edible rind (gouda, camembert, and the like) and melting cheese					X/3(**)	
	C. Processed cheese (soft cheese, cottage cheese and similar)		X(*)		X		
	D. Preserved cheese:						
	I. In an oily medium	X				X	
	II. In an aqueous medium (feta, mozzarella, and similar)		X(*)		X		
08	Miscellaneous products						
08.01	Vinegar		X				
08.02	Fried or roasted foods:						
	A. Fried potatoes, fritters and the like	X				X/5	
	B. Of animal origin	X				X/4	
08.03	Preparations for soups, broths, sauces, in liquid, solid or powder form (extracts, concentrates); homogenised composite food preparations, prepared dishes including yeast and raising agents						
	A. Powdered or dried:						
	I. With fatty character					X/5	
	II. Other						X
	B. any other form than powdered or dried:						
	I. With fatty character	X	X(*)			X/3	
	II. Other		X(*)	X			
08.04	Sauces:						
	A. With aqueous character		X(*)	X			

▼B

(1)	(2)	(3)					
Reference number	Description of food	Food simulants					
		A	B	C	D1	D2	E
	B. With fatty character e.g. mayonnaise, sauces derived from mayonnaise, salad creams and other oil/water mixtures e.g. coconut based sauces	X	X(*)			X	
08.05	Mustard (except powdered mustard under heading 08.14)	X	X(*)			X/3(**)	
08.06	Sandwiches, toasted bread pizza and the like containing any kind of foodstuff						
	A. With fatty substances on the surface	X				X/5	
	B. Other						X
08.07	Ice-creams			X			
08.08	Dried foods:						
	A. With fatty substances on the surface					X/5	
	B. Other						X
08.09	Frozen or deep-frozen foods						X
08.10	Concentrated extracts of an alcoholic strength equal to or exceeding 6 % vol.		X(*)		X		
08.11	Cocoa:						
	A. Cocoa powder, including fat-reduced and highly fat reduced						X
	B. Cocoa paste					X/3	
08.12	Coffee, whether or not roasted, decaffeinated or soluble, coffee substitutes, granulated or powdered						X
08.13	Aromatic herbs and other herbs such as camomile, mallow, mint, tea, lime blossom and others						X
08.14	Spices and seasonings in the natural state such as cinnamon, cloves, powdered mustard, pepper, vanilla, saffron, salt and other						X
08.15	Spices and seasoning in oily medium such as pesto, curry paste					X	

▼ M8**4. Food simulant assignment for testing overall migration**

For tests to demonstrate compliance with the overall migration limit food simulants shall be chosen as set out in Table 3:

Table 3

Food simulant assignment for demonstrating compliance with the overall migration limit

Foods covered	Food simulants in which testing shall be performed
all types of food	1. distilled water or water of equivalent quality or food simulant A; 2. food simulant B; and 3. food simulant D2.
all types of food except for acidic foods	1. distilled water or water of equivalent quality or food simulant A; and 2. food simulant D2.
▼ M12 all aqueous and alcoholic foods and milk products with a pH \geq 4,5	food simulant D1
all aqueous and alcoholic foods and milk products with a pH < 4,5	food simulant D1 and food simulant B
▼ M8 all aqueous foods and alcoholic foods up to an alcohol content of 20 %	food simulant C
all aqueous and acidic foods and alcoholic foods up to an alcohol content of 20 %	1. food simulant C; and 2. food simulant B.

▼ M7**5. General derogation to the assignment of food simulants**

By derogation from the assignments of food simulants in points 2 to 4 of this Annex, where testing with several food simulants is required, a single food simulant shall be sufficient if on the basis of evidence acquired using generally recognised scientific methods this food simulant is shown to be the most severe food simulant for the particular material or article being tested under the applicable time and temperature conditions selected in accordance with Chapters 2 and 3 of Annex V.

The scientific basis on which this derogation is used shall in such cases form part of the documentation required under Article 16 of this Regulation.

▼ B*ANNEX IV***Declaration of compliance**

The written declaration referred to in Article 15 shall contain the following information:

- (1) the identity and address of the business operator issuing the declaration of compliance;
- (2) the identity and address of the business operator which manufactures or imports the plastic materials or articles or products from intermediate stages of their manufacturing or the substances intended for the manufacturing of those materials and articles;
- (3) the identity of the materials, the articles, products from intermediate stages of manufacture or the substances intended for the manufacturing of those materials and articles;
- (4) the date of the declaration;

▼ M7

- (5) confirmation that the plastic materials or articles, products from intermediate stages of manufacture or the substances meet the relevant requirements laid down in this Regulation and in Article 3, 11(5), 15 and 17 of Regulation (EC) No 1935/2004;

▼ B

- (6) adequate information relative to the substances used or products of degradation thereof for which restrictions and/or specifications are set out in Annexes I and II to this Regulation to allow the downstream business operators to ensure compliance with those restrictions;
- (7) adequate information relative to the substances which are subject to a restriction in food, obtained by experimental data or theoretical calculation about the level of their specific migration and, where appropriate, purity criteria in accordance with Directives 2008/60/EC, 95/45/EC and 2008/84/EC to enable the user of these materials or articles to comply with the relevant EU provisions or, in their absence, with national provisions applicable to food;
- (8) specifications on the use of the material or article, such as:
 - (i) type or types of food with which it is intended to be put in contact;
 - (ii) time and temperature of treatment and storage in contact with the food;

▼ M8

- (iii) the highest food contact surface area to volume ratio for which compliance has been verified in accordance with Article 17 and 18 or equivalent information;

▼ B

- (9) when a functional barrier is used in a multi-layer material or article, the confirmation that the material or article complies with the requirements of Article 13(2), (3) and (4) or Article 14(2) and (3) of this Regulation.

▼B

ANNEX V

COMPLIANCE TESTING

For testing compliance of migration from plastic food contact materials and articles the following general rules apply.

CHAPTER 1

Testing for specific migration of materials and articles already in contact with food**1.1. Sample preparation**

The material or article shall be stored as indicated on the packaging label or under conditions adequate for the packaged food if no instructions are given. The food shall be removed from contact with the material or article before its expiration date or any date by which the manufacturer has indicated the product should be used for reasons of quality or safety.

1.2. Conditions of testing

The food shall be treated in accordance with the cooking instructions on the package if the food is to be cooked in the package. Parts of the food which are not intended to be eaten shall be removed and discarded. The remainder shall be homogenised and analysed for migration. The analytical results shall always be expressed on the basis of the food mass that is intended to be eaten, in contact with the food contact material.

1.3. Analysis of migrated substances

The specific migration is analysed in the food using an analytical method in accordance with the requirements of Article 11 of Regulation (EC) No 882/2004.

▼M7**1.4. Account of substances originating from other sources**

In case there is evidence linked to the food sample that a substance partially or wholly originates from a source or sources other than the material or article for which the test is being carried out, the test results shall be corrected for the amount of that substance originating from the other source or sources before comparing the test results to the applicable specific migration limit.

▼B

CHAPTER 2

Testing for specific migration of materials and articles not yet in contact with food**2.1. Verification method**

Verification of compliance of migration into foods with the migration limits shall be carried out under the most extreme conditions of time and temperature foreseeable in actual use taking into account paragraphs 1.4, 2.1.1, 2.1.6 and 2.1.7.

Verification of compliance of migration into food simulants with the migration limits shall be carried out using conventional migration tests according to the rules set out in paragraphs 2.1.1 to 2.1.7.

▼B2.1.1. *Sample preparation*

The material or article shall be treated as described by accompanying instructions or by provisions given in the declaration of compliance.

Migration is determined on the material or article or, if this is impractical, on a specimen taken from the material or article, or a specimen representative of this material or article. For each food simulant or food type, a new test specimen is used. Only those parts of the sample which are intended to come into contact with foods in actual use shall be placed in contact with the food simulant or the food.

2.1.2. *Choice of food simulant*

Materials and articles intended for contact with all types of food shall be tested with food simulant A, B and D2. However, if substances that may react with acidic food simulant or foods are not present testing in food simulant B can be omitted.

Materials and articles intended only for specific types of foods shall be tested with the food simulants indicated for the food types in Annex III.

2.1.3. *Conditions of contact when using food simulants***▼M7**

The sample shall be placed in contact with the food simulant in a manner representing the worst of the foreseeable conditions of use as regard contact time in Table 1 and as regard contact temperature in Table 2.

By way of derogation to the conditions set out in Tables 1 and 2, the following rules apply:

- (i) If it is found that carrying out the tests under the combination of contact conditions specified in Tables 1 and 2 causes physical or other changes in the test specimen which do not occur under worst foreseeable conditions of use of the material or article under examination, the migration tests shall be carried out under the worst foreseeable conditions of use in which these physical or other changes do not take place;
- (ii) if the material or article during its intended use is subjected only to precisely controlled time and temperature conditions in food processing equipment, either as part of food packaging or as part of the processing equipment itself, testing may be done using the worst foreseeable contact conditions that can occur during the processing of the food in that equipment;
- (iii) if the material or article is intended to be employed only for hot-fill conditions, only a 2-hour test at 70 °C shall be carried out. However, if the material or article is intended to be used also for storage at room temperature or below, the test conditions set out in Tables 1 and 2 of this Section or in Section 2.1.4 of this Chapter apply depending on the duration of storage.

▼ M7

If the testing conditions representative for the worst foreseeable conditions of intended use of the material or article, are not technically feasible in food simulant D2, migration tests shall be done using ethanol 95 % and isooctane. In addition a migration test shall be done using food simulant E if the temperature under the worst foreseeable conditions of intended use exceeds 100 °C. The test that results in the highest specific migration shall be used to establish compliance with this Regulation.

▼ B

Table 1

▼ M7

Selection of test time

▼ B

Contact time in worst foreseeable use	► <u>M7</u> Time to be selected for testing ◀
$t \leq 5$ min	5 min
$5 \text{ min} < t \leq 0,5$ hour	0,5 hour
$0,5 \text{ hours} < t \leq 1$ hour	1 hour
$1 \text{ hour} < t \leq 2$ hours	2 hours
$2 \text{ hours} < t \leq 6$ hours	6 hours
$6 \text{ hours} < t \leq 24$ hours	24 hours
$1 \text{ day} < t \leq 3$ days	3 days
$3 \text{ days} < t \leq 30$ days	10 days
Above 30 days	See specific conditions

▼ M7

Table 2

Selection of test temperature

Worst foreseeable contact temperature	Contact temperature to be selected for testing
$T \leq 5$ °C	5 °C
$5 \text{ °C} < T \leq 20$ °C	20 °C
$20 \text{ °C} < T \leq 40$ °C	40 °C
$40 \text{ °C} < T \leq 70$ °C	70 °C
$70 \text{ °C} < T \leq 100$ °C	100 °C or reflux temperature
$100 \text{ °C} < T \leq 121$ °C	121 °C (*)
$121 \text{ °C} < T \leq 130$ °C	130 °C (*)
$130 \text{ °C} < T \leq 150$ °C	150 °C (*)
$150 \text{ °C} < T < 175$ °C	175 °C (*)
$175 \text{ °C} < T \leq 200$ °C	200 °C (*)
$T > 200$ °C	225 °C (*)

(*) This temperature shall be used only for food simulants D2 and E. For applications heated under pressure, migration testing under pressure at the relevant temperature may be performed. For food simulants A, B, C or D1 the test may be replaced by a test at 100 °C or at reflux temperature for duration of four times the time selected according to the conditions in Table 1.

▼ M7**2.1.4. Specific conditions for contact times above 30 days at room temperature and below**

For contact times above 30 days (long term) at room temperature and below, the specimen shall be tested in accelerated test conditions at elevated temperature for a maximum of 10 days at 60 °C ⁽¹⁾.

- (a) Testing for 10 days at 20 °C shall cover all storage times at frozen condition. This test can include the freezing and defrosting processes if labelling or other instructions ensure that 20 °C is not exceeded and the total time above – 15 °C does not exceed 1 day in total during the foreseeable intended use of the material or article.
- (b) Testing for 10 days at 40 °C shall cover all storage times at refrigerated and frozen conditions including hot-fill conditions and/or heating up to 70 °C ≤ T ≤ 100 °C for maximum $t = 120/2^{((T-70)/10)}$ minutes.
- (c) Testing for 10 days at 50 °C shall cover all storage times of up to 6 months at room temperature, including hot-fill conditions and/or heating up to 70 °C ≤ T ≤ 100 °C for maximum $t = 120/2^{((T-70)/10)}$ minutes.
- (d) Testing for 10 days at 60 °C shall cover storage above 6 months at room temperature and below, including hot-fill conditions and/or heating up to 70 °C ≤ T ≤ 100 °C for maximum $t = 120/2^{((T-70)/10)}$ minutes.
- (e) For storage at room temperature the testing conditions can be reduced to 10 days at 40 °C if it is shown by scientific evidence that migration of the respective substance in the polymer has reached equilibration under this test condition.
- (f) For worst foreseeable conditions of intended use not covered by the test conditions set out in points (a) to (e), the testing time and temperature conditions shall be based on the following formula:

$$t_2 = t_1 * \text{Exp} (9627 * (1/T_2 - 1/T_1))$$

t_1 is the contact time

t_2 is the testing time

T_1 is the contact temperature in Kelvin. For room temperature storage this is set at 298K (25 °C). For refrigerated conditions it is set at 278K (5 °C). For frozen storage it is set at 258 K (– 15 °C).

T_2 is the testing temperature in Kelvin.

⁽¹⁾ When testing at these accelerated test conditions the test specimen shall not undergo any physical or other changes compared to the real conditions of use, including a phase transition of the material.

▼ B2.1.5. *Specific conditions for combinations of contact times and temperature***▼ M7**

If a material or article is intended for different applications covering different combinations of contact time and temperature the testing shall be restricted to the test conditions which are recognised to be the most severe on the basis of scientific evidence.

▼ B

If the material or article is intended for a food contact application where it is successively subject to a combination of two or more times and temperatures, the migration test shall be carried out subjecting the test specimen successively to all the applicable worst foreseeable conditions appropriate to the sample, using the same portion of food simulant.

2.1.6. *Repeated use articles*

If the material or article is intended to come into repeated contact with foods, the migration test(s) shall be carried out three times on a single sample using another portion of food simulant on each occasion. Its compliance shall be checked on the basis of the level of the migration found in the third test.

However, if there is conclusive proof that the level of the migration does not increase in the second and third tests and if the migration limits are not exceeded on the first test, no further test is necessary.

▼ M7

The material or article shall respect the specific migration limit already in the first test for substances that are prohibited from migrating or from being released in detectable quantities under Article 11(4).

▼ B2.1.7. *Analysis of migrating substances*

At the end of the prescribed contact time, the specific migration is analysed in the food or food simulant using an analytical method in accordance with the requirements of Article 11 of Regulation (EC) No 882/2004.

2.1.8. *Verification of compliance by residual content per food contact surface area (QMA)*

For substances which are unstable in food simulant or food or for which no adequate analytical method is available it is indicated in Annex I that verification of compliance shall be undertaken by verification of residual content per 6 dm² of contact surface. For materials and articles between 500 ml and 10 l the real contact surface is applied. For materials and articles below 500 ml and above 10 l as well as for articles for which it is impractical to calculate the real contact surface the contact surface is assumed to be 6 dm² per kg food.

2.2. **Screening approaches****▼ M7**

To screen if a material or article complies with the migration limits any of the following approaches can be applied which are considered at least as severe as the verification method described in section 2.1.

▼B**2.2.1. *Replacing specific migration by overall migration***

To screen for specific migration of non-volatile substances, determination of overall migration under test conditions at least as severe as for specific migration can be applied.

2.2.2. *Residual content*

To screen for specific migration the migration potential can be calculated based on the residual content of the substance in the material or article assuming complete migration.

▼M7**2.2.3. *Migration modelling***

To screen for specific migration, the migration potential can be calculated based on the residual content of the substance in the material or article applying generally recognised diffusion models based on scientific evidence that are constructed in a way that must never underestimate real levels of migration.

2.2.4. *Food simulant substitutes*

To screen for specific migration, food simulants can be replaced by substitute food simulants if it is based on scientific evidence that the substitute food simulants result in migration that is at least as severe as migration that would be obtained using the food simulants specified in Section 2.1.2.

2.2.5. *Single test for successive combinations of time and temperature*

If the material or article is intended for a food contact application where it is successively subject to two or more time and temperature combinations, a single migration contact test time can be defined based on the highest contact test temperature from Section 2.1.3 and/or 2.1.4 by using the equation as described in point (f) of Section 2.1.4. The reasoning justifying that the resulting single test is at least as severe as the combined time and temperature combinations shall be documented in the supporting documentation provided for in Article 16.

▼B**CHAPTER 3*****Testing for overall migration***

Overall migration testing shall be performed under the standardised testing conditions set out in this chapter.

3.1. *Standardised testing conditions*

The overall migration test for materials and articles intended for the food contact conditions described in column 3 of Table 3 shall be performed for the time specified and at the temperature specified in column 2. For test OM5 the test can be performed either for 2 hours at 100 °C (food simulant D2) or at reflux (food simulant A, B, C, D1) or for 1 hour at 121 °C. The food simulant shall be chosen in accordance with Annex III.

▼B

If it is found that carrying out the tests under the contact conditions specified in Table 3 causes physical or other changes in the test specimen which do not occur under worst foreseeable conditions of use of the material or article under examination, the migration tests shall be carried out under the worst foreseeable conditions of use in which these physical or other changes do not take place.

▼M7

Table 3

Standardised conditions for testing the overall migration

Column 1	Column 2	Column 3
Test number	Contact time in days [d] or hours [h] at contact temperature in [°C] for testing	Intended food contact conditions
OM1	10 d at 20 °C	Any food contact at frozen and refrigerated conditions.
OM2	10 d at 40 °C	Any long term storage at room temperature or below, including when packaged under hot-fill conditions, and/or heating up to a temperature T where $70\text{ °C} \leq T \leq 100\text{ °C}$ for a maximum of $t = 120/2^{(T-70)/10}$ minutes.
OM3	2 h at 70 °C	Any food contact conditions that include hot-fill and/or heating up to a temperature T where $70\text{ °C} \leq T \leq 100\text{ °C}$ for maximum of $t = 120/2^{(T-70)/10}$ minutes, which are not followed by long term room temperature or refrigerated storage.
OM4	1 h at 100 °C	High temperature applications for all types of food at temperature up to 100 °C.
OM5	2 h at 100 °C or at reflux or alternatively 1 h at 121 °C	High temperature applications up to 121 °C.
OM6	4 h at 100 °C or at reflux	Any food contact conditions at a temperature exceeding 40 °C, and with foods for which point 4 of Annex III assigns simulants A, B, C or D1.
OM7	2 h at 175 °C	High temperature applications with fatty foods exceeding the conditions of OM5.

Test OM7 also covers food contact conditions described for OM1, OM2, OM3, OM4 and OM5. It represents the worst case conditions for food simulant D2 in contact with non-polyolefins. In case it is technically not feasible to perform OM 7 with food simulant D2 the test can be replaced as set out in Section 3.2.

Test OM6 covers also food contact conditions described for OM1, OM2, OM3, OM4 and OM5. It represents worst case conditions for food simulants A, B, C and D1 in contact with non-polyolefins.

▼M7

Test OM5 covers also food contact conditions described for OM1, OM2, OM3, and OM4. It represents the worst case conditions for all food simulants in contact with polyolefins.

Test OM2 covers also food contact conditions described for OM1 and OM3.

3.2. Substitute overall migration tests for tests with food simulant D2

If it is not technically feasible to perform one or more of the tests OM1 to OM6 in food simulant D2, migration tests shall be done using ethanol 95 % and isooctane. In addition a test shall be done using food simulant E in case the worst foreseeable conditions of use exceed 100 °C. The test that results in the highest specific migration shall be used to establish compliance with this Regulation.

In case it is technically not feasible to perform OM7 with food simulant D2 the test can be replaced by either test OM8 or test OM9 as appropriate given the intended or foreseeable use. Both tests involve testing at two test conditions for which a new test sample shall be used for each test. The test condition that results in the highest overall migration shall be used to establish compliance with this Regulation.

Test number	Test conditions	Intended food contact conditions	Covers the intended food contact conditions described in
OM8	Food simulant E for 2 hours at 175 °C and food simulant D2 for 2 hours at 100 °C	High temperature applications only	OM1, OM3, OM4, OM5 and OM6
OM9	Food simulant E for 2 hours at 175 °C and food simulant D2 for 10 days at 40 °C	High temperature applications including long term storage at room temperature	OM1, OM2, OM3, OM4, OM5 and OM6

3.3. Verification of compliance

3.3.1. Single use articles and materials

At the end of the prescribed contact time, to verify compliance the overall migration is analysed in the food simulant using an analytical method in accordance with the requirements of Article 11 of Regulation (EC) No 882/2004.

3.3.2. Repeated use articles and materials

The applicable overall migration test shall be carried out three times on a single sample using another portion of food simulant on each occasion. The migration shall be determined using an analytical method in accordance with the requirements of Article 11 of Regulation (EC) No 882/2004. The overall migration in the second test shall be lower than in the first test, and the overall migration in the third test shall be lower than in the second test. Compliance with the overall migration limit shall be verified on the basis of the level of the overall migration found in the third test.

▼ M7

If it is not technically feasible to test the same sample three times, such as when testing in oil, the overall migration test can be carried out by testing different samples for three different periods of time lasting one, two and three times the applicable contact test time. The difference between the third and the second test results shall be considered to represent the overall migration. Compliance shall be verified on the basis of this difference, which shall not exceed the overall migration limit. In addition, it shall not be higher than the first result and the difference between the second and the first test results.

By derogation from the first paragraph, if, on the basis of scientific evidence, it is established that for the material or article being tested the overall migration does not increase in the second and third tests and if the overall migration limit is not exceeded in the first test, the first test alone shall be sufficient.

▼ B**3.4. Screening approaches****▼ M7**

To screen if a material or article complies with the migration limits, any of the following approaches can be applied which are considered at least as severe as the verification method described in Sections 3.1 and 3.2.

▼ B**3.4.1. Residual content**

To screen for overall migration the migration potential can be calculated based on the residual content of migratable substances determined in a complete extraction of the material or article.

▼ M7**3.4.2. Food simulant substitutes**

To screen for overall migration, food simulants can be replaced if based on scientific evidence the substitute food simulants result in migration that is at least as severe as migration that would be obtained using the food simulants specified in Annex III.

▼ B**CHAPTER 4*****Correction factors applied when comparing migration test results with migration limits*****4.1. Correction of specific migration in foods containing more than 20 % fat by the Fat Reduction Factor (FRF)**

For lipophilic substances for which in Annex I it is indicated in column 7 that the FRF is applicable the specific migration can be corrected by the FRF. The FRF is determined according to the formula $FRF = (g \text{ fat in food/kg of food})/200 = (\% \text{ fat} \times 5)/100$.

The FRF shall be applied according to the following rules.

The migration test results shall be divided by the FRF before comparing with the migration limits.

The correction by the FRF is not applicable in the following cases:

- (a) when the material or article is or is intended to be brought in contact with food intended for infants and young children as defined by Directives 2006/141/EC and 2006/125/EC;

▼ B

- (b) for materials and articles for which it is impracticable to estimate the relationship between the surface area and the quantity of food in contact therewith, for example due to their shape or use, and the migration is calculated using the conventional surface area/volume conversion factor of 6 dm²/kg.

▼ M7

The specific migration in food or food simulant shall not exceed 60 mg/kg food before application of the FRF.

When testing is performed in food simulant D2 or E and when the test results are corrected in application of the correction factor laid down in Table 2 of Annex III this correction may be applied in combination with the FRF by multiplying both factors. The combined correction factor shall not exceed 5, unless the correction factor laid down in Table 2 of Annex III exceeds 5.



ANNEX VI

Correlation tables

Directive 2002/72/EC	This Regulation
Article 1(1)	Article 1
Article 1(2), (3) and (4)	Article 2
Article 1a	Article 3
Article 3(1), Article 4(1) and Article 5	Article 5
Article 4(2), Article 4a(1) and (4), Article 4d, Annex II (2) and (3) and Annex III (2) and (3)	Article 6
Article 4a(3) and (6)	Article 7
Annex II (4) and Annex III (4)	Article 8
Article 3(1) and Article 4(1)	Article 9
Article 6	Article 10
Article 5a(1) and Annex I (8)	Article 11
Article 2	Article 12
Article 7a	Article 13
Article 9(1) and (2)	Article 15
Article 9(3)	Article 16
Article 7 and Annex I (5a)	Article 17
Article 8	Article 18
Annex II (3) and Annex III (3)	Article 19
Annex I, Annex II, Annex IV, Annex IVa, Annex V Part B, and Annex VI	Annex I
Annex II (2), Annex III (2) and Annex V, Part A	Annex II
Article 8(5) and Annex VIa	Annex IV
Annex I	Annex V

Directive 93/8/EEC	This Regulation
Article 1	Article 11
Article 1	Article 12
Article 1	Article 18
Annex	Annex III
Annex	Annex V

Directive 97/48/EC	This Regulation
Annex	Annex III
Annex	Annex V